### POLITECNICO DI TORINO Repository ISTITUZIONALE

#### Enhanced latent thermal energy battery with additive manufacturing

Original

Enhanced latent thermal energy battery with additive manufacturing / Morciano, Matteo; Alberghini, Matteo; Fasano, Matteo; Almiento, Mariella; Calignano, Flaviana; Manfredi, Diego; Asinari, Pietro; Chiavazzo, Eliodoro. - In: JOURNAL OF PHYSICS. CONFERENCE SERIES. - ISSN 1742-6588. - 2766:(2024). (Intervento presentato al convegno Eurotherm 2024 tenutosi a Bled, Slovenia) [10.1088/1742-6596/2766/1/012220].

Availability: This version is available at: 11583/2990289 since: 2024-07-03T09:02:55Z

Publisher: IOP Publishing Ltd

Published DOI:10.1088/1742-6596/2766/1/012220

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

#### **PAPER • OPEN ACCESS**

# Enhanced latent thermal energy battery with additive manufacturing

To cite this article: Matteo Morciano et al 2024 J. Phys.: Conf. Ser. 2766 012220

View the article online for updates and enhancements.

#### You may also like

- <u>Review—The Synthesis and</u> <u>Characterization of Recent Two-</u> <u>Dimensional Materials for Energy Storage</u> <u>Applications</u> Shraddha Dhanraj Nehate, Sreeram Sundaresh, Ashwin Kumar Saikumar et al.
- <u>High-resolution simulations of the</u> thermophysiological effects of human <u>exposure to 100 MHz RF energy</u> David A Nelson, Allen R Curran, Hans A Nyberg et al.
- The relationship between specific absorption rate and temperature elevation in anatomically based human body models for plane wave exposure from 30 MHz to 6 GHz

Akimasa Hirata, Ilkka Laakso, Takuya Oizumi et al.



Joint International Meeting of The Electrochemical Society of Japar (ECSJ) The Korean Electrochemical Society (KECS) The Electrochemical Society (ECS)

HONOLULU,HI October 6-11, 2024



Early Registration Deadline: **September 3, 2024** 

MAKE YOUR PLANS



This content was downloaded from IP address 130.192.21.38 on 03/07/2024 at 09:59

## Enhanced latent thermal energy battery with additive manufacturing

Matteo Morciano<sup>1,2</sup>, Matteo Alberghini<sup>1,2</sup>, Matteo Fasano<sup>1,2</sup>, Mariella Almiento<sup>1</sup>, Flaviana Calignano<sup>3</sup>, Diego Manfredi<sup>4</sup>, Pietro Asinari<sup>1,5</sup> and Eliodoro Chiavazzo<sup>1,2</sup>

<sup>1</sup>Department of Energy, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129 Torino, Italy

<sup>2</sup>Clean Water Center, Corso Duca degli Abruzzi 24, Torino

<sup>3</sup>Department of Management and Production Engineering, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129 Torino, Italy

<sup>4</sup>Department of Applied Science and Technology, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129 Turin, Italy

<sup>5</sup>INRIM, Istituto Nazionale di Ricerca Metrologica, Strada delle Cacce 91, Torino

E-mail: matteo.morciano@polito.it

Abstract. The low thermal conductivity of Phase Change Materials (PCMs), such as paraffin waxes, hinders efficient latent heat storage, especially for rapid charging and discharging cycles. To address this issue, this study explores experimentally and numerically the use of metal additive manufacturing to create a latent heat storage system operating at medium temperatures (around 90°C). A 3D Cartesian metal lattice is manufactured through laser powder bed fusion to optimize heat conduction within the PCM. Experimental tests show impressive specific power densities (approximately 714  $\pm$  17 W kg<sup>-1</sup> during charging and 1310  $\pm$  48 W kg<sup>-1</sup> during discharging). Moreover, the device exhibits stability over multiple cycles. Finally, the validated finite-element model has the potential to provides a basis for general design guidelines to boost the system's performance further. Potential applications of this technology are highlighted in the automotive industry, where such systems could efficiently manage thermal energy, for instance, by capturing excess heat from an engine's cooling radiator to expedite the warm-up process during a cold start, which is a critical phase for reducing pollutant emissions.

#### 1. Introduction

Thermal energy storage (TES) is crucial for enhancing sustainability in various sectors, such as solar [1-5] and automotive [6,7] industries, enabling efficient utilization of intermittent heat sources. Latent TES, based on phase change materials (PCMs), offers higher energy density and precise heat release control compared to sensible TES [8,9]. Paraffin waxes are commonly used PCMs for medium temperatures, but their low thermal conductivity limits specific power, leading to longer charge and discharge times. Previous approaches have introduced highly conductive fillers like graphite nanoparticles [10-16] or foams [2, 17, 18] to enhance thermal conductivity. However, achieving uniform filler dispersion remains challenging. In contrast, the inclusion of 2D metal grids in paraffin matrices has shown promise for heat transfer improvement. Metal additive manufacturing offers the potential to take this concept further by producing complex 3D structures with high porosity and surface-to-volume ratio [19–24].

Content from this work may be used under the terms of the Creative Commons Attribution 4.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

This article utilizes metal additive manufacturing to create a 3D Cartesian metal lattice for improving latent heat storage performance with paraffin waxes at around 80 °C fusion temperatures. The study includes numerical simulations and experimental tests to assess energy storage and release, charge and discharge times, and power density. Notably, specific powers of approximately 714  $\pm$  17 W kg<sup>-1</sup> and 1310  $\pm$  48 W kg<sup>-1</sup> are achieved during charging and discharging, respectively, with stable device performance over multiple cycles [25]. The intended application is in the automotive sector to recover and reuse waste heat from engine cooling systems for reducing cold-start emissions.

#### 2. Materials and Methods

In this study, an innovative TES system was investigated with the goal of achieving rapid thermal charge and discharge cycles. The system employed a three-dimensional metal structure fabricated through laser powder bed fusion (L-PBF) [26–28], which was subsequently infiltrated with paraffin wax. This unique design aimed to leverage the high thermal conductivity of the metal lattice to homogenize the temperature of the PCM matrix and reduce its melting and solidification times. Additionally, the metal lattice served as a heat exchanger between a heat-transfer fluid (HTF) and the TES system.

The designed metal structure, represented in Fig. 1, had a cubic shape (80 mm  $\times$  80 mm  $\times$  80 mm) with an internal Cartesian lattice consisting of identical hollow cubic elements (6 mm side). The HTF flowed through both an inner duct and external fins on the device's surface, facilitating heat transfer. The 3D Cartesian lattice was fabricated using an aluminum alloy powder bed, AlSi10Mg, via L-PBF, a technique that utilizes a laser beam to melt metal powders layer by layer. The resulting device had a mass of approximately 630 g and a porosity of 71%. A test bench was employed to evaluate the TES system's performance, comprising a 20 L water tank, an electric heater, a volumetric pump, three thermocouples, and a data acquisition (DAQ) system. During testing, the water in the tank was heated by the electric heater, and a three-way valve directed the hot water toward the TES prototype and back to the tank. Thermocouples were used to measure water temperatures at the inlet and outlet of the prototype, as well as ambient temperature. Paraffin wax with a melting temperature of about 70°C was chosen as the PCM, and the HTF flow rate was set at 3.3 L/min, typical for automotive TES systems.



Figure 1. Design of the heat storage prototype. (A) Single hollow cubic element used to create the ordered Cartesian lattice. (B) 3D CAD model of the device realized. A STL file of the device can be downloaded from the Supplementary Material. All the quotes are expressed in mm. (C) Picture of the realized prototype. Picture taken from Ref [25], under licence CC BY 4.0.

A finite elements model implemented using COMSOL Multiphysics was used to simulate the device's behavior. The model considered energy conservation within the PCM and fluid flow

within the HTF channels [25]. The fusion and solidification of paraffin wax were modeled using the apparent specific heat capacity method, which models the latent heat as a temperaturedependent function presenting peaks at the characteristic temperatures of phase change, to be added to the specific heat capacity. Material properties such as density, thermal conductivity, and specific heat capacity were provided for aluminum, wood, and mineral wool. Extensive details are reported in Ref. [25].

#### 3. Results

The charge and discharge processes of the device manufactured were tested both experimentally and numerically. In particular, the experimental results were used to validate the FEM model developed in COMSOL Multiphysics (see Fig. 2). The system demonstrated an impressive energy storage capacity, capable of storing approximately 125 kJ of thermal energy. One of the most remarkable features of the TES prototype was its charging and discharging time. In detail, the characteristic time required to store or release 90% of the available latent heat (i.e.,  $t_{90}$ ) was equal to 176 ± 4 seconds (see Fig. 2a) and 88 ± 3 seconds (see Fig. 2b) for the charging and discharging phases, respectively. This rapid charging/discharging time is particularly crucial for applications where quick response times are required, such as renewable energy integration and automotive systems. The specific power density during both charging and discharging processes was also notable, with values ranging from approximately 714 W/kg to 1310 W/kg during charging. This indicates the TES system's capability to absorb and release energy quickly and efficiently [25].

Moreover, numerical simulations provided a detailed understanding of the PCM's melting process within the TES system. These simulations revealed that the PCM near the HTF channels melted rapidly, around 50 seconds into the process (see Fig. 2c). Subsequently, it took an additional 40 seconds for the PCM surrounding the metal lattice to be completely melted. The remainder of the process relied on thermal diffusion within the PCM. The incorporation of the 3D-printed metal lattice within the TES system significantly enhanced heat transfer efficiency. The lattice structure, with its high thermal conductivity, effectively homogenized the temperature distribution within the PCM, reducing both the melting and solidification times.

Finally, the TES prototype experimentally demonstrated stability and repeatability over multiple cycles, affirming its reliability for long-term use [25]. This stability is a crucial characteristic for applications that require consistent thermal energy management.

#### 4. Discussion and Conclusions

This study demonstrated the promising potential of additive manufacturing, specifically laser powder bed fusion, for creating innovative latent thermal energy storage systems. The rapid charge and discharge capabilities, along with high power density, make such systems suitable for various applications, including automotive and renewable energy. The integration of phase change materials, such as paraffin wax, into the design allowed for substantial energy storage through latent heat. Moving forward, future research could focus on optimizing the 3Dprinted lattice structure, potentially altering the size and geometry of elementary cells to enhance performance further. Additionally, investigating the scalability of this technology for larger or industrial-scale applications would be of great interest, paving the way for broader adoption of this innovative TES system. In summary, this research highlights the significant advancements achievable in thermal energy storage through additive manufacturing techniques, offering solutions for efficient and rapid thermal energy management in various domains.

#### 4.1. Acknowledgments

The authors are grateful to the NANOSTEP (La Ricerca dei Talenti, Fondazione CRT – Torino) project. E.C. acknowledges partial support of the Italian National Project PRIN Heat transfer



Figure 2. Thermal energy storage performance of the device: numerical results. Analysis of the percentage of the melted volume of PCM ( $\alpha$ , red data) and thermal energy stored (A) or released (B) during the charging and discharging phases. Simulation results show that the tested conditions lead to faster solidification rather than melting. (C) Liquid volume fraction  $\alpha$  of the PCM during the simulated charging process at different time frames. Picture taken from Ref [25], under licence CC BY 4.0.

and Thermal Energy Storage Enhancement by Foams and Nanoparticles (2017F7KZWS).

#### 4.2. Declarations

This proceeding is a summary of the results published in *Journal of Energy Storage* (see Ref. [25]: doi.org/10.1016/j.est.2023.107350).

#### References

- [1] Xu J, Wang R and Li Y 2014 Solar Energy 103 610-638
- [2] Liu G, Du Z, Xiao T, Guo J, Lu L, Yang X and Hooman K 2022 International Journal of Thermal Sciences 182 107809
- [3] Liu G, Xiao T, Guo J, Wei P, Yang X and Hooman K 2022 Applied Thermal Engineering 212 118564
- [4] Bologna A, Fasano M, Bergamasco L, Morciano M, Bersani F, Asinari P, Meucci L and Chiavazzo E 2020 Applied Sciences 10 4771
- [5] Giagnorio M, Morciano M, Zhang W, Hélix-Nielsen C, Fasano M and Tiraferri A 2022 Desalination 543 116083
- [6] Narayanan S, Li X, Yang S, Kim H, Umans A, McKay I S and Wang E N 2015 Applied Energy 149 104–116
- [7] Narayanan S, Kim H, Umans A, Yang S, Li X, Schiffres S N, Rao S R, McKay I S, Perez C A R, Hidrovo C H et al. 2017 Applied Energy 189 31–43
- [8] Sharma A, Tyagi V V, Chen C and Buddhi D 2009 Renewable and Sustainable energy reviews 13 318-345
- [9] Han G G, Li H and Grossman J C 2017 Nature Communications 8 1446
- [10] Wang J, Xie H and Xin Z 2009 Thermochimica Acta 488 39–42
- [11] Kim S and Drzal L T 2009 Solar Energy Materials and Solar Cells 93 136-142
- [12] Sari A and Karaipekli A 2007 Applied Thermal Engineering 27 1271–1277
- [13] Lin C and Rao Z 2017 Applied Thermal Engineering 110 1411–1419
- [14] Fasano M, Bigdeli M B, Sereshk M R V, Chiavazzo E and Asinari P 2015 Renewable and Sustainable Energy Reviews 41 1028–1036
- [15] Li M 2013 Applied energy 106 25–30
- [16] Ribezzo A, Bergamasco L, Morciano M, Fasano M, Mongibello L and Chiavazzo E 2023 Applied Thermal Engineering 231 120907
- [17] Abujas C R, Jové A, Prieto C, Gallas M and Cabeza L F 2016 Renewable energy 97 434-443
- [18] Zhang P, Meng Z, Zhu H, Wang Y and Peng S 2017 Applied Energy 185 1971–1983
- [19] du Plessis A, Razavi S M J, Benedetti M, Murchio S, Leary M, Watson M, Bhate D and Berto F 2021 Progress in Materials Science 100918
- [20] Righetti G, Savio G, Meneghello R, Doretti L and Mancin S 2020 International Journal of Thermal Sciences 153 106376
- [21] Mancin S, Diani A, Doretti L, Hooman K and Rossetto L 2015 International Journal of Thermal Sciences 90 79–89
- [22] Hu X and Gong X 2020 Applied Thermal Engineering 175 115337
- [23] Diani A, Nonino C and Rossetto L 2022 Applied Thermal Engineering 215 118969
- [24] Chiavazzo E, Ventola L, Calignano F, Manfredi D and Asinari P 2014 Experimental Thermal and Fluid Science 55 42–53
- [25] Morciano M, Alberghini M, Fasano M, Almiento M, Calignano F, Manfredi D, Asinari P and Chiavazzo E 2023 Journal of Energy Storage 65 107350
- [26] Calignano F, Cattano G and Manfredi D 2018 Journal of Materials Processing Technology 255 773-783
- [27] Ventola L, Robotti F, Dialameh M, Calignano F, Manfredi D, Chiavazzo E and Asinari P 2014 International Journal of Heat and Mass Transfer 75 58–74
- [28] Fasano M, Ventola L, Calignano F, Manfredi D, Ambrosio E P, Chiavazzo E and Asinari P 2016 International Communications in Heat and Mass Transfer 74 36–39