# POLITECNICO DI TORINO Repository ISTITUZIONALE

# Crack deflection in brittle materials by Finite Fracture Mechanics

Original

Crack deflection in brittle materials by Finite Fracture Mechanics / Sapora, ALBERTO GIUSEPPE; Cornetti, Pietro; Carpinteri, Alberto; Mantic, Vladislav. - In: PROCEDIA STRUCTURAL INTEGRITY. - ISSN 2452-3216. - 2:(2016), pp. 1975-1982. (Intervento presentato al convegno 21st European Conference on Fracture, ECF21 tenutosi a Catania, Italy nel 20-24 June 2016) [10.1016/j.prostr.2016.06.248].

Availability: This version is available at: 11583/2651648 since: 2016-10-03T16:39:13Z

Publisher: Elsevier

Published DOI:10.1016/j.prostr.2016.06.248

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)





Available online at www.sciencedirect.com



Procedia Structural Integrity 2 (2016) 1975-1982

Structural Integrity
Procedia

www.elsevier.com/locate/procedia

# 21st European Conference on Fracture, ECF21, 20-24 June 2016, Catania, Italy Crack deflection in brittle materials by Finite Fracture Mechanics

Alberto Sapora<sup>a,\*</sup>, Pietro Cornetti<sup>a</sup>, Alberto Carpinteri<sup>a</sup>, Vladislav Mantič<sup>b</sup>

<sup>a</sup>Department of Structural, Geotechnical and Building Engineering, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129 Torino, Italy <sup>b</sup>Group of Elasticity and Strength of Materials, School of Engineering, Universidad de Sevilla, Camino de los Descubrimientos s/n, 41092 Sevilla, Spain

# Abstract

When dealing with mixed-mode brittle fracture of cracked elements, *T*-stress affects both the stress field and the energy balance. This problem is investigated here through the coupled Finite Fracture Mechanics (FFM) criterion by varying mode mixity of the main crack. Results are presented in terms of the critical stress intensity factors (SIF) and the critical kinking angle. As concerns pure mode *I* loading conditions, if T > 0 is large enough, the crack ceases to propagate collinearly and the critical SIF deviates from the fracture toughness of the material. On the other hand, for mode *II* loading conditions, if T < 0 is sufficiently low, the critical SIF ceases to increase and the critical kinking angle jumps to an infinitesimal value.

© 2016, PROSTR (Procedia Structural Integrity) Hosting by Elsevier Ltd. All rights reserved. Peer-review under responsibility of the Scientific Committee of PCF 2016.

Keywords: Crack kinking, brittle fracture, FFM;

# 1. Introduction

*T*-stress effects on crack kinking in brittle fracture mechanics have been investigated since seventies (Williams and Ewing, 1972; Carpinteri et al., 1979; Cotterell and Rice, 1980; Kariahaloo, 1981; Yukio et al., 1983; Sumi et al., 1985; He et al., 1991; Becker et al., 2001; Christopher et al., 2007; Lazzarin et al., 2009), but it was only since the middle of nineties, that failure criteria based on a linear-elastic analysis combined with an internal material length have been successfully proposed (Kosai et al., 1993; Seweryn, 1998; Smith et al., 2001).

More recently, also coupled stress and energy approaches of FFM were formalized in this framework. Leguillon and Murer (2008) modified the criterion proposed in Leguillon (2002) to include *T*-stress effects: the analysis was carried out numerically, by a two-scale asymptotic matching procedure (Leguillon, 1993). On the other hand, in the present work, the problem is faced by the approach put forward in Cornetti et al. (2006): the criterion is similar to that presented in Leguillon and Murer (2008), but the stress condition is averaged and not of punctual type (Cornetti et al., 2014; Sapora and Mantic, 2016). It is important to remark that according to FFM, the crack advance becomes a structural parameter, allowing to remove some inconsistencies related to the criteria previously introduced.

<sup>\*</sup> Corresponding author. Tel.: +39-011-0904911 ; fax: +39-011-0904899.

E-mail address: alberto.sapora@polito.it

<sup>2452-3216 © 2016,</sup> PROSTR (Procedia Structural Integrity) Hosting by Elsevier Ltd. All rights reserved. Peer review under responsibility of the Scientific Committee of PCF 2016. 10.1016/j.prostr.2016.06.248

The FFM analysis is carried out by exploiting asymptotic expressions for the asymptotic stress field and the crack driving force available in the Literature (Amestoy and Leblond, 1992; Seweryn, 1998). The coupled equations providing the critical load and kinking angle are derived analytically and then solved numerically. It is found that positive *T*-stresses decrease both the critical failure load and the critical kinking angle, whereas an opposite trend is observed for negative *T*-values. Furthermore, in pure mode *I* loading conditions, there exists a critical threshold  $T_+ > 0$  above which the crack ceases to propagate collinearly and the critical mode *I* SIF  $K_{If}$  deviates from the fracture toughness  $K_{Ic}$  of the material (Cotterell and Rice, 1980; Smith et al., 2001; Leguillon and Murer, 2008; Cornetti et al., 2014). On the contrary, under mode *II* loading conditions (indeed, note that  $K_I = 0$  does not represent, strictly speaking, a pure mode *II* condition since T = 0 corresponds to a symmetrical load), theoretical predictions show an infinitesimal critical kinking angle and a unit limit value for the ratio between the critical mode *II* SIF  $K_{IIf}$  and  $K_{Ic}$ , below a critical value  $T_- < 0$  (Sapora and Mantic, 2016).

#### 2. FFM criterion

The coupled FFM criterion by Cornetti et al. (2006); Carpinteri et al. (2008) is based on the assumption of a finite crack extension  $\Delta$  and on the contemporaneous fulfilment of two conditions. The former is a stress requirement: the average circumferential stress  $\sigma_{\theta\theta}(r,\theta)$  on  $\Delta$ , prior to the crack extension, must be greater than the material tensile strength  $\sigma_u$ . By referring to a cracked element with a polar reference system placed at the notch root (Fig.1), we have in formulae:

$$\int_{0}^{\Delta} \sigma_{\theta\theta}(r,\theta) \mathrm{d}r \ge \sigma_{u} \Delta. \tag{1}$$

The latter is the energy balance: the integral of the crack-driving force on  $\Delta$ , representing the energy available for a crack increment, must be higher than the fracture energy ( $G_c$ ) times the crack increment  $\Delta$ . By means of Irwin's relationships, the condition can be expressed in terms of the SIFs related to the kinked crack,  $k_I$  and  $k_{II}$  for mode I and mode II, respectively, and of the fracture toughness  $K_{Ic}$ , namely:

$$\int_0^{\Delta} [k_I(c,\theta)^2 + k_{II}(c,\theta)^2] \mathrm{d}c \ge K_{Ic}^2 \Delta.$$
<sup>(2)</sup>

The FFM criterion is thus described by the coupled inequalities (1) and (2), and in order to be implemented the functions  $\sigma_{\theta\theta}$ ,  $k_I$  and  $k_{II}$  are required.

#### 2.1. Stress field and SIFs functions

By taking the *T*-stress effects into account, the circumferential stress field  $\sigma_{\theta\theta}(r, \theta)$  at the crack tip can be approximated as (see Fig.1 with c = 0):

$$\sigma_{\theta\theta}(r,\theta) = \frac{K_I}{\sqrt{2\pi}r} f^I_{\theta\theta}(\theta) + \frac{K_{II}}{\sqrt{2\pi}r} f^{II}_{\theta\theta}(\theta) + T\sin^2\theta,$$
(3)

where  $K_I, K_{II}$  are the SIFs related to the main crack and  $f_{\theta\theta}^I, f_{\theta\theta}^{II}$  are two angular functions (see the Appendix, Eq. (A.1)). On the other hand, by dimensional analysis concepts and the principle of superposition, the SIFs related to a



Fig. 1. Cracked element with polar coordinate system and kinked crack of length c.

kinked crack of length c can be expressed as (He et al., 1991; Amestoy and Leblond, 1992):

$$k_I(c,\theta) = \beta_{11}(\theta)K_I + \beta_{12}(\theta)K_{II} + \beta_1(\theta)T\sqrt{c}, \qquad (4)$$

and

$$k_{II}(c,\theta) = \beta_{21}(\theta)K_I + \beta_{22}(\theta)K_{II} + \beta_2(\theta)T\sqrt{c}.$$
(5)

Approximating analytical expressions for the angular functions  $\beta$  presented by Amestoy and Leblond (1992) are reported in the Appendix (Eqs. (A.2)-(A.7)). Tabulated values can be also found in Tada et al. (1985); Melin (1994); Fett et al. (2004). Note that  $\beta_2, \beta_{12}$  and  $\beta_{21}$  are odd functions, whereas  $\beta_1, \beta_{11}$  and  $\beta_{22}$  result to be even.

Before proceeding, let us now introduce, for the sake of clarity:

- the functions *f*<sup>i</sup><sub>θθ</sub> = √2/π f<sup>i</sup><sub>θθ</sub> (*i* = *I*,*II*);
  the mode-mixity related to the main crack, ψ = arctan(K<sub>II</sub>/K<sub>I</sub>).
- the characteristic length,  $l_{ch} = (K_{Ic}/\sigma_u)^2$ ;
- the dimensionless crack advance,  $\delta = \Delta/l_{ch}$ ;
- the dimensionless *T*-stress,  $\tau = T \sqrt{l_{ch}} / \sqrt{K_I^2 + K_{II}^2}$ ;
- the combinations for the angular functions,

$$\overline{\beta}_1 = \beta_1 \beta_{11} + \beta_2 \beta_{21}, \quad \overline{\beta}_2 = \beta_1 \beta_{12} + \beta_2 \beta_{22}, \quad \overline{\beta}_{11} = \beta_{11}^2 + \beta_{21}^2, \quad \overline{\beta}_{22} = \beta_{12}^2 + \beta_{22}^2, \quad \overline{\beta}_{12} = 2(\beta_{11}\beta_{12} + \beta_{21}\beta_{22}), \quad \overline{\beta}_{11} = \beta_{11}^2 + \beta_{21}^2, \quad \overline{\beta}_{12} = \beta_{12}^2 + \beta_{22}^2, \quad \overline{\beta}_{12} = \beta_{12}^2 + \beta_{12}^2 +$$

#### 2.2. Implementation and results

At incipient failure  $(K_I = K_{If})$ , the coupled conditions (1) and (2) become a system of two equations in two unknowns: the critical crack advancement  $\delta_c$  and the failure load, implicitly embedded in the  $K_{If}$  function. The substitution of Eqs. (3), (4) and (5) into Eqs. (1) and (2) provides after some simple manipulations (Cornetti et al.,



Fig. 2. *T*-stress effects on FFM fracture loci. From the top to the bottom, curves refer to  $\tau = -0.3, -0.2, -0.1, 0$  (dashed line), 0.1, 0.2, 0.3.

2014):

$$\begin{cases} \frac{K_{If}}{K_{Ic}} = \frac{\sqrt{\delta}}{\overline{f}_{\theta\theta}^{I} + \tan\psi\overline{f}_{\theta\theta}^{II} + \overline{\tau}\sin^{2}\theta}, \\ \delta = \frac{(\overline{f}_{\theta\theta}^{I} + \tan\psi\overline{f}_{\theta\theta}^{II} + \overline{\tau}\sin^{2}\theta)^{2}}{(\overline{\beta}_{11} + \overline{\beta}_{12}\tan\psi + \overline{\beta}_{22}\tan^{2}\psi) + \frac{4\overline{\tau}}{3}(\overline{\beta}_{1} + \overline{\beta}_{2}\tan\psi) + \frac{\overline{\tau}^{2}}{2}(\beta_{1}^{2} + \beta_{2}^{2})}, \end{cases}$$
(6)

where  $\bar{\tau} = \tau \sqrt{\delta(1 + \tan \psi)}$ , for the sake of simplicity.

Observe that, for given loading and structural properties,  $\psi$  and  $\tau$  are fixed. In order to implement FFM, the latter equation in (6) should be firstly solved: a different crack advance  $\delta$  corresponds to a different kinking angle  $\theta$ . Each couple ( $\delta$ ,  $\theta$ ) must be substituted into the former equation: the actual crack advance  $\delta_c$  and critical kinking angle  $\theta_c$  are those which minimize the  $K_{If}$  function. The relationship  $K_{IIf} = \tan \psi K_{If}$  then provides the corresponding value for  $K_{IIf}$ .

FFM results are presented in Figs. 2 and 3, for the fracture loci and the critical kinking angle, respectively. By assuming  $K_I, K_{II} > 0$ , as T increases, the failure load decreases, as well as the critical kinking angle  $\theta_c$ , which tends asymptotically towards  $-90^\circ$ .

As concerns pure mode *I* loading conditions ( $K_{II} = 0$ ), if T > 0 is sufficiently large,  $\tau \ge \tau_+ = 0.42$ , the crack does not propagate collinearly any more ( $\theta_c$  different from 0°) and  $K_{If}$  deviates from  $K_{Ic}$ . This phenomenon has been already described in the Literature (Cotterell and Rice, 1980; Smith et al., 2001; Leguillon and Murer, 2008; Cornetti et al., 2014) on the basis of some experimental observations (Selvarathinam and Goree, 1998; Chao et al., 2001). FFM predictions are presented in Figs. 4 and 5. The present results, showing nearly continuous functions, are in qualitative agreement with those derived in Smith et al. (2001), but slightly differ from those proposed in Leguillon and Murer (2008) where the existence of a  $\theta_c$ -jump from 0° to  $-72^\circ$  was detected at a threshold tensile  $\tau_+ = 0.704$ . On the other hand, in the case of a compressive *T*-stress (T < 0), the straight crack path always reveals to be stable.



Fig. 3. *T*-stress effects on FFM critical kinking angle. From the top to the bottom, curves refer to  $\tau = -0.3, -0.2, -0.1, 0$  (dashed line), 0.1, 0.2, 0.3.

As regards mode *II* loading conditions ( $K_I = 0$ ), an increasing tensile *T*-stress provides decreasing kinking angles  $\theta_c$  from  $-75.5^{\circ}$  (T = 0, Sapora et al. (2014)) to  $-90^{\circ}$  ( $T \to \infty$ ). The trend is similar for compressive *T*-stress till the threshold  $\tau = \tau_- \simeq -0.325$ . Below  $\tau_-$ , the kinking angle becomes infinitesimal and  $K_{IIf}$  keeps equals to  $K_{Ic}$  (Figs. 4 and 5). The reason of this behavior is imputable to the fact that the shear contribution to the strain energy release rate prevails and the maximum released energy corresponds to  $\theta_c = 0^{\circ}$ . In order for the stress requirement in (1) to match this condition, the crack advance (which is not reported here) must become infinitesimal too, so that tensile stresses result to be high enough.

In order to overcome this drawback, as suggested by Sapora and Mantic (2016), let us observe that estimates of the toughening of elements under shear should consider possible local plastic and viscoelastic dissipation, crack face asperity shielding and frictional effects: the assumption of  $G_c$  to be constant is reasonable only if the  $G_I$ -contribution to the energy release rate (ERR) prevails, whereas a larger amount of dissipated energy should be associated to crack kinking dominated by  $G_{II}$  (Hutchinson and Suo, 1992; Liechti and Chai, 1992; Banks-Sills and Ashkenazi, 2000; Mantič et al., 2006). One of the most implemented fracture criterion writes (Hutchinson and Suo, 1992):

$$\frac{G_I}{G_{Ic}} + \frac{G_{II}}{G_{IIc}} = 1, \tag{7}$$

where  $G_{IIc} = G_{Ic}/\gamma$  has the interpretation of pure mode *II* toughness and  $\gamma$  is a parameter weighting the mode *II*contribution. It vanishes for  $\gamma \rightarrow 0$ , whereas  $\gamma = 1$  corresponds to an ideally brittle material. Note that the condition  $\gamma \rightarrow 0$  provides the basis for the well-known  $k_{II} = 0$  criterion proposed on the basis of simple symmetry arguments by Goldstein and Salganik (1974), and that an analogous relationship to (7) was adopted by Seweryn (1998) and suggested by Leguillon and Murer (2008).



Fig. 4. T-stress effects on FFM failure loads for pure mode I and mode II loading conditions.



Fig. 5. T-stress effects on FFM critical kinking angle for pure mode I and mode II loading conditions.

In order to improve FFM predictions (Sapora and Mantic, 2016), from an equivalent point of view, one could consider the following modified ERR in the energy balance:

$$\overline{G} = G_I + \gamma G_{II}.$$
(8)

# 3. Conclusions

It was shown that *T*-stress effects reveal to be more significant for i) sufficiently high *T*-magnitudes; ii) prevailing mode *II* conditions; iii) less brittle materials (i.e., higher  $l_{ch}$ ). Indeed, for a specific test, since all the parameters  $K_I, K_{II}$  and *T* generally vary as the mode mixity  $\psi$  varies, the real impact of *T*-stress on predictions should be discussed from case to case, after evaluating these three parameters. Whereas for mode *I* loading conditions the crack propagation reveals to be unstable for  $\tau \ge 0.42$ , for mode *II* loading conditions a singular behavior was observed for  $\tau \le -0.325$ .

# Acknowledgements

The financial support of V Plan Propio de Investigación de la Universidad de Sevilla (Modalidad I.6C), the Spanish Ministry of Economy and Competitiveness and European Regional Development Fund (Project MAT2012-37387), the Junta de Andaluca and the European Social Fund (Project TEP-04051) are also gratefully acknowledged. Eventually, Dr. Alberto Sapora acknowledges the hospitality of Universidad de Sevilla, where this work was mostly accomplished.

## Appendix A. Angular functions

The following equations hold for what concerns the angular functions related to the stress field:

$$f^{I}_{\theta\theta}(\theta) = \cos^{3}(\theta/2), \qquad f^{II}_{\theta\theta}(\theta) = -3\sin(\theta/2)\cos^{2}(\theta/2)$$
 (A.1)

whereas the approximating expressions for the functions  $\beta$  in Eq. (4) and (5) can be found in Amestoy and Leblond (1992), with  $m = \theta/\pi$ :

$$\beta_{11} = 4.1m^{20} + 1.63m^{18} - 4.059m^{16} + 2.996m^{14} - 0.0925m^{12} - 2.88312m^{10} + 5.0779m^8 + (\pi^2/9 - 11\pi^4/72 + 119\pi^6/15360)m^6 + (\pi^2 - 5\pi^4/128)m^4 - 3\pi^2m^2/8 + 1,$$
(A.2)

$$\beta_{12} = 4.56m^{19} + 4.21m^{17} - 6.915m^{15} + 4.0216m^{13} + 1.5793m^{11} - 7.32433m^9 + 12.313906m^7 + (-2\pi - 133\pi^3/180 + 59\pi^5/1280)m^5 + (10\pi/3 + \pi^3/16)m^3 - 1.5\pi m,$$
(A.3)

$$\beta_{21} = -1.32m^{19} - 3.95m^{17} + 4.684m^{15} - 2.07m^{13} - 1.534m^{11} + 4.44112m^9 - 6.176023m^7 + (-2\pi/3 + 13\pi^3/30 - 59\pi^5/3840)m^5 - (4\pi/3 + \pi^3/48)m^3 + \pi/2m,$$
(A.4)

$$\beta_1 = -13.7m^{20} - 2.85m^{18} + 10.947m^{16} - 7.314m^{14} - 6.0205m^{12} + 26.66807m^{10} - 50.70880m^8 + 63.665987m^6 - 47.93339m^4 + (2\pi)^{3/2}m^2,$$
(A.6)

$$\beta_2 = 6.62m^{19} + 9.69m^{17} - 12.781m^{15} + 3.043m^{13} + 15.6222m^{11} - 39.90249m^9 + 61.174444m^7 + -59.565733m^5 + 12\sqrt{2\pi}m^3 - 2\sqrt{2\pi}m.$$
(A.7)

## References

- Amestoy, M., Leblond, J.B., 1992. Crack paths in plane situations ii. detailed form of the expansion of the stress intensity factors. International Journal of Solids and Structures 29, 465–501.
- Banks-Sills, L., Ashkenazi, D., 2000. A note on fracture criteria for interface fracture. International Journal of Fracture 103, 177-188.
- Becker, T.L., Cannon, R.M., Ritchie, R.O., 2001. Finite crack kinking and *T*-stresses in functionally graded materials. International Journal of Solids and Structures 38, 5545–5563.
- Carpinteri, A., Cornetti, P., Pugno, N., Sapora, A., Taylor, D., 2008. A finite fracture mechanics approach to structures with sharp V-notches. Engineering Fracture Mechanics 75, 1736–1752.
- Carpinteri, A., DiTommaso, A., Viola, E., 1979. Collinear stress effect on the crack branching phenomenon. Matériaux et Construction 12, 439–446.
- Chao, Y.J., Liu, S., Broviak, B.J., 2001. Brittle fracture: Variation of fracture toughness with constraint and crack curving under mode I conditions. Experimental Mechanics 41, 232–241.
- Christopher, C.J., James, M.N., Patterson, E.A., Tee, K.F., 2007. Towards a new model of crack tip stress fields. International Journal of Fracture 148, 361–371.
- Cornetti, P., N.Pugno, Carpinteri, A., D.Taylor, 2006. Finite fracture mechanics: a coupled stress and energy failure criterion. Engineering Fracture Mechanics 73, 2021–2033.
- Cornetti, P., Sapora, A., Carpinteri, A., 2014. *T*-stress effects on crack kinking in finite fracture mechanics. Engineering Fracture Mechanics 132, 169–176.
- Cotterell, B., Rice, J.R., 1980. Slightly curved or kinked cracks. International Journal of Fracture 16, 155–169.

Fett, T., Pham, V.B., Bahr, H.A., 2004. Weight functions for kinked semi-infinite cracks. Engineering Fracture Mechanics 71, 1987–1995.

- Goldstein, R., Salganik, R., 1974. Brittle fracture of solids with arbitrary cracks. International Journal of Fracture 10, 507–523.
- He, M.Y., Bartlett, A., Evans, A.G., Hutchinson, J.W., 1991. Kinking of a crack out of an interface: Role of in-plane stress. Journal of the American Ceramic Society 74, 767–771.
- Hutchinson, J., Suo, Z., 1992. Mixed mode cracking in layered materials. Advances in Applied Mechanics 29, 63-191.
- Kariahaloo, B., 1981. On crack kinking and curving. Mechanics of Materials 1, 189-201.
- Kosai, M., Kobayashi, A.S., Ramulu, M., 1993. Tear straps in airplane fuselage. In: Durability of Metal Aircraft Structures. Atlanta Technology Publications. Atlanta, USA.
- Lazzarin, P., Berto, F., Radaj, D., 2009. Fatigue-relevant stress field parameters of welded lap joints: pointed slit tip compared with keyhole notch. Fatigue & Fracture of Engineering Materials & Structures 32, 713–735.
- Leguillon, D., 1993. Asymptotic and numerical analysis of a crack branching in non-isotropic materials. European Journal of Mechanics A/Solids 12, 33–51.
- Leguillon, D., 2002. Strength or toughness? a criterion for crack onset at a notch. European Journal of Mechanics A/Solids 21, 61-72.
- Leguillon, D., Murer, S., 2008. Crack deflection in a biaxial stress state. International Journal of Fracture 150, 75-90.
- Liechti, K., Chai, Y., 1992. Asymmetric shielding in interfacial fracture under in-plane shear. Journal of Applied Mechanics 59, 295–304.
- Mantič, V., Blázquez, A., Correa, E., París, F., 2006. Analysis of interface cracks with contact in composites by 2D BEM. In: Fracture and Damage of Composites, p. 189-248, Guagliano M, Aliabadi MH, editors. WIT Press.
- Melin, S., 1994. Accurate data for stress intensity factors at infinitesimal kinks. Journal of the Applied Mechanics 61, 467-470.
- Sapora, A., Cornetti, P., Carpinteri, A., 2014. V-notched elements under mode II loading conditions. Structural Engineering and Mechanics 49, 499–508.
- Sapora, A., Mantic, V., 2016. Finite fracture mechanics: a deeper investigation on negative T-stress effects. International Journal of Fracture 197, 111–118.
- Selvarathinam, A.S., Goree, J.G., 1998. T-stress based fracture model for crack in isotropic materials. Engineering Fracture Mechanics 60, 543–561.
- Seweryn, A., 1998. A non-local stress and strain energy release rate mixed mode fracture initiation and propagation criteria. Engineering Fracture Mechanics 59, 737–760.
- Smith, D.J., Ayatollahi, M.R., Pavier, M.J., 2001. The role of T-stress in brittle fracture for linear elastic materials under mixed-mode loading. Fatigue Fract Engng Mater Struct 24, 137–150.
- Sumi, Y., Nemat-Nasser, S., Keer, L.M., 1985. On crack path stability in a finite body. Engineering Fracture Mechanics 22, 759–771.
- Tada, H., Paris, P.C., Irwin, G.R., 1985. The Stress Analysis of Cracks Handbook. Paris Productions Incorporated. St Louis, MO, USA.
- Williams, J.G., Ewing, P.D., 1972. Fracture under complex stress the angled crack problem. International Journal of Fracture Mechanics 8, 441–446.
- Yukio, U., Kazuo, I., Tetsuya, Y., Mitsuru, A., 1983. Characteristics of brittle fracture under general combined modes including those under bi-axial tensile loads. Engineering Fracture Mechanics 18, 1131–1158.

1982