

Catalytic stability of a Ni-Catalyst towards biogas reforming in the presence of deactivating trace compounds

*Original*

Catalytic stability of a Ni-Catalyst towards biogas reforming in the presence of deactivating trace compounds / Papurello, Davide; Chiodo, Vitaliano; Maisano, Susanna; Lanzini, Andrea; Santarelli, Massimo. - In: RENEWABLE ENERGY. - ISSN 0960-1481. - ELETTRONICO. - 127:(2018), pp. 481-494. [10.1016/j.renene.2018.05.006]

*Availability:*

This version is available at: 11583/2728436 since: 2019-03-15T08:45:36Z

*Publisher:*

Elsevier Ltd

*Published*

DOI:10.1016/j.renene.2018.05.006

*Terms of use:*

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

*Publisher copyright*

Elsevier postprint/Author's Accepted Manuscript


© 2018. This manuscript version is made available under the CC-BY-NC-ND 4.0 license  
<http://creativecommons.org/licenses/by-nc-nd/4.0/>. The final authenticated version is available online at:  
<http://dx.doi.org/10.1016/j.renene.2018.05.006>

(Article begins on next page)

# Accepted Manuscript

Catalytic Stability of a Ni-Catalyst Towards Biogas Reforming in the Presence of Deactivating Trace Compounds

Davide Papurello, Vitaliano Chiodo, Susanna Maisano, Andrea Lanzini, Massimo Santarelli



PII: S0960-1481(18)30525-1  
DOI: 10.1016/j.renene.2018.05.006  
Reference: RENE 10058  
To appear in: *Renewable Energy*  
Received Date: 23 June 2017  
Revised Date: 27 March 2018  
Accepted Date: 02 May 2018

Please cite this article as: Davide Papurello, Vitaliano Chiodo, Susanna Maisano, Andrea Lanzini, Massimo Santarelli, Catalytic Stability of a Ni-Catalyst Towards Biogas Reforming in the Presence of Deactivating Trace Compounds, *Renewable Energy* (2018), doi: 10.1016/j.renene.2018.05.006

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

# Catalytic stability of a Ni-catalyst towards biogas reforming in the presence of deactivating trace compounds

Davide Papurello<sup>b\*</sup>, Vitaliano Chiodo<sup>a</sup>, Susanna Maisano<sup>a</sup>, Andrea Lanzini<sup>b</sup>, Massimo Santarelli<sup>b</sup>

<sup>a</sup> *Institute CNR-ITAE “Nicola Giordano”, Via S. Lucia sopra Contesse, 5 – 98126, Messina, Italy*

<sup>b</sup> *Department of Energy, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129, Torino – Italy*

\*Corresponding author. Tel.: +393402351692. Email address: [davide.papurello@polito.it](mailto:davide.papurello@polito.it)

## Abstract

Trace compounds contained in the produced biogas range from tens to thousands of ppm(v) and the gas cleaning is crucial, as much as it is important the investigation of the trace compounds impact on the reforming section and on the SOFC performance. The catalytic stability of a Ni-catalyst towards biogas reforming in the presence of three types of deactivating compounds (sulfur, siloxanes and aromatic compounds) was investigated. When the biogas is composed of a methane to carbon dioxide ratio >1 under the tested operating conditions, the Ni catalyst stability is achieved. A Ni/Al<sub>2</sub>O<sub>3</sub> catalyst appears suitable for the steam reforming of biogas including contaminants, under the operative conditions adopted. On the contrary, the effect of a biogas stream with composition CH<sub>4</sub>/CO<sub>2</sub>=50/50 vol. % is much more harmful under steam reforming conditions both in terms of activity and stability. This result was due to CO<sub>2</sub>-promoted Boudouard reaction that leads to extensive carbon formation on the catalyst surface. Under this condition, sulfur and D5 compounds in the biogas have a significant impact on the longevity of the Ni catalyst. Hence, carbon formation rate is affected by the degree of catalyst poisoning due to adsorption and/or deposition of other species on catalytic sites.

## Keywords:

Catalytic stability, biogas, trace compounds, SOFC, Direct internal reforming

## Nomenclature:

ASR, Area Specific Resistance;

CEM, Controlled Evaporator Mixer;

DIR, Direct Internal Reforming;

EIS, Electrochemical Impedance Spectroscopy;

FID, chromatography-Flame Ionization Detector;

FU, Fuel Utilization;

32 GC, Gas Chromatography;  
33 GHSV, Gas Hourly Space Velocity;  
34 LSCF, Lanthanum Strontium Cobalt Ferrite;  
35 OFMSW, Organic Fraction Municipal Solid Waste;  
36 ppb(v), parts per billion by volume;  
37 ppm(v), parts per million by volume;  
38 SEM, Scanning Electron Microscope;  
39 SOFC, Solid Oxide Fuel Cell;  
40 TAR, dark brown or black viscous liquid of hydrocarbons  
41 TCD, gas chromatography-Thermal Conductivity Detector;  
42 TEM, Transmission Electron Microscope;  
43 TPB, Three Phase Boundary;  
44 WWTp, Waste Water Treatment plant;  
45 YSZ, Yttria-Stabilized Zirconia.

## 1. Introduction

Biogas coming from the anaerobic digestion of organic waste covers a crucial role regarding landfilling and pollutant reduction, matter recovery and energy production. Putrescible waste can derive from the domestic urban organic waste, agricultural waste, manure and sludge collected in wastewater treatment plants. Biogas consists of  $\text{CH}_4$  (45-70 vol. %),  $\text{CO}_2$  (30-50 vol. %),  $\text{N}_2$  (<5 vol. %),  $\text{O}_2$  (0-3 vol. %) and a wide variety of trace compounds. The type and quantity of trace compounds depend on waste treated [1–4]. In fact, trace compounds found in landfill biogas and from digestion of organic wastes are completely different [1,5]. Landfill gas quality is widely varying depending on the degradation status of the landfilled material as well as moisture and temperature conditions, all of which may vary considerably in different parts of the landfill body [5]. The higher amount of aromatic compounds found in landfill biogas compared to sewage or farm biogases is often associated with older waste even though elevated levels of aromatic compounds have also been measured in urban waste disposal bins [6–8]. The main trace compound contained in a biogas from the anaerobic digestion of organic wastes – both from WWTPs or municipal organic waste – is hydrogen sulfide ( $\text{H}_2\text{S}$ ) [1,5,9]. The  $\text{H}_2\text{S}$  concentration can range from 10 to thousands of ppm(v), and it is a function of the organic waste, digester temperature and pre-treatments process adopted to improve the methane yield [1,10]. Some pre-treatments can be adopted during the biogas production to reduce the sulfur content in the biogas, such as processes with metal oxides. Other processes are implemented outside the digester, mainly processes that adopt the physical adsorption solution to abate trace concentration [3,8,11–17]. Among energy generators, SOFCs are silent systems, with low emissions and high electrical and thermal efficiency. These systems can produce energy in a distributed way and they can be adopted in the next future to reduce the energy dependency from fossil fuels with high efficiency [8,18,19]. The cleaning process of biogas results to be mandatory in order to reduce the trace contaminants to achieve SOFC requirements [3,12,13,15,19–21]. A SOFC co-generator fed by biogas needs a reforming process to produce a more suitable gas mixture rich in hydrogen and carbon monoxide content, electrochemically suitable for the SOFC [22,23].

Biogas can be converted to synthesis gas either by dry reforming or by a combination of dry and steam reforming using appropriate catalysts [24–27]. Since the  $\text{CH}_4$  to  $\text{CO}_2$  (molar) ratio in biogas is about 1.5, dry reforming alone can lead to significant carbon deposition within the reactor [24,28,29]. Therefore, it is desirable to mix biogas with steam for reforming and generally, the  $\text{H}_2\text{O}$  to  $\text{CH}_4$  ratio (S/C) is maintained at 2 to avoid any coke formation [30,23,22]. Besides carbon deposition issues, the presence of impurities has a tremendous effect on the performance of the catalyst. Among these, the most studied contaminant for catalytic steam reforming is sulfur, in the form of  $\text{H}_2\text{S}$ , which leads to an almost total deactivation of the catalyst [31–33]. Catalyst poisoning occurs due to the strong adsorption of sulfur or other impurities on active sites, promoting by poisoning-metal electron affinity; this consequently, blocks or alters the adsorptivity of the other species [34,35]. Overall, the saturation coverage of sulfur and other species (silicon compounds) depends on the operating temperature, metal loading, and the partial pressure of reacting gasses.

Catalysts with lower metal loading lose activity at a faster rate compared to catalysts with higher metal loading [36,37].

Moreover, the presence of higher molecular weight hydrocarbons ( $C_nH_m$  such as ethane, propane, etc.) and aromatic compounds (benzene, toluene, etc.) can significantly affect the formation of carbon species and thus the effectiveness of the catalyst [38,39]. The formation of carbon on the catalyst under steam reforming conditions may take place mostly through cracking of hydrocarbons and aromatic compounds as well as the Boudouard reaction. In this way, researchers [40,41] determined the coking tendency for steam reforming of methane in the presence of  $C_2$  and  $C_3$  hydrocarbons over a Ni catalyst, and an increasing of coking with carbon number was noted especially in the presence of olefin species. D'Angeli et al. [42] have also shown that coke formation increases with the molecular weight of the feed and that the deactivation rates during steam-reforming of ethane and propane over Ni/MgO were higher compared to methane.

Although poisoning of Ni in the presence of  $H_2S$  or hydrocarbons is well known, combined effects of  $H_2S$  with other contaminants – which are the typical case of biogas – are lacking in the literature. Hence, the main objectives of our research are:

- i) to investigate the catalytic stability of a Ni-catalyst towards biogas reforming in the presence of three types of deactivating compounds ( $H_2S$ , higher hydrocarbons, and siloxane compounds) either alone or combined;
- ii) to analyze the catalytic performances when different biogas compositions are used;
- iii) to evaluate reforming options to increase catalyst lifetime and/or reduce the reformer operating temperature;
- iv) to find the best performance regarding carbon deposition and voltage stability in an SOFC single cell fed with a mixture that simulates the direct internal reforming of biogas;
- v) to investigate the SOFC performance fed by biogas with different trace compounds, starting from sulfur compounds ( $H_2S$ ) to continue with the addition of siloxanes (D4) and aromatic compounds ( $C_7H_8$ ).

The novelty of the paper, from the catalytic point of view, can be identified mainly on two aspects. The first aspect is related to the combined effect of biogas contaminants on Ni catalytic stability; while the second one is the performance evaluation of biogas contaminants depending on biogas stream composition in terms of  $CH_4/CO_2$  inlet ratio.

## 2. Experimental

### 2.1. Catalytic experiments on the reformer Ni catalyst

Catalytic experiments were carried out in a quartz fixed-bed reactor (i.d. = 4 mm;  $h_{\text{bed}} = 2.0\text{--}4.0$  cm) at 1073 K and atmospheric pressure. 0.2 g of commercial Ni/Al<sub>2</sub>O<sub>3</sub> reforming catalyst [28,22,43]. The operative temperature in the reactor was assured by three thermocouples located in different zones of the catalytic bed. Before each test run, catalysts were reduced in-situ at T=1073 K for 1.5 h under hydrogen flow (100 cc/min).


The flow rates of biogas (CH<sub>4</sub>+CO<sub>2</sub>) and poisoning species (H<sub>2</sub>S, hydrocarbons, and siloxane) were controlled by Brooks Instruments mass flow meters. In particular, the following poisoning concentrations ranges were added in the reactant mixture: i) H<sub>2</sub>S=0.4-1 ppm(v), ii) Decamethylcyclopentasiloxane (D5-siloxane, C<sub>10</sub>H<sub>30</sub>O<sub>5</sub>Si<sub>5</sub>=0.5-1 ppm(v) and iii) hydrocarbons mixture=200-800 ppm(v)

Carbon formation during experiments was estimated by using a CHSN-O Carlo Erba elementary analysis instrument, while A PHILIPS CM12 Transmission Electron Microscope (TEM) provided with a high-resolution camera was used to analyze the morphology of both fresh and spent Ni catalysts. A field emission Scanning Electron Microscope (SEM) equipped with EDAX microprobe (Philips XL30 S FEG) was used to carry out qualitative and quantitative analysis of solid compounds (i.e., SiO<sub>2</sub>) on the powders of spent Ni catalysts.

### 2.2. Electrochemical characterization of SOFC single cells

Single SOFC cells were tested with simulated biogas to investigate the effects of direct internal reforming and fuel contamination on the electrochemical performance of the fuel cell.

The laboratory test station is designed to test the planar SOFCs. A schematic diagram of the test rig is provided in Figure 1. The test rig includes an oven, in which ceramic housings holding the planar cell are placed. Moreover includes a gas mixing and distribution system; a humidification system, in which water is added to dry gaseous streams; electric auxiliaries, which supply electricity to the oven and to the cell. Finally, a data acquisition and control system is used to control the system.



150 *Figure 1. Schematic diagram of the test-rig. Solid lines indicate mass and energy streams, while dashed lines*  
 151 *indicate data exchange between the acquisition and control system and the other subsystems.*

152 Two sintered alumina circular housings (diameter 80 mm) are located inside the oven. During  
 153 experiments, the tested cell is placed between the housings which provide gas distribution to both cell  
 154 electrodes and connect the cell to an external electronic load. The SOFC adopted in the tests is a planar  
 155 anode supported fuel cell. The cell is composed by a porous YSZ anode plus a support layer, a dense  
 156 electrolyte and a porous cathode made with LSCF. The cell has a circular section with an active surface of 47  
 157  $\text{cm}^2$  (it means a radius of about 3.86 cm) and the thicknesses of the different layers are reported in Table 1.  
 158 More detail on the experimental set-up can be found elsewhere [20,32,33,44].

159 *Table 1. Geometrical and material characteristics of the SOFC.*

Layer	Material	Thickness
Anode (Support+ Active layers)	Ni/8YSZ	517 $\mu\text{m}$
Electrolyte	YSZ	5 $\mu\text{m}$
Cathode	LSCF	45 $\mu\text{m}$

160 The gas distribution system connects the test-rig to laboratory gas manifolds and ensures that dry gas  
 161 streams with specified flow rates and compositions are sent to the humidification system or directly to the  
 162 cell. This system is composed by pipes, valves (Swagelok), mass flow controllers (Bronkhorst) and a  
 163 Controlled Evaporator Mixer (CEM).

### 164 165 3. Results

#### 166 3.1. Boundary concentration of biogas poisoning on reformer section

##### 167 3.1.1. $\text{H}_2\text{S}$ poisoning


168 Sulfur is known as harmful species for Ni based catalysts and it's hardly to inhibit the catalyst poisoning  
 169 without specific experimental feedings [31,45]. Hence, the effect of  $\text{H}_2\text{S}$  poisoning on the Ni catalyst  
 170 performance has been analyzed with respect to different concentrations (0.4 ppm(v) and 1 ppm(v)) in the  
 171 inlet gas stream. Previously, a catalytic steam reforming test was performed with a "clean" biogas stream in  
 172 order to verify the catalyst behavior in terms of carbon formation rate without poisoning.

173 Results in terms of methane conversion are shown for 0.4 and 1.0 ppm(v) of  $\text{H}_2\text{S}$  concentration in the  
 174 fuel feed, respectively (Figure 2). The catalyst was stable for 150 hours of test with a GHSV of 15,000  $\text{h}^{-1}$   
 175 when  $\text{H}_2\text{S}$  concentration was 0.4 ppm(v). In the experiment with 1 ppm(v) of  $\text{H}_2\text{S}$ , the Ni activity resulted in  
 176 a fast deactivation after about 60 hours of stable operation. The  $\text{CH}_4$  conversion dropped down rapidly from  
 177 about 99% to 20%. This behavior would indicate that the breakthrough time is driven by sulfur concentration  
 178 in the reactant gas mixture. Furthermore, analysis performed on "used" Ni catalysts through a CHNS  
 179 analyzer, highlighted low rates of carbon formation ( $\leq 0.1 \text{ mgC/g}_{\text{cat}}\cdot\text{h}$ ) as well as on Ni catalysts working with  
 180 a clean biogas stream. This means that under the examined experimental conditions and 150 hours of time on



stream, the methane conversion rates are not affected by the poor carbon amounts deposited on catalyst surfaces.

183




184

185 *Figure 2. Methane conversion vs time with H<sub>2</sub>S poisoning: CH<sub>4</sub>/CO<sub>2</sub>=60/40 mol%; H<sub>2</sub>O/CH<sub>4</sub>= 2 mol/mol;*  
 186 *GHSV=15,000 h<sup>-1</sup>; T=1073 K; P=1 bar.*

### 187 3.1.2. Deactivation effects from heavier hydrocarbons

188 Generally, the reasons for deactivation of a Ni-based catalyst for the reforming of hydrocarbons are  
 189 primarily due to carbon deposition promoted by unsaturated compounds (i.e. olefins, aromatics, etc.). Thus,  
 190 effects of C<sub>2</sub> and C<sub>3</sub> species on Ni performances have been investigated through steam reforming  
 191 experiments performed in presence of different hydrocarbons concentrations the biogas stream.

192 Results showed a dramatically reduction of the methane conversion rate from about 99% to about 10%  
 193 after 50 h of time on stream in presence of an hydrocarbons concentration of 800 ppm(v) (calculated on  
 194 biogas stream under dry condition) (see Figure3), while a total concentration of C<sub>2</sub> and C<sub>3</sub> compounds of 200  
 195 ppm(v) would seem to have had no effect on the catalyst stability for 150 hours.






196

197 *Figure 3. Methane conversion vs time with higher hydrocarbons mixture addition: CH<sub>4</sub>/CO<sub>2</sub>=60/40 mol%;*  
 198 *H<sub>2</sub>O/CH<sub>4</sub>= 2 mol/mol; GHSV=15,000 h<sup>-1</sup>; T=1073 K; P=1 bar.*

199 The different Ni catalyst behaviors shown in Figure 3, could be mainly explainable by equilibrium  
200 coking production (Eqs. 3.1,3.2 and 3.3).



201 In fact, the contribution of reaction 3.1, should increase with the increasing of heterogenous compounds  
202 to avoid massive coke deposition promoted by pyrolysis of species with carbon number >1 (Eq. 3.2) [39].  
203 Nevertheless, an excessive presence of harmful species (i.e. alkenes) could exert a substantial effect on coke  
204 formation pathway [46]. In this context, it can be supposed that working with moderate poisoning  
205 concentrations ( $\leq 200$  ppm(v)) and under the conditions considered, an equilibrium among the main reactions  
206 of the process has been achieved (Eqs. 3.4-3.6).



207 Data obtained by elementary analysis seem to confirm the above hypothesis; indeed a marked carbon  
208 formation (about  $0.39 \text{ mgC/g}_{\text{cat}}\cdot\text{h}$  after 70 hours of test) was detected on spent Ni sample working with 800  
209 ppm(v) of hydrocarbons poisoning (Table 2), while a minor carbon deposition ( $0.15 \text{ mgC/g}_{\text{cat}}\cdot\text{h}$ ) was  
210 observed on Ni catalyst exposed to an hydrocarbons concentration of 200 ppm(v), as shown in Table 2.

211 Table 2. Carbon and SiOx formation rates on spent Ni/Al<sub>2</sub>O<sub>3</sub> catalysts: CH<sub>4</sub>/CO<sub>2</sub>=60/40 mol%; H<sub>2</sub>O/CH<sub>4</sub>= 2  
212 mol/mol; GHSV=15,000 h<sup>-1</sup>; T=1073 K; P=1 bar.

	Hydrocarbons mixture*		D5 Siloxane	
<b>Inlet gas concentration [ppm(v)]</b>	800	200	1	0.5
<b>Time on stream [h]</b>	70	150	100	150
<b>CH<sub>4</sub> conversion [mol%]</b>	10	99	70	99
<b>C formation rate [mgC/g<sub>cat</sub>·h]</b>	0.39	0.15	$\leq 0.1$	$\leq 0.1$
<b>SiO<sub>2</sub> [wt%]</b>	-	-	4.8	2.0

213 \* Ethane, Ethylene, Acetylene, Propylene (200 ppm(v) for each)

### 214 3.1.3. Siloxanes poisoning

215 Experiments were performed adding to the inlet gas stream different concentrations of decamethyl-  
216 cyclopenta-siloxane (D5) as the selected siloxane model compound. Results in terms of methane conversion

highlighted a decreasing of the Ni activity (from 99% to 70% after about 100 hours) when a concentration of 1 ppm(v) was added in the inlet gas stream. On the contrary, D5 concentration of 0.5 ppm(v) leaved unchanged the methane conversion rate for 150 hours.

The Ni behavior can be attributed to its physical interaction with siloxanes compounds. In fact, D5 decomposes to  $\text{SiO}_2$ , which deposits on the catalyst surface compromising the catalytic activity (a similar mechanism has been observed for the Ni-anode of the SOFC when exposed to D4 or D5 [47,48]). As previously observed for spent Ni catalysts operated in presence of  $\text{H}_2\text{S}$ , the Ni samples exposed to different D5 concentrations results minimally affected by carbon deposition (Table 2). While depositions of silicon oxide were recorded on used Ni catalysts through SEM-EDAX analysis. As expected, the quantitative analysis showed higher  $\text{SiO}_2(\text{s})$  formation on Ni samples operated with 1 ppm(v) of D5 ( $\text{SiO}_2 = 4.8 \text{ wt. } \%$ ) than samples exposed to 0.5 ppm(v) of D5 ( $\text{SiO}_2 = 2.0 \text{ wt. } \%$ ). These results are in according with recently studies carried out by authors that detected remarkable micro-silica deposits ( $\text{SiO}_2$ ) on Ni spent catalyst exposed to D5 effect under biogas steam reforming reaction [42].

#### 3.1.4. Co-poisoning effect

In order to investigate on possible synergic effects of co-feeding of harmful compounds on the Ni catalyst stability versus time, two kinds of poisoning were added simultaneously in the inlet gas stream (' $\text{H}_2\text{S}$ +Hydrocarbons mix' and 'Hydrocarbons mix+D5', respectively). Hence, maximum boundary concentrations of each contaminant (0.4 ppm(v), 200 ppm(v) and 0.5 ppm(v) for  $\text{H}_2\text{S}$ , hydrocarbons and D5, respectively) were mixed with the biogas stream.

Results given in Figure 4 show that the performances of the Ni catalyst did not suffer deactivation under the simultaneous presence of two different kinds of poisoning species, at the concentrations examined ( $\text{H}_2\text{S}=0.4 \text{ ppm(v)}$ +Hydrocarbons=200 ppm(v) and Hydrocarbons=200 ppm(v)+D5=0.5 ppm(v)), when the molar ratio  $\text{CH}_4/\text{CO}_2=60\%/40\%$  was used. The catalytic stability was recorded for about 150 hours for each test; a methane conversion rate of about 99% was detected both in the presence of ' $\text{H}_2\text{S}$ +Hydrocarbons' and 'Hydrocarbons+D5' mixtures in the inlet gas stream.

Looking at the reformat gas compositions, the outlet molar fractions are very close to what is expected from thermodynamic equilibrium, with an  $\text{H}_2/\text{CO}$  molar ratio about 2.3 mol/mol (see Table 3).




Figure 4. Methane conversion vs time:  $\text{CH}_4/\text{CO}_2=60/40$  mol%;  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol;  $\text{GHSV}=15,000 \text{ h}^{-1}$ ;  $T=1073 \text{ K}$ ;  $P=1 \text{ bar}$ .

Table 3. Outlet stream composition:  $\text{CH}_4/\text{CO}_2=60/40$  mol%;  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol;  $\text{GHSV}=15,000 \text{ h}^{-1}$ ;  $T=1073 \text{ K}$ ;  $P=1 \text{ bar}$ .

Outlet stream	Thermodynamic Equilibrium	Experimental
	[Vol. %]	
$\text{H}_2$	49.8	48.3
$\text{CO}$	20.0	20.7
$\text{CO}_2$	9.1	11.5
$\text{CH}_4$	0.1	0.3
$\text{H}_2\text{O}$	21.0	19.2

### 3.1.5. Impact of the inlet gas stream composition on biogas reforming

#### 3.1.5.1. Effect of carbon dioxide concentration

The influence of the  $\text{CH}_4/\text{CO}_2$  ratio in the inlet gas stream on the Ni catalyst behavior was examined at 1073 K,  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol; 15,000  $\text{h}^{-1}$  of GHSV and atmospheric pressure. Experiments were repeated for 50/50 mol%  $\text{CH}_4/\text{CO}_2$  working both without and with the presence of poisoning in the biogas stream. Stable catalytic performance (about 140 hours) was observed when using clean biogas. In the presence of impurities, deactivation occurred. By adding the hydrocarbons mixture in the feed gas the methane conversion dropped from 98% to 86% after ~80 hours of operation with stable performance; the loss of catalytic activity vs. time was more evident when either  $\text{H}_2\text{S}$  or D5 were inserted in the inlet gas stream ( $\text{CH}_4$  conversion dropped from 98% to about 30% after 70 and 90 hours for  $\text{H}_2\text{S}$  and D5, respectively).

Finally, co-poisoning exposure under this 50/50 mol%  $\text{CH}_4/\text{CO}_2$  mixture resulted in the worst condition in terms of catalyst stability with time. The two investigated combinations ( $\text{H}_2\text{S}$ +hydrocarbons and hydrocarbons+D5) resulted in a loss of Ni catalytic activity after only 20 hours of operation (see Figure 5). From the outlet stream composition, as reported in Table 4, an  $\text{H}_2/\text{CO}$  molar ratio close to 2.1 mol/mol was obtained during the stable operation phase ( $\text{CH}_4$  conversion rate=98%).




Figure 5. Methane conversion over time in the presence of different poisoning exposures:  $CH_4/CO_2=50/50\text{mol}\%$ ;  $H_2O/CH_4=2\text{ mol/mol}$ ;  $GHSV=15,000\text{ h}^{-1}$ ;  $T=1073\text{ K}$ ;  $P=1\text{ bar}$ .

Table 4. Outlet stream composition:  $CH_4/CO_2=50/50\text{mol}\%$ ;  $H_2O/CH_4=2\text{ mol/mol}$ ;  $GHSV=15,000\text{ h}^{-1}$ ;  $T=1073\text{ K}$ ;  $P=1\text{ bar}$ .

Outlet stream	Experimental
	[Vol. %]
$H_2$	45.1
$CO$	21.4
$CO_2$	12.8
$CH_4$	0.4
$H_2O$	20.3

The results from Figure 5, compared with the Ni catalyst performance reported in Figure 4, suggest that a decrease of the  $CH_4/CO_2$  molar ratio in the biogas stream strongly induces negative effects on the Ni catalyst endurance. Moreover, the selectivity to  $H_2$  production was reduced while the CO formation was favored. This behavior is probably due to the reverse WGS reaction ( $CO_2+H_2=CO+H_2O$ ) promoted by carbon dioxide absorption on Ni catalyst active sites [43,44]. However, this means that coke formation by CO dissociation through the Boudouard reaction ( $2CO=C+CO_2$ ) is favored, affecting in this way the catalyst endurance. In addition, the Ni catalyst efficiency in a 50/50 vol%  $CH_4/CO_2$  stream, compared to a 60/40 mixture, was more vulnerable to the presence of contaminants. Especially, the co-feeding cases were now clearly more severe than the cases with only a single poison in the biogas stream.

### 3.1.6. Catalyst post-test characterization

#### 3.1.6.1. Carbon formation rate

Different samples of spent catalysts were analyzed by CHSN elementary analysis to better understand the fundamental degradation mechanisms of catalytic steam reforming in the presence of impurities.

Results in Figure 6 show how the coke formation rate increased by increasing the carbon dioxide concentration in the biogas composition. A deposition rate of about  $0.41\text{ mgC/g}_{\text{cat}}\cdot\text{h}$  was estimated for the mixture  $CH_4/CO_2=50/50\text{ vol}\%$  (under co-poisoning conditions). This observation seems to confirm that the

earlier hypothesis of competitive adsorption of carbon dioxide and H<sub>2</sub>O molecules on Ni active sites that leave to carbon formation probably promoted by CO dissociation through the Boudouard reaction (Eq.3.3). On the contrary, a biogas composition of CH<sub>4</sub>/CO<sub>2</sub>=60/40 vol% ensured stable catalyst performance for about 150 hours at a GHSV of 15,000 h<sup>-1</sup>, also under co-poisoning conditions.

According to literature [45,46], these results allow some considerations on the effect of sulfur and D5 on carbon formation during the biogas steam reforming reaction. Indeed, experimental data indicate that the carbon deposition rate can be accelerated by the presence of contaminants in the biogas stream: the adsorption/precipitation of chemical poisoning species (e.g., sulfur and SiO<sub>2</sub>) on the catalytic surface might inhibit the carbon regasification with steam that protects the metallic phase from coke deposition.





Figure 6. Coke formation rate on spent samples catalyst: GHSV=15,000 h<sup>-1</sup>; 1073K.

### 3.1.6.2. TEM and SEM microscopy evidences

To evaluate carbon deposits, TEM micrographs have been taken on spent catalyst samples. TEM images showed no evidence of large coke deposition when the feed gas was CH<sub>4</sub>/CO<sub>2</sub>=60/40 vol%. This result agrees with the catalytic data previously reported, which showed only modest coke formation rates.






Figure 7. TEM images on fresh and spent catalysts: a) Ni catalyst “fresh”; b) Ni catalyst “used”  $\text{CH}_4/\text{CO}_2=60/40$  mol%+ $\text{H}_2\text{S}$ +HydroC.;  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol;  $\text{GHSV}=15,000$   $\text{h}^{-1}$ ;  $T=1073$  K;  $P=1$  bar; c) Ni catalyst “used”  $\text{CH}_4/\text{CO}_2=60/40$ mol%+HydroC.+D5;  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol;  $\text{GHSV}=15,000$   $\text{h}^{-1}$ ;  $T=1073$  K;  $P=1$  bar.

On the contrary, agglomerates of carbon depositions were observed on spent Ni catalysts working under a biogas flow of  $\text{CH}_4/\text{CO}_2=50/50$  vol%. As highlighted by TEM images (see Figure 8), graphitic carbon deposits are present on the Ni surface. we suspect that the catalytic deactivation trends recorded during tests with poisoning might be due to deactivation/degradation effects other than only carbon deposition (e.g., deposition/adsorption of foreign chemical compounds or atoms). Further evidence of this is presented in section 3.




Figure 8. TEM images on spent Ni catalyst at different magnifications: Ni catalyst “used”  $\text{CH}_4/\text{CO}_2=50/50$ mol%+ $\text{H}_2\text{S}$ +HydroC.;  $\text{H}_2\text{O}/\text{CH}_4=2$  mol/mol;  $\text{GHSV}=15,000$   $\text{h}^{-1}$ ;  $T=1073$  K;  $P=1$  bar.

SEM investigations were carried out in order to determine silicon oxide deposits on spent Ni catalyst samples after exposure to D5 siloxane as a contaminant. As reported in Table 5, comparable concentrations of  $\text{SiO}_2$  were detected on catalyst samples used to reform biogas containing D5 in the inlet stream; however, the durations of the experiments were not identical. The condition with biogas of  $\text{CH}_4/\text{CO}_2=50/50\%$  was more prone to deposit silica when normalized for the experiment duration.

Table 5: SEM-EDAX analysis on spent Ni catalysts:  $T=1073$  K,  $\text{GHSV}=15,000$   $\text{h}^{-1}$ .

SEM-EDAX		Operating Condition		
$\text{SiO}_2$ (wt. %)	$\text{CH}_4/\text{CO}_2$ (vol. %)	Hydrocarbon mix. (ppm(v))	D5 (ppm(v))	Time on stream (h)
2.4	60/40	200	0.5	150
2.5	50/50	200	0.5	50

### 3.2. SOFC single cell testing

#### 3.2.1. Direct internal reforming study

The SOFC was fed by a gas mixture that simulates biogas fuel. The degree of direct internal reforming (DIR) of the biogas was varied from 0% (i.e., biogas is fully reformed externally before feeding the SOFC; in our experiments, we simulated directly the resulting reformat gas mixture) to 100% (in this case, the biogas is fully reformed inside the Ni-anode). Every experiment was carried out fixing the FU at 15% with a current density of 0.25 A/cm<sup>2</sup>. The gas flow mixture of electrochemical fuel comes from the electrochemical hydrogen content, see the following table:

Table 6. Biogas composition for different reforming degree.

DIR (%)	H <sub>2</sub> [mL/min]	CH <sub>4</sub> [mL/min]	CO [mL/min]	CO <sub>2</sub> [mL/min]	H <sub>2</sub> O [mL/min]	$\dot{V}_{\text{tot}}$ [mL/min]	T <sub>bubble</sub> [°C]
0	346.2	6.6	184.8	40.9	58.7	637.1	49.6
25	220.3	54.9	117.6	59.8	88	540.6	64.2
50	127.5	90.5	68.1	73.75	109.6	469.5	75.3
75	56.4	117.8	30.1	84.85	126.2	414.9	87.4
100	0	139.4	0	92.9	139.4	371.7	93.5

In Figure 9, the voltage profile of the cell is given for the gas mixtures reported in Table 6. The cell voltage was quite stable during DIR 0, DIR 25 and DIR 50, while it oscillated at DIR 75. At DIR 100, technical limitations related to the maximum temperature achievable by the bubbler have reduced the voltage stability inducing the carbon deposition phenomena on the cell. At DIR 0%, an average voltage of 840 mV is attained, while at DIR 25 and at DIR 50, 850 mV and 860 mV are reached, respectively. The cell voltage increased up to DIR 50, which can be justified considering the calculated flows and the conditions that ideally should be present at the anode. Low  $H_2O/H_2$  ratio allows to obtain a high-performance operation because reactants do not lower their partial pressure at the anode. At the same time a suitable  $H_2O/CH_4$  ratio should be present because the reforming reactions take place.






Figure 9. Voltage profile at different DIR condition.

The best biogas condition to feed the cell in terms of stable performance is closer to DIR 50 condition with a steam to methane and steam to hydrogen ratio comparable.

The Electrolyte Impedance Spectroscopy analyses are reported below. The cell monitoring has been done at the beginning and at the end of the time intervals every 12 h.

The results of the EIS analysis are shown in Figure 10 providing a comparison of the Nyquist diagrams obtained after 1 and 12 hours of operation in a given condition of DIR. The aim to reach in this phase is the determination of the optimal external reforming able to find a compromise between the cell performance and the economic impact.




Figure 10. EIS results for different DIR.

Taking in consideration the electrochemical impedance spectroscopy analysis, the entity of the different losses can be extrapolated using the model reported elsewhere (see table 7) [20]:

Table 7. Cell losses during operation.

DIR	Time (h)	$R_{ohm}$	$R_{el}$	$R_{transp}$	$R_p$
		$[\Omega \cdot cm]$	$[\Omega \cdot cm]$	$[\Omega \cdot cm]$	$[\Omega \cdot cm]$
<b>DIR0</b>	1 h	0.67	0.07	0.11	0.83
<b>DIR0</b>	12 h	0.59	0.06	0.13	0.78
<b>DIR 25</b>	1 h	0.56	0.07	0.11	0.72
<b>DIR 25</b>	12 h	0.55	0.06	0.13	0.73
<b>DIR 50</b>	1 h	0.53	0.05	0.14	0.72
<b>DIR 50</b>	12 h	0.53	0.07	0.12	0.72

<b>DIR 75</b>	1 h	0.55	0.05	0.1	0.7
<b>DIR 75</b>	12 h	0.55	0.05	0.14	0.72

Observing the results reported above, the ohmic losses are not subjected to drastic variations in the 12 h of observation for almost all the DIR analyzed. The only exception is represented by the DIR 0. However, the main cause for the shift of the intersection with the real axis toward the left direction when the biogas exposure time increases is a temperature variation at which the cell has been undergone when the reformat biogas has been sent and this situation has increased the electrolyte conductivity.

The first arch of Nyquist plot, as previously discussed exemplifies the activation and the electrochemical losses, which are stable in DIR 50 and DIR 75, while in the other two analyzed configurations tend to decrease when the biogas's exposure time increases [15,47]. Finally, the low frequency arch of Nyquist plot has tendency to increase its extension towards higher DIR because, being this arch representative of the concentration losses, it has a higher impact where it is required to diffuse molecules with higher dimensions. This situation happens when the gas mixture is over powered in methane and carbon dioxide.

### 3.2.2. Trace compounds single effect: sulfur compounds

Considering an initial failure of the gas cleaning section ultra-low concentrations of H<sub>2</sub>S can reach the cell during the operation. The possibility to not damage irreversibly the cell was proved from literature results with a concentration of H<sub>2</sub>S below 1 ppm(v) [26,48,49]. The cell was tested at an operating temperature of 750 °C for 50% pre-reformed biogas with a steam-to-carbon ratio equal to 1. An ultra-low concentration of H<sub>2</sub>S (0.46 ppm(v)) was sent to the anode of the cell. The test was carried out over 10 days and the EIS was performed every 24 h. The ASR starts from 0.71 Ωcm<sup>2</sup> after 24 h of test and every 24 h the ASR grew by an average of 2 Ωcm<sup>2</sup>. The final ASR value reached was 0.98 Ωcm<sup>2</sup>.

An initial voltage drop followed by a steady state cell voltage was observed, as reported also in other studies [32]. The degradation came about in the first 80 h of operation. In fact, the voltage assumes values from 0.85 V to 0.74 V in the 240 h of test, but the fastest degradation was recorded in the first 80 h. The long length of time required to achieve a stable condition is attributed to the low hydrogen sulphide concentration that determines a longer interval time to cover the first layer of catalytic sites. Sulfur poisoning of the Ni-anode is a phenomenon that is partially reversible. Once the H<sub>2</sub>S flow is stopped, a voltage increase that suggests S desorption from Ni sites is observed. The desorption trends are quite similar to the corresponding adsorption trends. As reported by Rasmussen and Hagen (2009), once the H<sub>2</sub>S concentration of 2 ppm(v) is removed the cell performance is completely regenerated [48]. However, above 2 ppm(v) of H<sub>2</sub>S, the performance recovery is not complete. It is likely that some sulfur remains trapped in the three-phase

boundary (TPB), thus permanently increasing the anode polarization. This is supported by ASR value and EIS analysis. It can be seen that the  $H_2S$  concentration in time leads to increases in the anode polarization due to concentration polarization, associated with the transport of gaseous fuel through the anode.




Figure 11. Voltage trend at 10A during 10 days of test with  $H_2S$ .

The stable condition is reached when the active surface achieves a high percentage of coverage. This situation determines a lower likelihood for the Sulphur to meet an active site. From this, a slowing in the coverage phenomenon is recorded. The main cause linked to the increase in the losses can be attributed overall to an increase in anodic over-potential respect to a variation of the ohmic effect. The main contribution is related to the low frequency term. This term is mainly affected by the presence of sulfur, this result is consistent with the results of other studies [50,51]. The frequency range of this arc is consistent with the range that can be expected for diffusion-related processes [52].

The presence of sulphur was found to have a greater effect on reforming reactions than electrochemical reactions, especially when compared to tests with hydrogen fuel on similar cells and condition [54]. This last statement allows us to consider the reforming reactions obstructed by the coverage caused by sulphur. Therefore, it is possible to deduce that the lack in reforming reactions leads to a high amount of no reacting methane that can take part in the cracking reaction. Consequence of the cracking is that the pores become blocked. This phenomenon manifests itself through an increase in the second arch of Nyquist plot. In fact,

the deposited carbon obstructs the entering of fresh fuel. However, the above mentioned is not the only reading that can be given at low frequency arch.

Recent studies have shown that at SOFC operating temperature, also very small amounts of Sulphur (<1 ppm(v)) can interact with nickel at microstructural level. Prolonged exposure to fuel containing  $H_2S$  at elevated temperatures can lead to Ni coarsening due to adsorption [53]. The growth in Ni particles, results in loss of percolation and determines the difficulty to spread fresh fuel.

The next figure shows that the voltage recovery is around 94% of the value before  $H_2S$  administration (Figure 12). The total voltage recovery is not fully respected because the degradation due to the previous Sulphur presence was not totally reversible. This occurred both because the adsorbed sulphur is not totally desorbed from the Ni-sites, as well as because the microstructural changings in Ni were not recovered.




Figure 12. Voltage trend after  $H_2S$  removal.

### 3.2.3. Trace compounds effect: multiple species impact

The aim to test the single cell with biogas conditions closer to the reality other pollutants are added to the gas mixture. These trace compounds are detect in biogas and reported in previous studies, such as siloxanes, aromatic compounds and terpenes [1].

### 3.2.3.1. Double trace compounds impact on SOFC performance: sulfur and siloxane

Few studies consider the impact of siloxane on SOFC performance but the combined effect with other pollutants are not reported [20,48]. Octamethylcyclotetrasiloxane (D4) was selected as model compound for siloxanes. Siloxanes were detected not only in biogas coming from WWTP, as reported in literature [54,55], but also in biogas coming from organic waste anaerobic digestion process [56]. D4 was detected in biogas coming from the dry anaerobic digestion of OFMSW with a range from 30 to 300 ppb(v). It is known that the more important siloxanes' effect is the formation of  $\text{SiO}_2$ . The tested siloxane is contained in certified bottles with 20 ppm(v) of D4 in pure  $\text{H}_2$ . The experiments were carried out considering a D4 concentration equal to 0.15 ppm(v) that acts in a period of 72 h. The EIS was carried out with intervals of 12 h and what emerged is shown in the following figure.




Figure 13. EIS Nyquist diagram for  $\text{H}_2\text{S}+\text{D4}$ .

Table 8. Losses recorded in the EIS analysis using the electric circuit model approach.

Test condition	Time (h)	$R_{ohm}$ [ $\Omega \cdot \text{cm}^2$ ]	$R_{el}$ [ $\Omega \cdot \text{cm}^2$ ]	$R_{tranp}$ [ $\Omega \cdot \text{cm}^2$ ]	$R_p$ [ $\Omega \cdot \text{cm}^2$ ]
$\text{H}_2\text{S}$ (last)	240	0.53	0.3	0.15	0.98
$\text{H}_2\text{S}+\text{D4}$	1	0.53	0.3	0.16	0.99

<b>H<sub>2</sub>S+D4</b>	72	0.53	0.36	0.21	1.08
--------------------------	----	------	------	------	------

After 1 h of exposure of the second pollutant, the polarization loss assumed a value similar to that detected in the last test with the H<sub>2</sub>S only. The situation appeared to be slightly different after 72 h, when the increase in the total loss was about  $0.09 \Omega \cdot \text{cm}^2$  compared to the H<sub>2</sub>S case. The losses were due to a 65% to activation and to a 34% to transportation, determining an increase of  $0.06 \Omega \cdot \text{cm}^2$  and  $0.05 \Omega \cdot \text{cm}^2$  in the high and low frequency arches, respectively. The total losses increased to  $0.35 \Omega \cdot \text{cm}^2$  compared to the clean biogas, but  $0.25 \Omega \cdot \text{cm}^2$  were recorded when only H<sub>2</sub>S acts. As other studies confirm [48], Si is able to deposit and condense not only at the TPB, as happens with Sulphur, but deposits everywhere from the distribution channel to the interface anode-electrolyte. However, after 72 h a condition of stability had still not been reached because the D4 acted very slow (the rate is 0.04 V/50 h). Hence, slow but durable in time degradation is attributed to silicon that can deposit it everywhere. This mechanism is deleterious from the SOFC performance point of view; in fact the siloxanes act heavily on the cell decreasing as reported below.




Figure 14. Voltage trend at 10A during 72 h of test with H<sub>2</sub>S+D4.

### 3.2.3.2. Triple trace compounds impact on SOFC performance: sulfur, siloxane and toluene

Another trace compound was added to the gas mixture and cell performance are recorded and reported in terms of EIS analysis and voltage profile along the test. The considered TAR was the toluene (C<sub>7</sub>H<sub>8</sub>). This is

one of the lightest TAR compounds and it can be easily detected in biogas from organic waste [1,5]. Toluene is one of the TAR with the lower molecular weight thus highly reactive, for this reason, it represents the worst condition for the cell operation.

The SOFC was fed with a concentration of toluene equal to 45.7 ppm(v). The tests were carried out over six days, and the EIS was performed at intervals of 24 h each. As for the ohmic contribution, no variations were recorded. However, the overall polarization tended to increase.

Losses increase of  $0.15 \Omega \cdot \text{cm}^2$  and mostly affect the low frequency arch of Nyquist plot. This last aspect is verifiable observing that the high frequencies account only for 20% of the total. Considering all the pollutants introduced, the  $\text{C}_7\text{H}_8$  had the highest consequences on the diffusivity of fresh fuel at the anode.

Being the second arch related to the mass transport mechanisms, carbon deposition could have occurred. This hypothesis is also confirmed by previous studies [20]. The presence of hydrocarbons in the biogas feed could lead to the cracking of molecules. This situation induces a decrease in the active sites that are normally the promoter of reforming or electrochemical reactions. Under these conditions, methane is more prone to take part in the cracking reaction compared to the reforming reactions. The carbon released by cracking is deposited in the anode layer, so obstructing the inlet of fresh fuel.

The low-frequency arch, as already specified, is also affected by the  $\text{H}_2\text{S}$  impact, even if this produces consequences that are not alarming. In fact, the losses related to combined effect accounts for  $0.15 \Omega \cdot \text{cm}^2$  in the most degraded condition, otherwise, the only  $\text{H}_2\text{S}$  effect is of  $0.02 \Omega \cdot \text{cm}^2$ . This means that, the losses related to the  $\text{C}_7\text{H}_8$  assume values around  $0.12 \Omega \cdot \text{cm}^2$ . Considering Figure 15 the voltage profile shows the cell performance decreasing when three different trace compounds are added to the SOFC cell. The performance achieved are quite stable at the end, this demonstrates how the cell is not broken but it is irreversibly affected by the trace compounds considered, when these compounds are removed from the gas mixture, see Figure 16.






Figure 15. Voltage trend at 10A during 6 days of test with  $H_2S+D_4+C_7H_8$ .

Figure 16 shows the iV curve made at the beginning of the test and after the removal of trace compounds, demonstrating that the SOFC performance are irreversibly affected.




Figure 16. *iV* curve in hydrogen made at the beginning and at the end of the test session.

#### 4. Conclusions

A Ni/Al<sub>2</sub>O<sub>3</sub> catalyst appears suitable for the steam reforming of biogas including contaminants, under the operative conditions adopted (CH<sub>4</sub>/CO<sub>2</sub>=60/40 vol.%, T=1073 K, H<sub>2</sub>O/CH<sub>4</sub>=2 mol/mol and GHSV=15,000 h<sup>-1</sup>). Some tolerance towards the presence of one or more poisoning compounds in the inlet gas stream has been shown (among H<sub>2</sub>S≤0.4 ppm(v), C<sub>2</sub>-C<sub>3</sub> hydrocarbons mixture ≤200 ppm(v), and D5≤0.5 ppm(v)). The combined effect of two poisoning compounds in the feed does not seem to affect the Ni catalyst stability (if the concentration of the contaminants are below a threshold limit) when the biogas is composed of a methane to carbon dioxide ratio >1 under the tested operating conditions.

On the contrary, the effect of a biogas stream with composition CH<sub>4</sub>/CO<sub>2</sub>=50/50 vol. % is much more harmful under steam reforming conditions both in terms of activity and stability, probably due mainly to the CO<sub>2</sub>-promoted Boudouard reaction that leads to extensive carbon formation on the catalyst surface. Under this condition, sulfur and D5 compounds in the biogas have a significant impact on the longevity of the Ni catalyst. Hence, the carbon formation rate is affected by the degree of catalyst poisoning due to adsorption and/or deposition of other species (i.e. sulfur and/or silicon oxide) on catalytic sites.

The Ni-anode SOFC performance was investigated varying the DIR condition and testing the impact of trace compounds. DIR investigation proved that the single cell was able to withstand stable up to DIR 50. The best

performance was achieved in this condition given the low  $H_2O/H_2$  ratio that allows to obtain a high-performance operation because reactants do not lower their partial pressure at the anode. At the same time a suitable  $H_2O/CH_4$  ratio should be present because the reforming reactions take place. The combinations from these conditions are well verified in the DIR50 condition.

Considering the trace compounds impact on SOFC performance,  $H_2S$  single compound plus D4 and  $C_7H_8$  as model compounds for sulfurs, siloxanes, and aromatic compounds were investigated. Some conclusions are resumed below, considering the EIS analysis:

- Ohmic losses: the presence of any species of contaminant in the feeding biogas does not damage the electrolytic layer that preserves unchanged its conductive characteristics.
- Activation Losses: the drop in the activation losses is recorded to reach the highest value when the  $H_2S$  is sent to the anode, in fact, the increasing of the activation losses is of  $0.26 \Omega \cdot cm^2$ . Even if  $C_7H_8$  and D4 have an influence on the performance, they produce an increase in losses equal to  $0.03 \Omega \cdot cm^2$  and  $0.04 \Omega \cdot cm^2$ , respectively. The justification linked to these behaviours can be found on the effect that each pollutant produces, i.e. the adsorption/desorption in the catalytic sites and the capability to deposit itself everywhere in the cell structure, respectively.
- Transportation losses: the low frequency arch of the Nyquist plot is mostly affected by the presence of  $C_7H_8$ , while the D4 concentration, below 150 ppb(v) and  $H_2S$  do not influence most this loss. In fact, the aromatic compound leads to an increase in the losses of about  $0.12 \Omega \cdot cm^2$  compared to the case when only D4 and  $H_2S$  act. This is mostly due to the carbon deposition that follows the reduced capacity of Ni sites to promote reforming reactions.

## Acknowledgements

This research is a part of the DEMOSOFC project (European project FCH2 JU – grant number 671470).

## References

- [1] Papurello D, Soukoulis C, Schuhfried E, Cappellin L, Gasperi F, Silvestri S, et al. Monitoring of volatile compound emissions during dry anaerobic digestion of the Organic Fraction of Municipal Solid Waste by Proton Transfer Reaction Time-of-Flight Mass Spectrometry. *Bioresour. Technol.*, vol. 126, 2012, p. 254–65.
- [2] Papurello D, Silvestri S, Tomasi L, Belcari I, Biasioli F. Natural gas trace compounds analysis with innovative systems: PTR-ToF-MS and FASTGC. *Energy Procedia* 2016;101:536–41. doi:10.1016/j.egypro.2016.11.068.

- 535 [3] Papurello D, Schuhfried E, Lanzini A, Romano A, Cappellin L, Märk TD, et al. Proton transfer  
536 reaction-mass spectrometry as a rapid inline tool for filter efficiency of activated charcoal in support  
537 of the development of Solid Oxide Fuel Cells fueled with biogas. *Fuel Process Technol* 2015;130:78–  
538 86. doi:10.1016/j.fuproc.2014.09.042.
- 539 [4] Papurello D, Lanzini A, Leone P, Santarelli M, Silvestri S. Biogas from the organic fraction of  
540 municipal solid waste: Dealing with contaminants for a solid oxide fuel cell energy generator. *Waste*  
541 *Manag* 2014;34:2047–56.
- 542 [5] Rasi S, Veijanen a., Rintala J. Trace compounds of biogas from different biogas production plants.  
543 *Energy* 2007;32:1375–80. doi:10.1016/j.energy.2006.10.018.
- 544 [6] Statheropoulos M, Agapiou A, Pallis G. A study of volatile organic compounds evolved in urban  
545 waste disposal bins. *Atmos Environ* 2005;39:4639–45. doi:10.1016/j.atmosenv.2005.04.013.
- 546 [7] Allen MR, Braithwaite A, Hills CC. Trace Organic Compounds in Landfill Gas at Seven U . K .  
547 Waste Disposal Sites 1997;31:1054–61.
- 548 [8] Papurello D, Silvestri S, Tomasi L, Belcari I, Biasioli F, Santarelli M. Biowaste for SOFCs. *Energy*  
549 *Procedia* 2016;101:424–31. doi:10.1016/j.egypro.2016.11.054.
- 550 [9] Rasi S, Lantela J, Rintala J. Trace compounds affecting biogas energy utilisation - A review. *Energy*  
551 *Convers Manag* 2011;52:3369–75. doi:10.1016/j.enconman.2011.07.005.
- 552 [10] Papurello D, Lanzini A, Schufried E, Santarelli M, Silvestri S. Proton Transfer Reaction-Mass  
553 Spectrometry ( PTR-MS ) as a rapid online tool for biogas VOCs monitoring in support of the  
554 development of Solid Oxide Fuel Cells ( SOFCs ). 6th Int PTR-MS Conf 2013;130:144–50.  
555 doi:10.1016/j.fuproc.2014.09.042.
- 556 [11] Papurello D, Schuhfried E, Lanzini A, Romano A, Cappellin L, Märk TD, et al. Influence of co-  
557 vapors on biogas filtration for fuel cells monitored with PTR-MS (Proton Transfer Reaction-Mass  
558 Spectrometry). *Fuel Process Technol* 2014;118:133–40. doi:10.1016/j.fuproc.2013.08.011.
- 559 [12] Papurello D, Tomasi L, Silvestri S, Santarelli M. Evaluation of the Wheeler-Jonas parameters for  
560 biogas trace compounds removal with activated carbons. *Fuel Process Technol* 2016;152:93–101.  
561 doi:10.1016/j.fuproc.2016.06.006.
- 562 [13] Papurello D, Tognana L, Lanzini A, Smeacetto F, Santarelli M, Belcari I, et al. Proton transfer  
563 reaction mass spectrometry technique for the monitoring of volatile sulfur compounds in a fuel cell  
564 quality clean-up system. *Fuel Process Technol* 2015;130:136–46. doi:10.1016/j.fuproc.2014.09.041.
- 565 [14] Papurello D, Tomasi L, Silvestri S, Belcari I, Santarelli M, Smeacetto F, et al. Biogas trace compound  
566 removal with ashes using proton transfer reaction time-of-flight mass spectrometry as innovative  
567 detection tool. *Fuel Process Technol* 2016;145:62–75. doi:10.1016/j.fuproc.2016.01.028.
- 568 [15] Papurello D, Boschetti A, Silvestri S, Khomenko I. Real-time monitoring of removal of trace  
569 compounds with PTR-MS: Biochar experimental investigation. *Renew Energy* 2018.  
570 doi:10.1016/j.renene.2018.02.122.
- 571 [16] Nam S, Namkoong W, Kang J, Park J, Lee N. Adsorption characteristics of siloxanes in landfill gas  
572 by the adsorption equilibrium test. *Waste Manag* 2013;33:2091–8.  
573 doi:10.1016/j.wasman.2013.03.024.
- 574 [17] Lodewyckx P, Verhoeven L. Using the modified Wheeler-Jonas equation to describe the adsorption  
575 of inorganic molecules: Chlorine. *Carbon N Y* 2003;41:1215–9. doi:10.1016/S0008-6223(03)00052-  
576 6.
- 577 [18] Van Herle J, Membrez Y, Bucheli O. Biogas as a fuel source for SOFC co-generators. *J Power*

- 578 Sources 2004;127:300–12. doi:10.1016/j.jpowsour.2003.09.027.
- 579 [19] Papurello D, Lanzini A, Tognana L, Silvestri S, Santarelli M. Waste to energy: Exploitation of biogas  
580 from organic waste in a 500 W solid oxide fuel cell (SOFC) stack. *Energy* 2015;85:145–58.  
581 doi:10.1016/j.energy.2015.03.093.
- 582 [20] Papurello D, Lanzini A, Drago D, Leone P, Santarelli M. Limiting factors for planar solid oxide fuel  
583 cells under different trace compound concentrations. *Energy* 2016;95:67–78.  
584 doi:10.1016/j.energy.2015.11.070.
- 585 [21] Chavez R-H, Guadarrama JJ, Kastner JR, Das KC, Buquoi Q, Melear ND. Biogas treatment by ashes  
586 from incineration processes. *Clean Technol Environ Policy* 2003;37:2568–74. doi:10.1007/s10098-  
587 015-0980-3.
- 588 [22] Galvagno A, Chiodo V, Urbani F, Freni F. Biogas as hydrogen source for fuel cell applications. *Int J*  
589 *Hydrogen Energy* 2013;38:3913–20. doi:10.1016/j.ijhydene.2013.01.083.
- 590 [23] Chiodo V, Galvagno A, Lanzini A, Papurello D, Urbani F, Santarelli M, et al. Biogas reforming  
591 process investigation for SOFC application. *Energy Convers Manag* 2015;98:252–8.  
592 doi:10.1016/j.enconman.2015.03.113.
- 593 [24] Effendi A, Zhang ZG, Hellgardt K, Honda K, Yoshida T. Steam reforming of a clean model biogas  
594 over Ni/Al<sub>2</sub>O<sub>3</sub> in fluidized- and fixed-bed reactors. *Catal. Today*, vol. 77, 2002, p. 181–9.  
595 doi:10.1016/S0920-5861(02)00244-4.
- 596 [25] Rostrup-Nielsen J, Bak Hansen J-H. CO<sub>2</sub>-Reforming of Methane over Transition Metals. *J Catal*  
597 1993;144:38–49. doi:10.1006/jcat.1993.1312.
- 598 [26] Izquierdo U, Barrio VL, Lago N, Requies J, Cambra JF, Gemez MB, et al. Biogas steam and  
599 oxidative reforming processes for synthesis gas and hydrogen production in conventional and  
600 microreactor reaction systems. *Int. J. Hydrogen Energy*, vol. 37, 2012, p. 13829–42.  
601 doi:10.1016/j.ijhydene.2012.04.077.
- 602 [27] Avraam DG, Halkides TI, Liguras DK, Bereketidou OA, Goula MA. An experimental and theoretical  
603 approach for the biogas steam reforming reaction. *Int. J. Hydrogen Energy*, vol. 35, 2010, p. 9818–27.  
604 doi:10.1016/j.ijhydene.2010.05.106.
- 605 [28] Appari S, Janardhanan VM, Bauri R, Jayanti S. Deactivation and regeneration of Ni catalyst during  
606 steam reforming of model biogas: An experimental investigation. *Int J Hydrogen Energy*  
607 2014;39:297–304. doi:10.1016/j.ijhydene.2013.10.056.
- 608 [29] Galvagno A, Chiodo V, Urbani F, Freni F. Biogas as hydrogen source for fuel cell applications. *Int J*  
609 *Hydrogen Energy* 2013;38:3913–20. doi:10.1016/j.ijhydene.2013.01.083.
- 610 [30] Chiodo V, Urbani F, Galvagno A, Mondello N, Freni S. Analysis of biogas reforming process for  
611 molten carbonate fuel cells. *J Power Sources* 2012;206:215–21. doi:10.1016/j.jpowsour.2012.01.114.
- 612 [31] Ashrafi M, Pfeifer C, Pröll T, Hofbauer H. Experimental study of model biogas catalytic steam  
613 reforming: 2. Impact of sulfur on the deactivation and regeneration of Ni-based catalysts. *Energy and*  
614 *Fuels* 2008;22:4190–5. doi:10.1021/ef8000828.
- 615 [32] Papurello D, Lanzini A, Fiorilli S, Smeacetto F, Singh R, Santarelli M. Sulfur poisoning in Ni-anode  
616 solid oxide fuel cells (SOFCs): Deactivation in single cells and a stack. *Chem Eng J* 2016;283:1224–  
617 33. doi:10.1016/j.cej.2015.08.091.
- 618 [33] Papurello D, Borchellini R, Bareschino P, Chiodo V, Freni S, Lanzini A, et al. Performance of a  
619 Solid Oxide Fuel Cell short-stack with biogas feeding. *Appl Energy* 2014;125:254–63.

- [34] Ereksen EJ, Bartholomew CH. Sulfur poisoning of nickel methanation catalysts. II. Effects of H<sub>2</sub>S concentration, CO and H<sub>2</sub>O partial pressures and temperature on reactivation rates. *Appl Catal* 1983;5:323–36. doi:10.1016/0166-9834(83)80160-2.
- [35] Papurello D, Lanzini A, Drago D, Leone P, Santarelli M. Limiting factors for planar solid oxide fuel cells under different trace compound concentrations. *Energy* 2016;95:67–78. doi:10.1016/j.energy.2015.11.070.
- [36] Abild-Pedersen F, Lytken O, Engbæk J, Nielsen G, Chorkendorff I, Nørskov JK. Methane activation on Ni(1 1 1): Effects of poisons and step defects. *Surf Sci* 2005;590:127–37. doi:10.1016/j.susc.2005.05.057.
- [37] Sidjabat O, Trimm DL. Nickel-magnesia catalysts for the steam reforming of light hydrocarbons. *Top Catal* 2000;11–12:279–82. doi:10.1023/A:1027212301077.
- [38] Hofmann P, Panopoulos KD, Fryda LE, Schweiger A, Ouweltjes JP, Karl J. Integrating biomass gasification with solid oxide fuel cells: Effect of real product gas tars, fluctuations and particulates on Ni-GDC anode. *Int J Hydrogen Energy* 2008;33:2834–44. doi:10.1016/j.ijhydene.2008.03.020.
- [39] Hofmann P, Panopoulos KD, Aravind P V., Siedlecki M, Schweiger A, Karl J, et al. Operation of solid oxide fuel cell on biomass product gas with tar levels. *Int J Hydrogen Energy* 2009;34:9203–12. doi:10.1016/j.ijhydene.2009.07.040.
- [40] Trimm DL. Catalyst design for reduced coking (review). *Appl Catal* 1983;5:263–90. doi:10.1016/0166-9834(83)80156-0.
- [41] Sidjabat O, Trimm DL. Nickel-magnesia catalysts for the steam reforming of light hydrocarbons. *Top Catal* 2000;11–12:279–82. doi:10.1023/A:1027212301077.
- [42] Angeli SD, Pilitsis FG, Lemonidou AA. Methane steam reforming at low temperature: Effect of light alkanes' presence on coke formation. *Catal Today* 2015;119–28. doi:10.1016/j.cattod.2014.05.043.
- [43] Chiodo V, Urbani F, Galvagno A, Mondello N, Freni S. Analysis of biogas reforming process for molten carbonate fuel cells. *J Power Sources* 2012;206:215–21. doi:10.1016/j.jpowsour.2012.01.114.
- [44] Papurello D, Lanzini A, Leone P, Santarelli M. The effect of heavy tars (toluene and naphthalene) on the electrochemical performance of an anode-supported SOFC running on bio-syngas. *Renew Energy* 2016;99:747–53. doi:10.1016/j.renene.2016.07.029.
- [45] Abild-Pedersen F, Lytken O, Engbæk J, Nielsen G, Chorkendorff I, Nørskov JK. Methane activation on Ni(1 1 1): Effects of poisons and step defects. *Surf Sci* 2005;590:127–37. doi:10.1016/j.susc.2005.05.057.
- [46] Didenko LP, Savchenko VI, Arutyunov VS, Sementsova LA. Steam reforming of methane mixtures with ethylene over an industrial nickel catalyst. *Pet Chem* 2008;48:22–7. doi:10.1007/s11494-008-1004-x.
- [47] Haga K, Adachi S, Shiratori Y, Itoh K, Sasaki K. Poisoning of SOFC anodes by various fuel impurities. *Solid State Ionics* 2008;179:1427–31. doi:10.1016/j.ssi.2008.02.062.
- [48] Madi H, Lanzini A, Diethelm S, Papurello D, Van herle J, Lualdi M, et al. Solid oxide fuel cell anode degradation by the effect of siloxanes. *J Power Sources* 2015;279:460–71. doi:10.1016/j.jpowsour.2015.01.053.
- [49] Choudhary V., Uphade B., Mamman A. Simultaneous steam and CO<sub>2</sub> reforming of methane to syngas over NiO/MgO/SA-5205 in presence and absence of oxygen. *Appl Catal A Gen* 1998;168:33–46. doi:10.1016/S0926-860X(97)00331-1.

- 662 [50] Avraam DG, Halkides TI, Liguras DK, Bereketidou OA, Goula MA. An experimental and theoretical  
663 approach for the biogas steam reforming reaction. *Int. J. Hydrogen Energy*, vol. 35, 2010, p. 9818–27.  
664 doi:10.1016/j.ijhydene.2010.05.106.
- 665 [51] Delahay G, Duprez D. Effect of sulphur on the coking of rhodium in the steam reforming of 1-  
666 methyl-naphthalene. *Appl Catal* 1989;53:95–105. doi:10.1016/S0166-9834(00)80014-7.
- 667 [52] Strohm JJ, Zheng J, Song C. Low-temperature steam reforming of jet fuel in the absence and  
668 presence of sulfur over Rh and Rh-Ni catalysts for fuel cells. *J Catal* 2006;238:309–20.  
669 doi:10.1016/j.jcat.2005.12.010.
- 670 [53] Leone P, Matencio T, Garcia ME, Domigues ZR, Lanzini A, Santarelli M. Limiting Factors for a  
671 Planar Solid Oxide Fuel Cell Under Different Flow and Temperature Conditions. *Fuel Cells* 2013;n/a-  
672 n/a. doi:10.1002/fuce.201200154.
- 673 [54] Rasmussen JFB, Hagen A. The effect of H<sub>2</sub>S on the performance of Ni-YSZ anodes in solid oxide  
674 fuel cells. *J Power Sources* 2009;191:534–41. doi:10.1016/j.jpowsour.2009.02.001.
- 675 [55] Rasmussen JFB, Hagen A. The Effect of H<sub>2</sub>S on the Performance of SOFCs using Methane  
676 Containing Fuel 2010;1135–42. doi:10.1002/fuce.201000012.
- 677 [56] Zha S, Cheng Z, Liu M. Sulfur Poisoning and Regeneration of Ni-Based Anodes in Solid Oxide Fuel  
678 Cells. *J Electrochem Soc* 2007;154:B201–6. doi:10.1149/1.2404779.
- 679 [57] Cheng Z, Zha S, Liu M. Influence of cell voltage and current on sulfur poisoning behavior of solid  
680 oxide fuel cells. *J Power Sources* 2007;172:688–93. doi:10.1016/j.jpowsour.2007.07.052.
- 681 [58] Aravind PV, Ouweltjes JP, Schoonman J. Diffusion Impedance on Nickel/Gadolinia-Doped Ceria  
682 Anodes for Solid Oxide Fuel Cells. *J Electrochem Soc* 2009;156:B1417–22. doi:10.1149/1.3231490.
- 683 [59] Ivey DG, Brightman E, Brandon N. Structural modifications to nickel cermet anodes in fuel cell  
684 environments. *J Power Sources* 2010;195:6301–11. doi:10.1016/j.jpowsour.2010.04.059.
- 685 [60] Arnold M, Kajolinnä T. Development of on-line measurement techniques for siloxanes and other  
686 trace compounds in biogas. *Waste Manag* 2010;30:1011–7. doi:10.1016/j.wasman.2009.11.030.
- 687 [61] Arnold M. Reduction and monitoring of biogas trace compounds. 2009.
- 688

**Highlights**

- Ni catalyst stability is achieved with biogas mixture with  $\text{CH}_4/\text{CO}_2 > 1$
- $\text{CH}_4/\text{CO}_2 = 50/50$  vol. % is much more harmful under steam reforming conditions both in terms of activity and stability
- The impact of trace contaminants not removed from the cleaning section from biogas are investigated on SOFCs