

CO2 valorisation towards alcohols by Cu-based electrocatalysts: challenges and perspectives

*Original*

CO2 valorisation towards alcohols by Cu-based electrocatalysts: challenges and perspectives / Hilmar, Guzman; Russo, Nunzio; Simelys, Hernandez. - In: GREEN CHEMISTRY. - ISSN 1463-9262. - ELETTRONICO. - 23:5(2021), pp. 1896-1920. [10.1039/d0gc03334k]

*Availability:*

This version is available at: 11583/2875982 since: 2021-03-23T16:43:06Z

*Publisher:*

RSC

*Published*

DOI:10.1039/d0gc03334k

*Terms of use:*

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

*Publisher copyright*

(Article begins on next page)

# CO<sub>2</sub> valorisation towards alcohols by Cu-based electrocatalysts: Challenges and perspectives

Hilmar Guzmán,<sup>a,b</sup> Nunzio Russo <sup>a</sup> and Simelys Hernández <sup>a,b,\*</sup>

<sup>a</sup> *CREST group, Department of Applied Science and Technology (DISAT), Politecnico di Torino, C.so Duca degli Abruzzi, 24, 10129, Turin, Italy.*

<sup>b</sup> *IIT – Istituto Italiano di Tecnologia, Via Livorno, 60, 10144, Turin, Italy.*

\* *Corresponding author. E-mail address: [simelys.hernandez@polito.it](mailto:simelys.hernandez@polito.it)*

## Supporting Information

### Summary

|   |    |
|---|----|
| <b>S1. CO<sub>2</sub>-to-methanol via thermochemical route</b> .....  | 2  |
| <b>S2. CO<sub>2</sub>-to-methanol via liquid phase electrochemical route</b> .....                            | 3  |
| <b>S3. Total Faradaic efficiencies of the best liquid-phase EC CO<sub>2</sub>R electrocatalysts</b>           | 4  |
| <b>S4. Ethanol and n-propanol production from CO<sub>2</sub> via liquid-phase electrochemical route</b> ..... | 5  |
| <b>S5. CO<sub>2</sub>-to-alcohols via catholyte-free electrochemical route.</b> ....                          | 7  |
| <b>S6. Total Faradaic efficiencies of the best catholyte-free EC CO<sub>2</sub>R electrocatalysts</b> .....   | 9  |
| <b>S7. References</b> .....   | 10 |

### ***S1. CO<sub>2</sub>-to-methanol via thermochemical route***

Outstanding results following TC reactions for methanol production from our work<sup>1</sup> with data taken from references<sup>2–6</sup>. Table S1 shows the best results following thermochemical reactions for methanol production.

Table S1. Outstanding results following TC reactions for methanol production from our work<sup>1</sup> with data taken from references<sup>2–6</sup>.

| Catalysts   | CO <sub>2</sub> conversion, % | Selectivity Methanol, % | Temperature, °C | Pressure, MPa | Ref. |
|---|-------------------------------|-------------------------|-----------------|---------------|------|
| Cu/ZnO  | 5.5                           | 50                      | 240             | 2             | 3    |
| Cu/ZrO <sub>2</sub>   | 2.5                           | 78                      | 240             | 2             | 3    |
| Cu/ZnO/Ga   | 6                             | 88                      | 270             | 2             | 5    |
| Cu/ZrO <sub>2</sub> /Ga   | 13.7                          | 75.5                    | 250             | 2             | 5    |
| Cu/ZnO/ZrO <sub>2</sub>   | 13                            | 32                      | 240             | 2             | 3    |
| Cu/ZnO/ZrO <sub>2</sub> /SiO <sub>2</sub>                                 | 13.9                          | 36                      | 240             | 2             | 4    |
| Cu/ZnO/ZrO <sub>2</sub> /TiO <sub>2</sub>                                 | 17.4                          | 43.8                    | 240             | 3             | 2    |
| Cu/ZnO/ZrO <sub>2</sub> /Al <sub>2</sub> O <sub>3</sub> /SiO <sub>2</sub> | 11.7                          | 99.7                    | 250             | 5             | 6    |

## S2. CO<sub>2</sub>-to-methanol via liquid phase electrochemical route

Table S2. State-of-the-art performance of the best catalysts to produce methanol from liquid-phase electrochemical CO<sub>2</sub> conversion.

| Electrocatalysts  | Faradaic efficiency to Methanol, % | Total current density, mA cm <sup>-2</sup> | Cell configuration                     | Ref. |
|---|------------------------------------|--|--|------|
| Cu <sub>63.9</sub> Au <sub>36.1</sub> /NCF                  | 15.9                               | -  | H-type cell (Nafion 117)               | 7    |
| Anodiz. Cu foils  | 100.0                              | 1.4  | Traditional undivided 3 electrode cell | 8    |
| Electroch. Anodiz. Cu foils                                 | 20.0                               | 5.0  | Traditional undivided 3 electrode cell |      |
| Cu <sub>2</sub> O/stainless steel                           | 38.0                               | 5.0  | Traditional undivided 3 electrode cell |      |
| Cu <sub>88</sub> Sn <sub>6</sub> Pb <sub>6</sub> alloy foil | 34.0                               | 0.6  | Two compartmentss (Nafion 117)         |      |
| Cu/Carbon paper   | 0.4                                | 8.9  | Two compartmentss (SPEEK)              |      |
| Electropolished Cu  | 0.1                                | 10.0                                       | Two compartmentss (AMV Selemion)       |      |
| Cu/ZnO  | 2.8                                | 12.0                                       | Two compartmentss (Nafion 117)         |      |
| Cu <sub>2</sub> O /Carbon paper                             | 20.0                               | 2.4  | Two compartmentss SPE (AMI-7001/ MEA)  |      |
| Cu/CuO  | 2.5                                | 17.3                                       | Two compartmentss (Nafion 117)         |      |
| Ru/Cu   | 42.0                               | 0.1  | Two compartmentss (agar bridge)        |      |
| Mo/Cu   | 84.0                               | 0.8  | Traditional undivided 3 electrode cell |      |
| Cu <sub>2</sub> O/ZnO                                       | 17.7                               | 10.6                                       | Two compartmentss (Nafion 117)         |      |
| Cu-10-CNT/C   | 8.3                                | 16.7                                       | Two compartmentss (Nafion 117)         | 10   |
| Cu <sub>2</sub> O-MWCNTs                                    | 38.0                               | 7.5  | Two compartmentss (Nafion 117)         | 11   |
| Oxide-der, Cu/ C (MOF)                                      | 18.0                               | 1.0  | Two compartmentss (Nafion 117)         | 12   |
| CuO <sub>x</sub> /ZnO                                       | 34.0                               | 2.7  | Traditional undivided 3 electrode cell | 13   |
| CuCNT-nanowires   | 47.4                               | 0.9  | Traditional undivided 3 electrode cell | 14   |
| CuCNT-Impregnation  | 23.3                               | 0.9  | Two compartmentss (Nafion 117)         | 14   |
| Cu/Graphene   | 12.7                               | 0.3  | Two compartmentss (Nafion 117)         | 15   |
| Cu/TiO <sub>2</sub> /Graphene                               | 19.5                               | 0.3  | Two compartmentss (Nafion 117)         | 15   |
| Cu/Cu <sub>2</sub> O  | 47.5                               | 7.8  | Two compartmentss (Nafion 117)         | 16   |
| Cu-Y/CS:PVA MCE   | 68.0                               | 0.3  | Membrane coated electrode (MCE)        | 17   |
| Pd <sub>83</sub> Cu <sub>17</sub> Aerogels                  | 80.0                               | 31.8                                       | H-type cell (Nafion 117)               | 18   |
| Cu <sub>1.63</sub> Se <sub>1/3</sub>                        | 77.6                               | 41.5                                       | H-type cell (Nafion 117)               | 19   |
| CuSAs/TCNFs   | 44.0                               | 93.0                                       | H-type cell (Nafion 117)               | 20   |

**S3. Faradaic efficiencies for different CO<sub>2</sub>R products of the best liquid-phase electrocatalysts.**

| Electrocatalysts                                      | Faradaic efficiency, % * |      |                               |                              |                    |                                  |                                 |                               |                                  |                 | J <sub>total</sub> ,<br>mA cm <sup>-2</sup> | Ref. |
|---|--------------------------|------|-------------------------------|------------------------------|--------------------|----------------------------------|---------------------------------|-------------------------------|----------------------------------|-----------------|---|------|
|   | H <sub>2</sub>           | CO   | C <sub>2</sub> H <sub>4</sub> | HCOO <sup>-</sup> /<br>HCOOH | CH <sub>3</sub> OH | C <sub>2</sub> H <sub>5</sub> OH | C <sub>3</sub> H <sub>8</sub> O | C <sub>2</sub> H <sub>6</sub> | CH <sub>3</sub> COO <sup>-</sup> | CH <sub>4</sub> |   |      |
| Pd <sub>83</sub> Cu <sub>17</sub> Aerogels            |                          | <1.0 |                               |                              | 80.0               |                                  |                                 |                               |                                  |                 | 31.8  | 18   |
| Cu <sub>1.63</sub> Se1/3                              | <1.0                     | 2.0  | -                             | 22.0                         | 77.6               | -                                | -                               | -                             | -                                | -               | 41.5  | 19   |
| CuSAs/TCNFs   | <1.0                     | 54.0 | -                             | -                            | 44.0               | -                                | -                               | -                             | -                                | -               | 93.0  | 20   |
| Cu <sub>2</sub> O                                     |                          |      |                               |                              | 42.3               | 10.1                             | 2.4                             |                               |                                  |                 | 10.0  | 43   |
| Cu <sub>2</sub> O/ZnO                                 |                          |      |                               |                              | 27.5               | 3.9                              | -                               |                               |                                  |                 | 10.0  | 43   |
| CuB <sub>9</sub> MOF                                  | 34.0                     | 11.0 | 6.0                           | 13.0                         | 10.0               | 17.0                             | -                               | -                             | -                                | -               | 20.0  | 33   |
| CuBi <sub>12</sub> MOF                                | 30.0                     | 9.0  | 7.0                           | 16.0                         | 9.0                | 28.0                             | -                               | -                             | -                                | -               | 20.0  | 33   |
| B-OD-Cu   | 45.0                     | <1.0 | 20.0                          | 5.0                          | -                  | 20.0                             | -                               | 8.0                           | -                                | -               | 33.4  | 44   |
| Cu 25nm thickness                                     | 5.0                      | 5.0  | 70.0                          | 1.0                          | -                  | 11.0                             | -                               | -                             | 5.0                              | -               | 275.0                                       | 35   |
| Ag <sub>0.14</sub> /Cu <sub>0.86</sub> /PTFE          | 10.0                     | 3.0  | 31.0                          | -                            | -                  | 41.0                             | -                               | -                             | 10.0                             | 5.0             | 250.0                                       | 36   |
| Electrodeposited<br>CuAg alloy                        | 9.8                      | 6.5  | 55.2                          | 3.0                          | -                  | 25.9                             | 2.4                             | -                             | 1.6                              | 1.6             | 300.0                                       | 37   |
| Nanoporous Cu   | 7.6                      | 14.7 | 38.6                          | 1.9                          | -                  | 16.6                             | 4.5                             | -                             | 2.2                              | -               | 653.0                                       | 34   |
| Cu Nps/Carbon<br>paper                                | 10.6                     | 38.9 | 35.0                          | 7.6                          | -                  | 11.2                             | 2.1                             | -                             | 0.4                              | -               | 430.0                                       | 38   |
| Cu <sub>2</sub> S–Cu–V                                | 12.6                     | 5.5  | 21.2                          | 15.4                         | -                  | 25.0                             | 7.0                             | -                             | 3.0                              | 1.1             | 400.0                                       | 39   |
| Ce(OH) <sub>x</sub> /Cu/PTFE                          | 14.2                     | 0.5  | 33.8                          | 1.1                          | -                  | 42.6                             | 0.6                             | -                             | 3.3                              | 2.9             | 300.0                                       | 45   |
| NGQ/Cu-nr   | 10.0                     | 5.0  | 23.0                          | 5.0                          | -                  | 45.0                             | 7.0                             | -                             | 4.0                              | -               | 282.0                                       | 46   |
| 34% N-C/Cu/PTFE                                       | 7.4                      | 0.3  | 37.5                          | 1.7                          | -                  | 52.3                             | 1.4                             | -                             | 2.3                              | 1.2             | 300.0                                       | 40   |
| La <sub>1.8</sub> SrO <sub>0.2</sub> CuO <sub>4</sub> |                          |      |                               |                              | 2.0                | 30.5                             | 10.0                            |                               |                                  |                 | 180.0                                       | 41   |
| Porous copper foam                                    | 69.2                     | 4.6  | 4.0                           | 5.9                          | -                  | 3.2                              | 4.9                             | 2.8                           | 0.7                              | -               | 37.5  | 42   |

Empty cells: no information available. (-) These products were not detected. \* All values were approximated from the reported literature data.

#### S4. Ethanol and n-propanol production from CO<sub>2</sub> via liquid-phase electrochemical route

Table S3. State-of-the-art performance of the production of ethanol and n-propanol from liquid-phase electrochemical CO<sub>2</sub> conversion.

| Electrocatalysts                           | Faradaic efficiency to Ethanol, % | Faradaic efficiency to n-Propanol, % | Total current density, mA cm <sup>-2</sup> | Cell configuration   | Ref. |
|--|-----------------------------------|--------------------------------------|--|--|------|
| Graphene/Cu <sub>2</sub> O/Cufoil          | 9.9                               | -                                    | 5.3  | Two compartments 3-electrodes cell separated by a glass frit | 21   |
| Cu(100)                                    | 9.7                               | 1.5                                  | 5.0  | Traditional undivided 3 electrode cell                       | 22   |
| Polycrystalline Cu                         | 21.9                              | -                                    | 5.0  | Two compartments separated by Selemion                       | 23   |
| 3,6 μm film of Cu <sub>2</sub> O           | 16.4                              | -                                    | 35.0                                       | Two compartments separated by Selemion                       | 24   |
| CuO/TiO <sub>2</sub>                       | 37.5                              | 5.6                                  | 8.3  | H-type cell (Nafion 117)                                     | 25   |
| Cu <sub>63,9</sub> Au <sub>36,1</sub> /NCF | 12.0                              | -                                    | -  | H-type cell (Nafion 117)                                     | 7    |
| Cu/N-Graphene                              | 63.0                              | -                                    | 2.8  | Two compartments separated by Selemion                       | 26   |
| Graphene/ZnO/Cu <sub>2</sub> O/Cufoil      | -                                 | 30.0                                 | 8.0  | Two compartments cell separated by a glass frit              | 27   |
| Cu nanocrystals                            | -                                 | 10.6                                 | 16.4                                       | Two compartments separated by Selemion                       | 28   |
| Cu Nps/ Carbon paper x22.5 loading         | 13.3                              | 5.9                                  | 12.7                                       | Two compartments separated by Selemion                       | 29   |
| Cu/Graphene                                | 24.1                              | 3.1                                  | 1.3  | Gas Diffusion electrode (Nafion 117)                         | 30   |
| CuO/TiO <sub>2</sub> /Graphene             | 43.6                              | 3.3                                  | 1.4  | Gas Diffusion electrode (Nafion 117)                         | 30   |
| Cu <sub>1ML</sub> /THH Pd NCs              | 20.4                              | -                                    | 0.6  | H-type cell (Nafion 115)                                     | 31   |
| Electrodeposited Cu onto Cu mesh           | 10.0                              | 13.0                                 | 10.0 (normalized to the ECSA)              | H-type cell (Nafion 117)                                     | 32   |
| CuBi <sub>9</sub> MOF                      | 17.0                              | -                                    | 20.0                                       | Two compartments (Nafion 117)                                | 33   |

|  |      |      |       |                               |    |
|--|------|------|-------|-------------------------------|----|
| CuBi <sub>12</sub> MOF                               | 28.0 | -    | 20.0  | Two compartments (Nafion 117) | 33 |
| Nanoporous Cu  | 16.6 | 4.5  | 653.0 | Gas Diffusion electrode       | 34 |
| Cu 25nm thickness                                    | 11.0 | -    | 275.0 | Flow cell reactor             | 35 |
| Ag <sub>0.14</sub> /Cu <sub>0.86</sub> /PTFE         | 41.0 | -    | 250.0 | Gas Diffusion electrode       | 36 |
| Electrodeposited CuAg alloy                          | 25.0 | -    | 300.0 | Flow cell reactor             | 37 |
| Cu Nps/Carbon paper                                  | 11.0 | 2.1  | 430.0 | Flow cell reactor             | 38 |
| Cu <sub>2</sub> S–Cu–V                               | 25.0 | 7.0  | 400.0 | Gas Diffusion electrode       | 39 |
| 34% N-C/Cu/PTFE                                      | 52.0 | 1.0  | 300.0 | Gas Diffusion electrode       | 40 |
| La <sub>1.8</sub> Sr <sub>0.2</sub> CuO <sub>4</sub> | 30.5 | 10.0 | 180.0 | H-cell                        | 41 |
| Porous copper foam                                   | -    | 4.93 | 37.5  | H-cell                        | 42 |

**S5. CO<sub>2</sub>-to-alcohols via catholyte-free electrochemical route.**

Table S4. State-of-the-art performance of the production of alcohols from solvent-less electrochemical CO<sub>2</sub> conversion .

| Electrocatalysts            | Relative FE to methanol, % | Relative FE to ethanol, % | Relative FE to n-Propanol, % | Total current density, mA cm <sup>-2</sup> | Cell configuration  | Ref. |
|-----------------------------|----------------------------|---------------------------|------------------------------|--|---|------|
| Fe <sub>10</sub> -CNTox/GDL | 21.7                       | 70.5                      | 3.3                          | 1.4  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 47   |
| Pt <sub>10</sub> -CNTox/GDL | 16.1                       | 25.1                      | 34.8                         | 1.4  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 47   |
| Cu-Graphite/C               | 75.0                       | -                         | -                            | 2.4  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 48   |
| Cu-AC/C                     | 45.0                       | -                         | -                            | 2.4  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 48   |
| Cu-CNF/C                    | 2.5                        | 2.0                       | 2.5                          | 2.4  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 48   |
| Cu-CNF/C (PBI)              | 5.0                        | 2.0                       | 0.2                          | 1.6  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 49   |
| Cu powder                   | 92.8                       | -                         | -                            | 1.6  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 50   |
| Cu_C powder                 | 14.1                       | -                         | -                            | 1.6  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 50   |
| Cu Oxide/ZnO                | 0.2                        | 0.2                       |                              | 7.5  | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 51   |
| Pb/CNT                      | 6.3                        | -                         | -                            | 16.0                                       | Continuous gas-phase  | 52   |



|  |      |      |     |       |   |    |
|--|------|------|-----|-------|---|----|
|  |      |      |     |       | CO <sub>2</sub> electroreduction. MEA Configuration.                      |    |
| Cu(250nm)-C-G/PTFE                                     | -    | 20.3 | 5.4 | 150.0 | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 53 |
| Cu/TiO <sub>2</sub> NTs                                | 23.5 | -    | -   | 120.0 | Continuous Solid Polymer Electrolyte Membrane (SPE) Reactor               | 54 |
| 34% N-C/Cu/PTFE  | -    | 56.5 | 2.7 | 160.0 | Continuous gas-phase CO <sub>2</sub> electroreduction. MEA Configuration. | 40 |
| Commercial Cu <sub>2</sub> O (solid-state electrolyte) | -    | 7.0  | 7.0 | 90.0  | CO <sub>2</sub> electroreduction. MEA Configuration.                      | 55 |

**S6. Total Faradaic efficiencies of the best catholyte-free EC CO<sub>2</sub>R electrocatalysts**

| Electrocatalysts  | Relative Faradaic efficiency, % |                                 |                                  |                                 |                                 |                      |                 |  |      |                               |                              | J <sub>total</sub> ,<br>mA cm <sup>-2</sup> | Ref. |
|---|---------------------------------|---------------------------------|----------------------------------|---------------------------------|---------------------------------|----------------------|-----------------|--|------|-------------------------------|------------------------------|---|------|
|   | CH <sub>3</sub> OH              | C <sub>2</sub> H <sub>4</sub> O | C <sub>2</sub> H <sub>5</sub> OH | C <sub>3</sub> H <sub>6</sub> O | C <sub>3</sub> H <sub>8</sub> O | CH <sub>3</sub> COOH | CH <sub>4</sub> | C <sub>2</sub> H <sub>4</sub> O <sub>2</sub> | CO   | C <sub>2</sub> H <sub>4</sub> | HCOO <sup>-</sup> /<br>HCOOH |   |      |
| Fe <sub>10</sub> -<br>CNTox/GDL                               | 21.7                            | 2.0                             | 70.5                             | 0.1                             | 3.3                             | 2.53                 | -               | -  | -    | -                             | -                            | 1.4   | 47   |
| Pt <sub>10</sub> -<br>CNTox/GDL                               | 16.1                            | 19.8                            | 25.1                             | 0.2                             | 34.8                            | 4.1                  | -               | -  | -    | -                             | -                            | 1.4   | 47   |
| Cu-Graphite/C   | 75.0                            | 8.0                             | -                                | 12.0                            | -                               | -                    | 2.5             | 2.5  | -    | -                             | -                            | 2.4   | 48   |
| Cu-AC/C   | 45.0                            | 48.0                            | -                                | 5.0                             | -                               | -                    | 1.0             | 1.0  | -    | -                             | -                            | 2.4   | 48   |
| Cu-CNF/C  | 2.5                             | 70.0                            | 2.0                              | -                               | 2.5                             | -                    | 5.0             | 12.0   | 10.0 | -                             | -                            | 2.4   | 48   |
| Cu-CNF/C<br>(PBI)   | 5.0                             | 68.0                            | 2.0                              | -                               | 0.2                             | -                    | 0.6             | 19.0   | 5.0  | -                             | -                            | 1.6   | 49   |
| Cu_25nm<br>powder   | -                               | -                               | -                                | -                               | -                               | -                    | 2.1             | -  | 0.1  | 97.8                          | -                            | 7.5   | 56   |
| Cu powder   | 92.7                            | 1.9                             | -                                | -                               | -                               | -                    | 5.3             | -  | -    | -                             | -                            | 1.6   | 50   |
| Cu_C powder   | 14.1                            | 60.7                            | -                                | -                               | -                               | -                    | 25.8            | -  | -    | -                             | -                            | 1.6   | 50   |
| Cu Oxide/ZnO  | 0.2                             | -                               | 0.2                              | 0.2                             | -                               | -                    | 0.5             | -  | 0.3  | 98.5                          | -                            | 7.5   | 51   |
| Pb/CNT  | 6.3                             | -                               | -                                | -                               | -                               | -                    | 34.4            | -  | 9.4  | -                             | 50.0                         | 16.0  | 52   |
| Cu(250nm)-C-<br>G/PTFE  | -                               | -                               | 20.3                             | -                               | 5.4                             | 6.7                  | -               | -  | 13.5 | 54.1                          | -                            | 150.0                                       | 53   |
| Cu/TiO <sub>2</sub> NTs                                       | 23.5                            | -                               | -                                | -                               | -                               | -                    | 17.6            | -  | 58.8 | -                             | -                            | 120.0                                       | 54   |
| 34% N-<br>C/Cu/PTFE   | -                               | -                               | 56.5                             | -                               | 2.7                             | 2.7                  | -               | -  | -    | 38.0                          | -                            | 160.0                                       | 40   |
| Commercial<br>Cu <sub>2</sub> O (solid-<br>state electrolyte) | -                               | -                               | 7.0                              | -                               | 7.0                             | 1.4                  | -               | -  | 35.2 | 28.2                          | 21.1                         | 90.0  | 55   |

(-) These products were not detected.

## S7. References

- 1 H. Guzmán, M. A. Farkhondehfal, K. Rodulfo Tolod, N. Russo and S. Hernández, in *Solar Hydrogen Production Processes, Systems and Technologies*, Elsevier Inc., 2019, p. 560.
- 2 J. Xiao, D. Mao, X. Guo and J. Yu, *Appl. Surf. Sci.*, 2015, **338**, 146–153.
- 3 T. Witoon, N. Kachaban, W. Donphai, P. Kidkhunthod, K. Faungnawakij, M. Chareonpanich and J. Limtrakul, *Energy Convers. Manag.*, 2016, **118**, 21–31.
- 4 T. Phongamwong, U. Chantaprasertporn, T. Witoon, T. Numpilai, Y. Poo-arporn, W. Limphirat, W. Donphai, P. Dittanet, M. Chareonpanich and J. Limtrakul, *Chem. Eng. J.*, 2017, **316**, 692–703.
- 5 S. Saeidi, N. A. S. Amin and M. R. Rahimpour, *J. CO<sub>2</sub> Util.*, 2014, **5**, 66–81.
- 6 J. Toyir, R. Miloua, N. E. Elkadri, M. Nawdali, H. Toufik, F. Miloua and M. Saito, *Phys. Procedia*, 2009, **2**, 1075–1079.
- 7 F. Jia, X. Yu and L. Zhang, *J. Power Sources*, 2014, **252**, 85–89.
- 8 J. Albo, M. Alvarez-Guerra, P. Castaño and A. Irabien, *Green Chem.*, 2015, **17**, 2304–2324.
- 9 J. Albo, A. Sáez, J. Solla-Gullón, V. Montiel and A. Irabien, *Appl. Catal. B Environ.*, 2015, **176–177**, 709–717.
- 10 C. Genovese, C. Ampelli, S. Perathoner and G. Centi, *Green Chem.*, 2017, **19**, 2406–2415.
- 11 M. Irfan Malik, Z. O. Malaibari, M. Atieh and B. Abussaud, *Chem. Eng. Sci.*, 2016, **152**, 468–477.
- 12 K. Zhao, Y. Liu, X. Quan, S. Chen and H. Yu, *ACS Appl. Mater. Interfaces*, 2017, **9**, 5302–5311.
- 13 M. T. H. Le, Louisiana State University and Agricultural and Mechanical College, 2011.
- 14 B. C. Marepally, C. Ampelli, C. Genovese, F. Tavella, L. Veyre, E. A. Quadrelli, S. Perathoner and G. Centi, *J. CO<sub>2</sub> Util.*, 2017, **21**, 534–542.
- 15 J. Yuan, M. P. Yang, Q. L. Hu, S. M. Li, H. Wang and J. X. Lu, *J. CO<sub>2</sub> Util.*, 2018, **24**, 334–340.
- 16 J. Hazarika and M. S. Manna, *Electrochim. Acta*, 2019, **328**, 135053.
- 17 A. Marcos-Madrado, C. Casado-Coterillo and Á. Irabien, *ChemElectroChem*, 2019, **6**, 5273–5282.

- 18 L. Lu, X. Sun, J. Ma, D. Yang, H. Wu, B. Zhang, J. Zhang and B. Han, *Angew. Chemie - Int. Ed.*, 2018, **57**, 14149–14153.
- 19 D. Yang, Q. Zhu, C. Chen, H. Liu, Z. Liu, Z. Zhao, X. Zhang, S. Liu and B. Han, *Nat. Commun.*, 2019, **10**, 1–9.
- 20 H. Yang, Y. Wu, G. Li, Q. Lin, Q. Hu, Q. Zhang, J. Liu and C. He, *J. Am. Chem. Soc.*, 2019, **141**, 12717–12723.
- 21 R. A. Geioushy, M. M. Khaled, A. S. Hakeem, K. Alhooshani and C. Basheer, 2017, **785**, 138–143.
- 22 Y. Hori, I. Takahashi, O. Koga and N. Hoshi, *J. Mol. Catal. A Chem.*, 2003, **199**, 39–47.
- 23 Y. Hori and R. Takahashi, 1989, **85**, 2309–2326.
- 24 D. Ren, Y. Deng, A. D. Handoko, C. S. Chen, S. Malkhandi and B. S. Yeo, *ACS Catal.*, 2015, **5**, 2814–2821.
- 25 J. Yuan, J. J. Zhang, M. P. Yang, W. J. Meng, H. Wang and J. X. Lu, *Catalysts*, 2018, **8**, 171.
- 26 Y. Song, R. Peng, D. K. Hensley, P. V. Bonnesen, L. Liang, Z. Wu, H. M. Meyer, M. Chi, C. Ma, B. G. Sumpter and A. J. Rondinone, *ChemistrySelect*, 2016, **1**, 6055–6061.
- 27 R. A. Geioushy, M. M. Khaled, K. Alhooshani, A. S. Hakeem and A. Rinaldi, *Electrochim. Acta*, 2017, **245**, 456–462.
- 28 D. Ren, N. T. Wong, A. D. Handoko, Y. Huang and B. S. Yeo, *J. Phys. Chem. Lett.*, 2016, **7**, 20–24.
- 29 D. Kim, C. S. Kley, Y. Li and P. Yang, *Proc. Natl. Acad. Sci. U. S. A.*, 2017, **114**, 10560–10565.
- 30 J. Yuan, M. P. Yang, Q. L. Hu, S. M. Li, H. Wang and J. X. Lu, *J. CO2 Util.*, 2018, **24**, 334–340.
- 31 F. Y. Zhang, T. Sheng, N. Tian, L. Liu, C. Xiao, B. A. Lu, B. Bin Xu, Z. Y. Zhou and S. G. Sun, *Chem. Commun.*, 2017, **53**, 8085–8088.
- 32 M. Rahaman, A. Dutta, A. Zanetti and P. Broekmann, *ACS Catal.*, 2017, **7**, 7946–7956.
- 33 J. Albo, M. Perfecto-Irigaray, G. Beobide and A. Irabien, *J. CO2 Util.*, 2019, **33**, 157–165.
- 34 J. J. Lv, M. Jouny, W. Luc, W. Zhu, J. J. Zhu and F. Jiao, *Adv. Mater.*, 2018, **30**, 1–8.
- 35 C. T. Dinh, T. Burdyny, G. Kibria, A. Seifitokaldani, C. M. Gabardo, F. Pelayo García De Arquer, A. Kiani, J. P. Edwards, P. De Luna, O. S. Bushuyev, C. Zou, R. Quintero-Bermudez, Y. Pang, D. Sinton and E. H. Sargent, *Science (80-. )*, 2018, **360**, 783–787.
- 36 Y. C. Li, Z. Wang, T. Yuan, D. H. Nam, M. Luo, J. Wicks, B. Chen, J. Li, F. Li, F. P. G.

- De Arquer, Y. Wang, C. T. Dinh, O. Voznyy, D. Sinton and E. H. Sargent, *J. Am. Chem. Soc.*, 2019, **141**, 8584–8591.
- 37 T. T. H. Hoang, S. Verma, S. Ma, T. T. Fister, J. Timoshenko, A. I. Frenkel, P. J. A. Kenis and A. A. Gewirth, *J. Am. Chem. Soc.*, 2018, **140**, 5791–5797.
- 38 S. Ma, M. Sadakiyo, R. Luo, M. Heima, M. Yamauchi and P. J. A. Kenis, *J. Power Sources*, 2016, **301**, 219–228.
- 39 T. Zhuang, Z. Liang, A. Seifitokaldani, Y. Li, P. De Luna, T. Burdyny, F. Che, F. Meng, Y. Min, R. Quintero-bermudez, C. T. Dinh, Y. Pang, M. Zhong, B. Zhang, J. Li, P. Chen, X. Zheng, H. Liang, W. Ge, B. Ye, D. Sinton, S. Yu and E. H. Sargent, *Nat. Catal.*, 2018, **1**, 421–428.
- 40 X. Wang, Z. Wang, F. P. G. De Arquer, C. Dinh, A. Ozden, Y. C. Li, D. Nam, J. Li, Y. Liu, J. Wicks, Z. Chen, M. Chi, B. Chen, Y. Wang, J. Tam, J. Y. Howe, A. Proppe, P. Todorović, F. Li, T. Zhuang, C. M. Gabardo, A. R. Kirmani, C. Mccallum, S. Hung, Y. Lum, M. Luo, Y. Min, A. Xu, C. P. O. Brien, B. Stephen, B. Sun, A. H. Ip, L. J. Richter, S. O. Kelley, D. Sinton and E. H. Sargent, *Nat. Energy*, 2020, **5**, 478–486.
- 41 M. Schwartz, R. L. Cook, K. Victoria M., R. C. MacDuff, J. Patel and A. F. Sammells, *J. Electrochem. Soc.*, 1993, **140**, 614.
- 42 J. A. Rudd, E. Kazimierska, L. B. Hamdy, O. J. E. Bain, S. Ahn, A. R. Barron and E. Andreoli, *ChemRxiv*, , DOI:10.26434/chemrxiv.12022623.v1.
- 43 J. Albo and A. Irabien, *J. Catal.*, 2016, **343**, 232–239.
- 44 C. Chen, X. Sun, L. Lu, D. Yang, J. Ma, Q. Zhu, Q. Qian and B. Han, *Green Chem.*, 2018, **20**, 4579–4583.
- 45 M. Luo, Z. Wang, Y. C. Li, J. Li, F. Li, Y. Lum, D. H. Nam, B. Chen, J. Wicks, A. Xu, T. Zhuang, W. R. Leow, X. Wang, C. T. Dinh, Y. Wang, Y. Wang, D. Sinton and E. H. Sargent, *Nat. Commun.*, 2019, **10**, 1–7.
- 46 C. Chen, X. Yan, S. Liu, Y. Wu, Q. Wan, X. Sun, Q. Zhu, H. Liu, J. Ma, L. Zheng, H. Wu and B. Han, *Angew. Chemie*, 2020, **100049**, 16601–16606.
- 47 C. Genovese, C. Ampelli, S. Perathoner and G. Centi, *J. Catal.*, 2013, **308**, 237–249.
- 48 N. Gutiérrez-Guerra, L. Moreno-López, J. C. Serrano-Ruiz, J. L. Valverde and A. de Lucas-Consuegra, *Appl. Catal. B Environ.*, 2016, **188**, 272–282.
- 49 N. Gutiérrez-Guerra, J. L. Valverde, A. Romero, J. C. Serrano-Ruiz and A. de Lucas-Consuegra, *Electrochem. commun.*, 2017, **81**, 128–131.
- 50 N. Gutiérrez-Guerra, J. A. González, J. C. Serrano-Ruiz, E. López-Fernández, J. L. Valverde and A. de Lucas-Consuegra, *J. Energy Chem.*, 2019, 46–53.

- 51 I. Merino-Garcia, J. Albo, J. Solla-Gullón, V. Montiel and A. Irabien, *J. CO2 Util.*, 2019, **31**, 135–142.
- 52 J. García, C. Jiménez, F. Martínez, R. Camarillo and J. Rincón, *J. Catal.*, 2018, **367**, 72–80.
- 53 C. M. Gabardo, P. Colin, O. Brien, P. Jonathan, J. Li, H. Edward, D. Sinton, C. P. O. Brien, J. P. Edwards, C. McCallum, Y. Xu, C. Dinh, J. Li, E. H. Sargent and D. Sinton, *Joule*, 2019, **3**, 2777–2791.
- 54 S. K. S. Hossain, J. Saleem, S. U. Rahman, S. M. J. Zaidi, G. McKay and C. K. Cheng, *Catalysts*, 2019, **9**, 1–19.
- 55 C. Xia, P. Zhu, Q. Jiang, Y. Pan, W. Liang, E. Stavitsk, H. N. Alshareef and H. Wang, *Nat. Energy*, 2019, **4**, 776–785.
- 56 I. Merino-Garcia, J. Albo and A. Irabien, *Nanotechnology*, 2018, **29**, 14001.