

INSIGHTS INTO THE CO₂ ADSORPTION PROPERTIES OF NITROGEN-CONTAINING ORDERED
MESOPOROUS CARBONS

Original

INSIGHTS INTO THE CO₂ ADSORPTION PROPERTIES OF NITROGEN-CONTAINING ORDERED MESOPOROUS CARBONS / Maruccia, E.; Lourenço, M.; Priamushko, T; Bartoli, M.; Bocchini, S.; Kleitz, F.; Gerbaldi, C.. - ELETTRONICO. - (2022). (Intervento presentato al convegno XIII Congresso Nazionale INSTM tenutosi a Sestriere (TO), Italia nel 23-26 gennaio 2022).

Availability:

This version is available at: 11583/2953738 since: 2022-01-27T12:30:57Z

Publisher:

Consorzio Interuniversitario Nazionale per la Scienza e Tecnologia dei Materiali (INSTM)

Published

DOI:

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

INSIGHTS INTO THE CO₂ ADSORPTION PROPERTIES OF NITROGEN-CONTAINING ORDERED MESOPOROUS CARBONS

Maruccia E^{1,2,3}, Lourenço M¹, Priamushko T⁴, Bartoli M¹, Bocchini S¹, Kleitz F⁴, Gerbaldi C^{2,3}

¹*Istituto Italiano di Tecnologia - IIT, Centre for Sustainable Future Technologies (CSFT), Torino, Italy*

²*Group for Applied Materials and Electrochemistry (GAME Lab), Department of Applied Science and Technology (DISAT), Politecnico di Torino, Torino, Italy*

³*National Interuniversity Consortium of Materials Science and Technology (INSTM), Florence, Italy*

⁴*Department of Inorganic Chemistry – Functional Materials, University of Vienna, Vienna, Austria*

Introduction

The increase of global CO₂ concentration is the main responsible for global warming. Nitrogen containing ordered mesoporous carbons (NOMCs) are here proposed as CO₂ adsorbents, thanks to their adsorption ability and selectivity in simulated flue gases mixtures. In this work, NOMCs are synthesized as replications of an ordered mesoporous silica hard template, using the well-known nanocasting route. This method is convenient for achieving a pore architecture composed of both micro- and mesopores able to promote at the same time improved capture performances and fast kinetics of gas diffusion, respectively. One of the drawbacks of the synthesis of NOMCs is the use of toxic carbon/nitrogen sources or the addition of post-synthesis treatments for the nitrogen doping process.

Material and methods

A more sustainable approach is proposed in this work, using eco-friendly sources as nitrogen-rich carbon precursors. The effect of the pyrolysis temperature (varied from 600 to 900°C) on the development of microporosity and N incorporation was related to pure CO₂ adsorption and selectivity in CO₂/N₂ mixtures (20/80 v/v).

Results and discussion

A maximum CO₂ adsorption capacity of 1.47 mmol g⁻¹ was achieved by the sample pyrolyzed at the highest temperature (i.e., 900°C) at 30°C / 0.9 bar / pure CO₂, while a CO₂ uptake of 0.82 mmol g⁻¹ was obtained by the sample pyrolyzed at the lowest temperature (i.e., 600°C) at 35°C / 1 bar / 20% CO₂. The enhancement in pure CO₂ adsorption is due to the increase of the micropore content. On the contrary, a lower pyrolysis temperature (600°C) allowed for the retention of a higher amount of N, beneficial for the selective adsorption of CO₂ in presence of N₂.