POLITECNICO DI TORINO Repository ISTITUZIONALE

Evaluation of target non-uniformity and dispersion effects on energy measurement resolution in NUMEN experiment

Original

Evaluation of target non-uniformity and dispersion effects on energy measurement resolution in NUMEN experiment / Pinna, F.; Calvo, D.; Campostrini, M.; Capirossi, V.; Delaunay, F.; Fisichella, M.; Iazzi, F.; Rigato, V.. - In: PHYSICA SCRIPTA. - ISSN 0031-8949. - 95:9(2020), p. 094002. [10.1088/1402-4896/aba779]

Availability: This version is available at: 11583/2894112 since: 2021-04-16T17:45:05Z

Publisher: Institute of Physics Publishing

Published DOI:10.1088/1402-4896/aba779

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright IOP postprint/Author's Accepted Manuscript

"This is the accepted manuscript version of an article accepted for publication in PHYSICA SCRIPTA. IOP Publishing Ltd is not responsible for any errors or omissions in this version of the manuscript or any version derived from it. The Version of Record is available online at http://dx.doi.org/10.1088/1402-4896/aba779

(Article begins on next page)

Article

Evaluation of target non-uniformity and dispersion effects on energy measurement resolution in NUMEN experiment

Federico Pinna^{1,2*}, Daniela Calvo², Matteo Campostrini³, Vittoria Capirossi^{1,2}, Franck Delaunay⁴, Maria Fisichella², Felice Iazzi^{1,2}, Valentino Rigato³

- ¹ Politecnico di Torino, Torino, Italy
- ² INFN Sezione di Torino, Torino, Italy
- ³ INFN LNL, Legnaro, Padova, Italy
- ⁴ LPC Caen, Normandie Université, ENSICAEN, UNICAEN, CNRS/IN2P3, Caen, France
- * Correspondence: federico.pinna@polito.it; federico.pinna@to.infn.it

Abstract: In the NUMEN Experiment, Double Charge Exchange (DCE) reactions will be studied to 1 get very precise measurements of their cross sections and final state levels. The interest for these 2 reactions lies in the possibility for some nuclides to have DCE with initial and final states identical to з those of the Neutrinoless Double β -Decay. To reach a good precision in the energy measurements, high statistics is needed and severe constraints about the target thickness must be satisfied. A 50 5 μ A intense ion beam will provide the desired statistics, while posing the problem of dissipating the 6 massive heat generated in the target. It is therefore necessary to design a suitable cooling system, 7 which must affect the particles' energy as little as possible. Said energy is already influenced by the 8 current setup. The Superconducting Cyclotron (SC) and the MAGNEX Spectrometer introduce an q error on the particles' energy by $1/1000^{th}$ (FWHM value) of its average energy. In the target, the 10 main sources of error are straggling of projectiles and reaction products, and the dispersion effect. 11 Both closely depend on the target thickness, which must be of the order of few hundred nanometres. 12 In addition, the two effects are worsened if the target thickness is not uniform. The solution to 13 these problems has been found by backing the target isotope with relatively thin substrate of Highly 14 Oriented Pyrolytic Graphite (HOPG). Its thermodynamic properties fit the cooling requirements and 15 can be as thin as 450 μ g/cm². The further straggling suffered by the ejectiles is tolerable, falling 16 within the resolution requirements. Samples are deposited by using Electron Beam Evaporation: 17 results obtained for Sn and Te are checked by Scanning Electron Microscopy (SEM). A quantitative 18 evaluation of the samples' thickness has been performed by Alpha-Particle Transmission (APT) 19 and Rutherford Backscattering Spectrometry (RBS) measurements. A Monte Carlo code has been 20 implemented to estimate the ejectiles energy distribution using the experimental measurements as 21 input. Results from characterization and simulations help in optimizing the target thickness and the 22 energy resolution of reaction products. 23

Keywords: Double Charge Exchange; Neutrino-less Double β Decay; Target thickness uniformity; isotope deposition; FESEM; Rutherford Backscattering Spectrometry; Alpha-transmission measurements

27 1. Introduction

²⁸ The study of rare nuclear reactions requires a sufficiently good precision in the measurement of

²⁹ the physical quantity of interest, e.g. energy of particles. This is the case of the NUMEN experiment,

in which the energy of the reaction products, together with other quantities, must be measured with
 high precision [1]. The main goal of NUMEN is to obtain experimental information about the Nuclear

³³ and final states are the same of the corresponding Neutrino-less Double Beta decays $(0\nu\beta\beta)$, i.e.:

$$\begin{array}{lll} DCE \ reaction & (A_1, Z_1) + (A_2, Z_2) \to (A_1, Z_1 + 2) + (A_2, Z_2 - 2) & (1) \\ 0\nu\beta\beta \ (\beta^+ decay) & (A_2, Z_2) \to (A_2, Z_2 - 2) + 2\beta^+ & (2) \\ DCE \ reaction & (A_1, Z_1) + (A_2, Z_2) \to (A_1, Z_1 - 2) + (A_2, Z_2 + 2) & (3) \\ 0\nu\beta\beta \ (\beta^- decay) & (A_2, Z_2) \to (A_2, Z_2 + 2) + 2\beta^- & (4) \end{array}$$

In reactions (1) and (3) the target nucleus, labelled by index 2, transforms, by DCE with projectile, into the same final nucleus of the Double β -Decay without any accompanying neutrino shown in formulas (2) and (4). Projectiles used in NUMEN are ¹⁸O and ²⁰Ne ion beams, whose energy ranges from 15 to 60 MeV/A. Two preliminary sets of targets, ¹¹⁶Sn, ⁷⁶Se isotopes for ¹⁸O beam and ¹¹⁶Cd, ⁷⁶Ge, ¹³⁰Te isotopes for ²⁰Ne, are foreseen in the first phases of the experiment. The full list of the

⁴⁰ foreseen targets is reported in [2].

34

⁴¹ The required resolution in the energy measurement of the ejectiles depends on the target isotope,

⁴² but in most cases it is close to 0.5 MeV. Considering the error introduced by the experimental setup
⁴³ (Superconducting Cyclotron and track reconstruction in MAGNEX spectrometer, each one introducing

an error equal to 1/1000 of the beam energy in FWHM), not much room is left for the error due to the

target. Such an error depends on the target material, of course, but also on the thickness: the thicker

the target, the worse is the energy resolution, as will be described in more detail in the following

sections. Therefore, it is mandatory to produce thin targets. On the other hand, the searched DCE cross sections are about only few nb/sr up to few μ b/sr, and a large number of reactions are needed to get

statistically significant data. Given the very small target thickness, the only viable way is to use very

intense ion beams. The first downside of this approach is the massive generation of heat in the target,

⁵¹ which by no means can endure such a thermal stress [3].

⁵² The issue has been solved by using a special graphite backing, made of Highly Oriented Pyrolytic

⁵³ Graphite (HOPG), which has a very high in-plane thermal conductivity (1900±100 W/m⋅K at room

temperature). Aside from thermal management purposes, the graphite backing will also work as

mechanical support for the target and as post-stripper for the reaction products. This kind of graphite

can be as thin as 450 μ g/cm². Unfortunately, adding a further layer after the target affects the ejectile

energy and consequently the energy resolution, mainly for the straggling inside the graphite.

⁵⁸ In the following sections, the techniques used to characterize the targets will be described. The effects

influencing the energy resolution due to the target and HOPG thickness will be discussed in section 4,

⁶⁰ together with the effects coming from other sources.

Results from characterization of target prototypes will be shown. These results are used in a Monte

⁶² Carlo code to estimate the energy distribution of reaction products. Simulations outcome for Sn and Te

⁶³ prototypes will be reported.

⁶⁴ 2. Target and Substrate influence on energy resolution

As mentioned above, the final energy of each ion is affected by statistical effects due to the 65 experimental setup and to the target system (target and HOPG substrate). In the facility upgrade, 66 a great effort is being dedicated in keeping the effects of the equipment close to the current value 67 (1/1000 of the beam energy in FWHM). However, the loss of resolution due to the equipment cannot 68 be mitigated past a certain point. Among all, the target assembly (target and HOPG substrate) is the 69 source of uncertainty that can be reduced at most. Here, straggling and dispersion are the two main 70 factors affecting the projectile energy. Dispersion is due to the impossibility of knowing where the 71 reaction happens inside the target, while straggling is due to the statistical fluctuation around the 72 average energy loss. Both effects become more relevant with increasing the thickness of the crossed 73 mediums; also, they are worsened if the target and HOPG thickness is not uniform. Given these 74

⁷⁵ premises, the optimization of the target system physical characteristics is of paramount importance to

- ⁷⁶ have the best trade off among cooling, target thickness and energy resolution.
- ⁷⁷ Therefore, a thorough characterization procedure is mandatory to correlate deposition parameters
- ⁷⁸ and samples characteristics. The techniques used are FESEM, Alpha-Particle Transmission (APT) and
- 79 Rutherford Backscattering Spectrometry (RBS). Atomic Force Microscopy (AFM) was also considered
- to further investigate the samples' surface, but it proved to be unsuited for the research purposes and
- was soon abandoned.

82 3. Target Characterization

- Samples showed in this work are elemental Te and Sn film deposited by electron beam evaporation
- on HOPG substrates. The thicker graphite (nominal thickness 2200 μ g/cm²) was used at the beginning
- of the work to test the HOPG as a substrate; meanwhile, a thinner HOPG type, 1100 μ g/cm² thick, was
- ⁸⁶ found to be commercially available, so the initial results were then transferred on the thinner HOPG.
- ⁸⁷ Tellurium samples presented here are called A14 (on 2200 μ g/cm² HOPG) and B10 (on 1100 μ g/cm² HOPC) tip complex are parend A20 (on 2200 μ g/cm² HOPC) and B12 (on 1100 μ g/cm² HOPC). The
- ⁸⁸ HOPG); tin samples are named A20 (on 2200 μ g/cm² HOPG) and B13 (on 1100 μ g/cm² HOPG). The
- target morphology is influenced by several factors, such as the deposition parameters and conditions,
 the material properties, the substrate surface's properties. All of them must be considered or tuned to
- obtain a sufficiently uniform deposition and reduce the target contribution to the energy resolution.
- ⁹² As first step, the HOPG foil is characterized by APT technique measurements. Alpha-Particle
- ⁹³ Transmission is a non-destructive characterization technique that allows to get precise quantitative
- ⁹⁴ information on the sample thickness and its thickness uniformity. In this characterization procedure, a
- ⁹⁵ collimated ion beam of known energy crosses the sample, losing energy in the process. A Si detector,
- ⁹⁶ placed downstream the sample, is used to measure the residual energy of the ions, thanks to which
- ⁹⁷ the thickness distribution of the sample can be evaluated. The ion beam, made of alpha particles,
- ⁹⁸ is provided by a radioactive ²⁴¹Am source. The detailed characterization procedure is described in
- ⁹⁹ [4]. From such measurements, the HOPG's average thickness and disuniformity are evaluated. In
- ¹⁰⁰ particular, the average thickness is taken as the most probable value in the data distribution, while
- the disuniformity is evaluated through the distribution's standard deviation. A typical APT plot of a
- 102 HOPG substrate is shown in figure 1.



Figure 1. A standard APT data set of a 1100 μ g/cm² (nominal thickness) thick HOPG sample. The collected data are shown in black dots, while the red solid line is a Crystal-Ball fit [5].

The analysis of several HOPG samples, with nominal thickness of 1100 μ g/cm², suggests that a certain degree of roughness is intrinsic in the graphite substrates. The measured average thickness is

 $1208 \ \mu g/cm^2$, with an average disuniformity of 2% of the total thickness. The low-energy tail is more

 r_{10} represent the high energy one this can be due to the combined effect of large humps on the

- ¹⁰⁶ pronounced than the high-energy one; this can be due to the combined effect of large bumps on the ¹⁰⁷ HOPG surface and the higher energy loss of the α particle at lower energy. Details on the roughness
- estimation are reported in [4].
- ¹⁰⁹ After the backing has been characterized, the thin film target is deposited and qualitatively

characterized by Electron Microscopy, to quickly check the complete substrate coverage and have afirst insight on the film structure.



(a) SEM image of Te sample A14. Structure some hundred of nm top a uniform and compact background.



(b) SEM image of Te sample B10. The film appears to have a compact background, on which relatively small structures can be observed.

Figure 2. SEM images of Te samples A14 and B10. No relevant differences can be noticed.



(a) SEM image of Sn sample A20. Large structures cover a compact background.



(b) SEM image of Sn sample B13. The overall flat film is run by deep trenches

Figure 3. SEM images of Sn samples A20 and B13. The two samples does not belong to the same production batch.



(a) SEM image of a HOPG sheet, 30Kx magnification.



(b) Close up SEM image of a HOPG sheet, 150Kx magnification.

Figure 4. SEM image of a HOPG backing 1100 μ g/cm² thick. The sheet looks extremely flat, thanks to its crystalline structure (fig. a). Difference in thickness may be due to oddly stacked graphite layers (fig. b).

SEM images of the Te samples, reported in fig. 2, show that small structures some tens of nm in size cover an overall flat and compact background. Sample B10 (figure 2a) shows no particular

5 of 14

differences from sample A14 (figure 2b). On the contrary, the Sn films appear more uneven. In sample 114 A20, reported in figure 3a, the substrate is completely covered, but the background is topped by 11! relatively large structures. On the other hand, sample B13 appears overall flat, but deep trenches some tens of nm large can be seen (figure 3b). For comparison, the SEM image of a graphite substrate 117 is also reported (Fig. 4). Similarly to the HOPG case, the quantitative characterization of samples 118 thickness and thickness unevenness is performed by using APT. Data collected before and after the 119 deposition of the samples are shown in figure 5 and 6, for Te and Sn samples respectively. Using 120 previously performed measurements of the substrate, the HOPG contribution can be subtracted to 1 2 1 indirectly obtain the target average thickness and disuniformity. The plot reports data collected before 122 (black dots) and after (orange dots) the deposition of the target. The data are fitted using a Crystal-ball 123 function, a function developed for energy loss processes. It is composed by a Gaussian part, which fits 124 the peak of the distribution, and a power law, for the low energy tail [5]. Crystal Ball fits (red solid line) 125 are well superimposed to the data; since the core of the function is a Gaussian, it is fair to consider the 126 sample disuniformity to follow a Gaussian distribution too. A formal explanation will be provided in 127 an incoming work. 128 The thickness of samples A20 and B13 resulted to be 160.6 μ g/cm² and 131 μ g/cm², respectively. The 129 thickness distribution's standard deviation has been estimated to be equal to 70.8 μ g/cm² for A20 1 30 and 85.4 μ g/cm² for B13 (about 44% and 65% of the average thicknesses). For both the Te samples, 1 31

the measured thickness was 268 μ g/cm², sample A14 having a standard deviation of 16 μ g/cm² and sample B10 having a standard deviation of 29.5 μ g/cm² (about 6% and 11% of the respective average thicknesses). The spectra reported in figure 5a appear broader than the spectra in figure 5b, even if the deposited films have the same thickness. This is due to the much thicker A20 substrate, whose effect on the α -particle energy is much more pronounced. Sn samples usually show a more pronounced

¹³⁷ unevenness than Te ones, which can be intuitively observed by looking at the broader distribution of

¹³⁸ Sn data (orange dots in fig. 6) with respect to Te ones (orange dots in fig. 5).



(a) APT measurement of sample A14, before and after deposition. Te film is 268 μ g/cm² thick, with a standard deviation of 16 μ g/cm². The points distribution can be fitted with a Crystal Ball function, pictured as red solid line.



(b) APT measurement of sample B10, before and after deposition. Te film is $268 \ \mu g/cm^2$ thick, with a standard deviation of $29.5 \ \mu g/cm^2$. Data of the two sets are fitted with a Crystal Ball function, showed as a red solid line, properly fits the data of both sets.

Figure 5. APT analysis of samples A14 and B10, collected before (black dots) and after (orange dots) the deposition. Orange dots have a lower average energy due to the extra layer crossed.





(b) APT measurement of sample B13, before and after deposition. Sn film is 131 μ g/cm² thick, with a standard deviation of 85.4 μ g/cm². Crystal Ball fits are well superimposed to data distributions.

Figure 6. APT analysis of samples A20 and B13, collected before (black dots) and after (orange dots) the deposition. The little shift of the orange dots toward lower energies is due to the limited thickness of the samples.

The samples were also analyzed by Rutherford Backscattering Spectrometry at the AN2000 139 accelerator of the INFN Legnaro Laboratories. In the RBS measurements, a fraction of an accelerated 140 alpha beam hitting the sample is partially backscattered at a certain angle. Such scattered beam is 141 detected by a silicon detector that measures its energy. From the evaluation of the energy loss by the 142 beam inside the target, the sample thickness can be deduced, together with the thickness of the buffer 143 under the target layer, if present. Moreover, since the backscattered ions' energy strongly depends on 144 the hit nucleus, RBS can be used to perform elemental analysis and to check the purity of the target. In 145 the backscattering experiments the collection angle was 160° and the α -beam impinged on the samples 146 at normal incidence with E_{α} =2000 keV. As it can be seen in Figure 7 and 8, in the backscattering 147 configuration the Te and Sn spectra can be analyzed individually (i.e. separated by HPOG substrate). 148 Since the beam spot is of order of 1mm², the analyzed region is smaller than that of APT (where the 149 analyzed area is about 7 mm^2). 150



(a) RBS spectrum of sample A14, the thickness resulted to be 268 μ g/cm².

(b) RBS spectrum of sample B10, the thickness resulted to be 259 μ g/cm²

Figure 7. RBS spectra of Te samples A14 and B10. In both the plots, the steepness of the slopes suggests a small unevenness of the depositions thickness.





(a) RBS measurement of sample A20, the measured thickness being equal to $182.5 \ \mu g/cm^2$.

(b) B13 RBS spectrum, resulting to have a thickness of $116 \,\mu\text{g/cm}^2$.

Figure 8. RBS spectra of Sn samples B13 and A20. The relevant non uniformity detected by APT can be qualitatively observed in the long low energy tails of both the data sets. In both samples, a very thin Cr buffer is used to improve the adhesion between the film and the substrate; the Cr signal can be seen after the low energy tail of the Sn signal around 1.4 MeV, the position being influenced by the film thickness (not exclusively). In the B13 spectrum, a further bump can be seen at lower energies, due to impurities trapped during the deposition.

The thicknesses of the Te A14 and B10 samples were evaluated to be 268 μ g/cm² and 259 μ g/cm², respectively. The discrepancy between RBS and APT can be expressed as the difference of the measured values in relation to their average:

$$\Delta = \frac{|x_{APT} - x_{RBS}|}{\frac{x_{APT} + x_{RBS}}{2}} \tag{5}$$

Being x the measured thickness. The agreement with APT measurements is very good for sample A14 and good for sample B10 (around 3.4%). The measured thickness for sample A20 was 182.5 μ g/cm², in good agreement with APT results (discrepancy of 12.8%). Sample B13 resulted to be 116 μ g/cm², with a discrepancy of 11.5% with respect to APT value.

The analysis of the RBS spectra is complicated by the presence of a large roughness of both the substrate 158 and the thin film. As pointed out in [6] and references therein, roughness produces measurable effects 159 on the low energy edge of the elemental backscattering spectrum which is spread (see Figure 8) because 1 60 the surface and interface roughness results in variations of the layer thickness across the beam spot area. 161 Moreover for targets with high roughness, the leading (high energy) edge of the spectrum may also be 162 spread when the outgoing particle scattered from the rough surface may traverse asperities, exiting 163 and re-entering the sample material more times. This second effect is mitigated at high backscattering 1 64 angles and for normal incidence experiments like those used in this work. 1 65

As for the APT spectra, the RBS measurements confirm the fact that the Te targets are characterized by a better thickness uniformity than the Sn ones. The extraction of roughness distributions from combined APT and RBS measurements is a complex task and more work is ongoing to perfect the models used for fitting the APT and RBS data.

4. Evaluation of Energy resolution

The energy of the projectile is affected by a number of effects, which are sources of uncertainty. Some are due to the involved physics, like straggling, while some other are due to the target morphology or to the equipment. The effects playing a major role in changing a particle energy are listed below.

175

Superconducting Cyclotron: the energy of the ion beam is not perfectly monochromatic; particles' energy spread around the average value is about 1/1000th of the nominal energy. As a remark, the indicated value for the energy spreading is referred to the current setup; it will likely change after the programmed upgrade for the high beam intensity facility. A fine study on the magnetic optics and collimators is undergoing, in order to preserve (and hopefully decrease) the original energy spread.

MAGNEX Spectrometer: the error in the particles' energy measurement introduced by the dipole
 spectrometer, by the Si detectors and by the reconstruction algorithms is about 1/1000 of the
 detected particle's energy. In the upgraded facility, the system shall be able to keep up with a
 much higher count rate, preserving the previous uncertainty on the energy measurements.

Straggling: the straggling effect is due to a statistical variation of the number of small impacts 186 with e⁻, suffered by unit path, by a charged particle crossing a medium. The outcome is a certain spread of the particles' energy around the average energy loss. In this particular context, things 188 are complicated by the reactions under investigation. In a DCE event, the traveling charged 1 89 particle suffers an increase (or decrease) of its atomic number Z by 2 units. Straggling, as well as 190 the energy loss by ionization, depends on the projectile's Z, so that its magnitude differs sensibly 1 91 before and after the DCE reaction. Moreover, straggling impact will strongly depend on where the reaction happens: an ¹⁸O turning into a ¹⁸Ne on the target surface will suffer more straggling 193 with respect to an ¹⁸O reacting at the target/HOPG interface. In fact, it would cross a larger 1 94 portion of target having a higher Z. After the target, the ejectile has to cross the HOPG backing, 195 whose nuclei (^{nat}C) are much lighter than the target's. Straggling here will be once more different 196 from earlier in the target. 197

Dispersion: dispersion error arises from the impossibility of knowing the precise point in which 198 the reaction will occur within the target. This is particularly important when studying DCE 199 reactions, since the change in the projectile's Z number heavily influences the kinematics of 200 its interaction with the target. The average energy loss differs substantially between a particle 2.01 reacting at the target surface or at the target/HOPG interface. The first noticeable effect is a 202 spectrum of average energy losses, one per infinitesimal portion of the target thickness. Every 203 collection of particles reacting at the same depth, therefore having the same average energy loss, 204 will suffer straggling as well as every other particle belonging to other average energy losses. The net effect is a further broadening of the energy distribution, due to the cross effect of dispersion 206 and straggling. 207

• Thickness disuniformity: thickness disuniformity further broadens the shape of the energy distribution, worsening the effects of dispersion and straggling. Particles that cross a valley (i.e. impinges on a point of the target surface where the thickness is less than the target average thickness) will have a higher average energy that the rest of the particles. Conversely, particles crossing a bump (i.e. a spot thicker than the target average thickness) will lose more energy, spreading the energy distribution towards lower values. For this reason, the targets must be as flat as possible.

• **Final state of reaction products**: reaction products may exit the reaction in diverse excited states. Every state but the ground states will diminish the kinetic energy of the ejectile, effectively shifting the energy distribution toward lower energies.

Evaluating their cumulative effect on the ejectiles' energy distribution is somewhat tricky, since these effects cannot be evaluated independently. A statistical fluctuation on effect A (e.g. target thickness variation) can positively or negatively influence effect B (e.g. error due to unknown reaction depth). To evaluate the statistical and cumulative effects on reaction product energy, a Monte Carlo code was written.

The model has been designed to simulate step by step the energy loss of a particle within the target, randomizing the statistical events listed above using models or data from measurements when available.

226

227 4.1. General Remarks on Monte Carlo code

The Monte Carlo code has been developed as a standalone program, but it will be integrated into NUMEN simulation software package to improve its accuracy. Some changes are in order to match the experimental needs and to fit the already existing software, but the code will be mostly preserved. The necessary input parameters are listed below.

The target isotope is used by designated functions to automatically load a set of quantities related to the chosen reaction channel, (¹⁸O,¹⁸Ne) or (²⁰Ne,²⁰O). Depending on the latter, the beam species and the reaction products are set up, together with their characteristic quantities (atomic number, mass, energy levels, density). An optional sample label can be added to improve readability;

- The target and substrate thickness and roughness, either coming from APT measurements or
 guessed to estimate the resolution of a foreseen target;
- **Projectile energy**, expressed in MeV/u;
- Number of DCE events, set by default to $2 \cdot 10^6$.

The energy loss of each simulated particle is evaluated stepwise by using the Bethe-Bloch formula (eq. 6), keeping fixed the infinitesimal energy loss δE (default values set equal to $5 \cdot 10^{-5}$ MeV); the spacial increment *dx* varies accordingly. The quantities inside the formula are adjusted depending on the particle's position (the crossed medium quantities varies between target and substrate) and history (e.g. its Z depends on whether the DCE reaction already occurred).

²⁴⁶ Given the energy involved, high energy corrections are neglected and the formula reads:

$$-\frac{dE}{dx} = \frac{4\pi N_A r_e^2 m_e c^2 \rho}{\beta^2} z^2 \frac{Z}{A} (0.5 \ln \frac{\beta^2 \gamma^2 E_{max}}{I^2} - \beta^2)$$
(6)

where N_A the Avogadro's Number, m_e and r_e the electron's mass and radius; ρ , I, A and Z are the medium's density, mean excitation potential, atomic number and mass number, respectively; z the projectile atomic number. Finally, E_{max} is the maximum energy transferable to an electron in a single collision, defined as:

$$E_{max} = \frac{2m_e\beta^2\gamma^2}{1+2\gamma\frac{m_e}{m_x}+\frac{m_e^2}{m_x}^2}$$
(7)

- ²⁴⁷ being m_x the projectile mass.
- 248 4.2. Monte Carlo code structure

A short scheme of the present version of the code is provided here.

Target and beam parameters

Thickness and relative unevenness from APT measurements (see section 3) are used to guess 251 the path crossed by the simulated ion. The effective thickness is sorted from the Gaussian 252 distribution built with the measured average thickness and standard deviation of the sample. 253 The same procedure is applied to sort the effective HOPG thickness. The reaction depth at which 254 the DCE reaction occurs is sorted within the previously determined effective target thickness. 255 Due to the very small thickness, the reaction probability is assumed constant throughout the 256 target: the actual value of cross section is unknown and is the goal of the NUMEN experiment. 257 The particle's energy is also modified due to the SC beam energy spread. The energy distribution 258 of the SC beam can be assumed to follow a Gaussian, whose standard deviation σ_{SC} is related to 259 the FWHM of the beam spot by: $FWHM = 2\sqrt{2 \ln 2}\sigma_{SC}$). The FWHM of the SC beam at various 260 mean energies E_b is proportional to E_b by a factor 10^{-3} . Therefore, the value used for σ_{SC} in the 261 MC is: $\sigma_{SC} = E_h \cdot 10^{-3} / 2\sqrt{2 \ln 2}$. 262

263

• Evaluation of straggling before DCE

The energy loss suffered by the projectile is calculated by using the Bethe-Bloch formula (equation 6). Fixed very small energy steps, corresponding to very small spatial increments, are repeatedly added until the particle reaches the randomly sorted reaction depth, still having a certain residual energy. Before the reaction, straggling is evaluated using the Gaussian model [7]:

$$\sigma_{straggling} = \sqrt{\xi E_{max} (1 - \beta^2 / 2)} \tag{8}$$

where E_{max} was defined above (paragraph 4.1) and ξ is the mean energy loss, defined as:

$$\xi = \frac{2\pi e^4 N_A z^2 Z \rho \delta x}{m_e \beta^2 c^2 A} \tag{9}$$

Where e is the electron charge and the other quantities were defined in paragraph 4.1.

The energy of the particle is updated by sorting a value in a Gaussian distribution centered around the residual energy and having as standard deviation $\sigma_{straggling}$.

DCE reaction

The energy of the ejectile exiting the DCE reaction is obtained by computing the kinematics of the collision $X_A^B(y_a^b, y_a^{*b\pm 2})X^{*B\mp 2}$, supposing that both the recoiling nucleus and the ejectile can exit the reaction in an excited state. The first three energy levels are considered for each involved nucleus. Considering a flat equal probability, there is a total of 9 alike combinations. So far, only reactions in which the projectile exits at 0 degrees have been simulated.

• Evaluation of straggling after DCE

After the reaction, ejectile's straggling and energy loss are calculated for the residual depth of the target and for the HOPG backing. The procedure followed is the same used before the reaction, considering atomic number change of the traveling particle due to the DCE. Straggling is sorted twice here, once after the target and one after the HOPG substrate.

278 • MAGNEX Resolution

The last contribution to be added is due to the MAGNEX spectrometer and particles' trajectory reconstruction procedure. Similarly to the Cyclotron, MAGNEX error can be quantified by using the FWHM value $FWHM = E_{ion} \cdot 10^{-3}$, here considering the ion's energy after it's passed the target assembly. The energy of the ion is once again modified guessing a value within a Gaussian distribution, centered around the ion's energy and having σ_{MAGNEX} as standard deviation (being σ_{MAGNEX} defined similarly to the SC case: $\sigma_{MAGNEX} = E_{ion} \cdot 10^{-3}/2\sqrt{2 \ln 2}$).

Sorting of simulated particles

The energies of the simulated particles are collected into 10 vectors, one per each combination of excited levels plus one containing the energy of every simulated particle. This sorting proves useful when calculating the standard deviation of each energy distribution and the related FWHM, a necessary step in evaluating the global energy resolution. In fact, each the standard deviation is used to build a Gaussian, which is superimposed to each distribution. Using the Gaussian fits, the FWHM of each distribution is calculated and then used to evaluate the energy resolution. To distinguish two adjacent energy levels, it is necessary for the resolution to be smaller than their energy gap. For two adjacent energy distribution, this criteria translates into:

$$\Delta E_{res \ 1,2} = \frac{FWHM_1 + FWHM_2}{2} < E_{gap \ 1,2} \tag{10}$$

²⁸⁵ Where $\Delta E_{res 1,2}$ is the resolution between level 1 and 2, FWHM_{*i*} (i=1,2) the FWHM of the ith distribution and $E_{gap 1,2}$ is the energy gap between levels 1 and 2.

287 4.3. Results from simulations

Using the results obtained from measurements of the described prototypes, the final energy resolution was simulated. For the simulations, the characteristics of the isotope ¹³⁰Te and ¹³⁰Xe (the recoiling nucleus of the DCE) were considered. In the showed plots, the lowest energy states combination (i.e. ejectile and recoiling nucleus in Ground State) is the rightmost peak; higher energy states combinations appear at lower energies. The total energy distributions of Te samples A14, figure 9, and B10, figure 10, are shown.





Figure 9. Energy distribution outcome of Monte Carlo simulation of sample A14. The G.S. and the first two excited levels of ¹³⁰Xe are fitted, respectively, with red, green and blue coloured Gaussians. The red curves are centered around the energy shift due to the final state of the ejectile ²⁰O, the green and blue ones follow at lower energies. The triplets of the target's states are separated by yellow dotted lines.

Ground states, first excited and second excited of the recoiling nucleus are fitted with red, green 295 and blue coloured Gaussian, respectively. They are energy-shifted depending on the ejectile energy 296 level. The deposited films of Te are very similar, the only two differences lying in the disuniformity 297 (6% for A14 and 11% for B10) and the thickness of the backing (2200 μ g/cm² and 1100 μ g/cm² 298 HOPG, nominal thickness). The contribution of the backing thickness is apparent: despite B10 higher 299 roughness, by halving said thickness the resolution $\Delta E_{res 0,1}$ for G.S. and first excited level of ¹³⁰Te 300 (the ejectile ²⁰O in G.S.) decreases by nearly 70 keV. More specifically, $\Delta E_{res 0,1}$ = 654.2 keV for A14 and 301 $\Delta E_{res 0.1}$ = 579 keV for B10. The achieved resolution is not sufficient, yet. The energy gap $E_{gav 0.1}$ of 302 ¹³⁰Xe is in fact 536.1 keV; a further reduction of the target and backing thickness is needed. 303



Figure 10. Energy distribution outcome of Monte Carlo simulation of sample B10. The colour scheme used for sample A14 is used here as well. Due to the thinner backing, the peaks seem more distinguishable with respect to figure 9.

For what it concerns Sn prototypes, the comparison between sample B13 with sample B6 (described in [4]) can be instructive about the role played by non uniformity. Achieving a sufficient resolution for Sn target is particularly problematic, mainly for two reasons: the ¹¹⁶Cd energy gap narrowness ($\Delta E_{res 0,1}$ =513.5 keV) and the growing mechanism of Sn during the deposition, which favors large material clusters rather than a uniform material distribution. In figure 11 are shown the first three energy levels of ¹¹⁶Cd paired with the ejectile in G.S. for prototypes B6 (figure 11a) and B13 (figure 11b).





(a) Energy distribution of ejectiles ¹⁸Ne leaving ¹¹⁶Cd recoiling nuclei in G.S. (red line), first excited level (green line) and second excited level (blue line) in sample B6.

(b) Energy distribution of ejectiles ¹⁸Ne leaving ¹¹⁶Cd recoiling nuclei in G.S. (red line), first excited level (green line) and second excited level (blue line) in sample B13.

Figure 11. A comparison between energy distribution of ejectiles exiting samples B6 and B13. The distributions look similar, despite the differences in the samples' morphology.

The two samples have a very different morphology: B6 is 234.3 μ g/cm² thick with a disuniformity of 65.6 μ g/cm², while B13 is 131 μ g/cm² with an unevenness of 85.4 μ g/cm². Despite B13 being much From the simulation results showed in figure 11, it is apparent the importance of reducing the unevenness as much as possible, in order to maximize the deposition thickness and, therefore, the

318 reaction rate.

319 5. Procedure for samples' design

Combining all the steps exposed so far it is possible to establish a standard procedure to producetargets which meet the experimental requirements.

• **Substrates characterization**: HOPG substrates, purchased by an external company, are characterized by using APT, in order to assess their effective thickness and disuniformity.

• **Exploratory deposition**: The element under study is deposited on HOPG substrates $2200 \ \mu g/cm^2$ and $1100 \ \mu g/cm^2$ thick (nominal values). Thinner substrates, about $450 \ \mu g/cm^2$ are currently under study.

• **Sample characterization**: prototypes are characterized by using the techniques described in section 3.

Energy resolution simulation: results of characterization are used to simulate the final energy resolution. If the resolution must be improved, new deposition conditions are explored until satisfactory results are achieved.

The combination of suitable characterization techniques and simulation code is valuable in pointing out which specific target feature must be changed in order to improve the energy resolution. The code can be used to see the outcome after changing one or more parameters of the target or of the substrate, providing a lead on where to focus the efforts to obtain the desired resolution.

336 6. Conclusions and future research

The need for statistically valid data in the measurement of DCE cross-section in the NUMEN 337 experiment calls for the use of a high intensity ion beam. The targets need to be backed by a highly 338 thermally conductive HOPG substrate, which negatively affects the energy resolution of the collected 339 particles. Since preserving a sufficient energy resolution is as important as the high statistics, a careful study was performed on target prototypes to reach the required precision. Te and Sn prototype 341 were deposited by Electron Beam Evaporation on HOPG substrate of different thickness and then 342 thoroughly characterized with Scanning Electron Microscopy, Alpha-Particle Transmission, and 343 Rutherford Backscattering Spectrometry techniques. Once the targets' thickness and unevenness 344 were assessed, they were used as input parameters of a Monte Carlo code, written to account for the 345 major effects which affect the particles' energy. Thanks to the synergy of experimental characterization 346 techniques and simulations, it is possible to predict the effect of the target on the total energy resolution. 347 The program can be used to see what physical characteristic of the target is better to adjust to obtain the 348 maximum improvement. A procedure to produce targets suitable for the experimental requirements 349 has been established and described. Future experimental work include a deeper study on the thinnest 350 available HOPG substrate (450 μ g/cm²), the improvement of Te and Sn non uniformity and the study 351 of other target materials. The code will be tested using data collected during past NUMEN runs and 352 recently analyzed. Real data will prove of great help in improving the code accuracy. 353

354 References

- Cavallaro, M. et al. The MAGNEX magnetic spectrometer for double charge exchange reactions. *Nucl. Inst. and Methods B* 2020, 463, 334–338.
- 257 2. Cappuzzello, F. et al. The NUMEN project: NUclear Matrix Elements for Neutrinoless double beta decay.
- 358 Eur. Phys. J. A 2018, 54, 72.

- Iazzi, F. et al. A new cooling technique for targets operating under very intense beams. WIT Transactions on
 Engineering Sciences 2017, 116, 61–70.
- Capirossi, V. et al. Thickness and Uniformity Characterization of Thin Targets for Intense Ion Beam
 Experiments. *Acta Phys. Pol. B* 2020, *51*, 661.
- Gaiser, J.E., Appendix-F Charmonium Spectroscopy from Radiative Decays of the J/Psi and Psi-Prime, Ph.D.
 Thesis 1982.
- 6. Molodtsov, S.L. et al. Accurate ion beam analysis in the presence of surface roughness JoPD 2008, 41, 20.
- 366 7. Seltzer, S.M. and Berger, M.J., Energy Loss Straggling of Protons and Mesons Studies in Penetration of Charged
- Particles in Matter; Nuclear Science Series 39, Nat. Academy of Sciences, Washington DC, 1964.