

Ionic gating in metallic superconductors: A brief review

Original

Ionic gating in metallic superconductors: A brief review / Piatti, Erik. - In: NANO EXPRESS. - ISSN 2632-959X. - ELETTRONICO. - 2:(2021), p. 024003. [10.1088/2632-959X/ac011d]

Availability:

This version is available at: 11583/2902613 since: 2022-05-16T13:41:43Z

Publisher:

IOP Publishing

Published

DOI:10.1088/2632-959X/ac011d

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

PAPER • OPEN ACCESS

Ionic gating in metallic superconductors: A brief review

To cite this article: Erik Piatti 2021 *Nano Ex.* **2** 024003

View the [article online](#) for updates and enhancements.



The Electrochemical Society
Advancing solid state & electrochemical science & technology



18th

239th ECS Meeting with IMCS18

ECS PLENARY LECTURE - CARBON MATERIALS

Presenter: **Rodney S. Ruoff**, Ulsan National Institute of Science & Technology

DIGITAL EVENT • May 31, 2021, 2100-2200 EDT • No cost to attend



REGISTER NOW



PAPER

Ionic gating in metallic superconductors: A brief review

OPEN ACCESS

RECEIVED

31 December 2020

REVISED

22 April 2021

ACCEPTED FOR PUBLICATION

13 May 2021

PUBLISHED

24 May 2021

Original content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](#).

Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.



Erik Piatti

Department of Applied Science and Technology, Politecnico di Torino, I-10129 Torino, Italy

E-mail: erik.piatti@polito.it**Keywords:** ionic gating, metallic superconductors, proximity effect, electrostatic screening, thin films**Abstract**

Ionic gating is a very popular tool to investigate and control the electric charge transport and electronic ground state in a wide variety of different materials. This is due to its capability to induce large modulations of the surface charge density by means of the electric-double-layer field-effect transistor (EDL-FET) architecture, and has been proven to be capable of tuning even the properties of metallic systems. In this short review, I summarize the main results which have been achieved so far in controlling the superconducting (SC) properties of thin films of conventional metallic superconductors by means of the ionic gating technique. I discuss how the gate-induced charge doping, despite being confined to a thin surface layer by electrostatic screening, results in a long-range ‘bulk’ modulation of the SC properties by the coherent nature of the SC condensate, as evidenced by the observation of suppressions in the critical temperature of films much thicker than the electrostatic screening length, and by the pronounced thickness-dependence of their magnitude. I review how this behavior can be modelled in terms of proximity effect between the charge-doped surface layer and the unperturbed bulk with different degrees of approximation, and how first-principles calculations have been employed to determine the origin of an anomalous increase in the electrostatic screening length at ultrahigh electric fields, thus fully confirming the validity of the proximity effect model. Finally, I discuss a general framework—based on the combination of *ab-initio* Density Functional Theory and the Migdal-Eliashberg theory of superconductivity—by which the properties of any gated thin film of a conventional metallic superconductor can be determined purely from first principles.

1. Introduction

The electric field effect is the modulation of the electronic properties of a material by the application of a transverse electric field. Its most influential application is the field-effect transistor (FET), which forms the backbone of modern semiconductor electronics. The possibility to control the superconducting (SC) state by means of the electric field effect has been an open issue in condensed matter physics since the seminal experiments of Glover and Sherrill [1] and Stadler [2] in the Sixties. In the former, one electrode of a capacitor was replaced with either a tin or an indium SC film, and upon charging the transition temperature T_c of the films was shifted at most by 0.08 and 0.07 mK respectively, corresponding to a faint $\approx 0.002\%$ shift in the original T_c [1]. In the latter, the maximum T_c shift was enhanced to $\approx 0.035\%$ by substituting the solid-oxide dielectric with a ferroelectric in the asymmetric capacitor [2]. These first results showed that controlling the SC phase of metallic superconductors via the electric field effect was feasible but of negligible impact for device applications, and the topic was largely abandoned for over thirty years. The discovery of high- T_c superconductors led to a rekindled interest in the topic, since the much smaller carrier density of the cuprates with respect to metallic superconductors allowed a much more effective tunability. Examples included an electric-field-induced 10 K T_c shift in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ by gating through ultra-high- κ dielectric SrTiO_3 [3], and a full superconductor-insulator transition (SIT) induced in $\text{GaBa}_2\text{Cu}_3\text{O}_{7-\delta}$ [4] by ferroelectric gating. Similarly, the low carrier density of ultrathin Bi films was also exploited to achieve a SIT by gating through SrTiO_3 [5]. Still, the range of applicability remained limited.

A turning point was achieved in the late 2000s with the introduction of the ionic gating technique, which rapidly became a very popular tool to investigate and control the electric transport and electronic ground state in a wide variety of different materials [6–27]. Ionic gating operates by exploiting the ultrahigh electric fields that build up at a voltage-polarized solid-electrolyte interface in the so-called electric double layer (EDL), made possible by the sub-nanometric spacing between the two charged layers in the EDL [28, 29]. When incorporated in an EDL-FET architecture, this allows attaining modulations of the surface charge density in the device channel which are often comparable to those occurring in metallic systems [13, 30, 31]. Since then, the ionic gating technique has found large success in tuning the properties of low- and moderate-carrier density superconductors. The SC properties of intrinsically-superconducting transition metal dichalcogenide NbSe₂ have been efficiently tuned by ionic gating both in the electrostatic [32] and in the electrochemical [33, 34] regime. High- T_c copper oxides are also strongly tunable by ionic gating, as showcased first in La_{1-x}Sr_xCuO₄ [35] and then in YBa₂Cu₃O_{7- δ} [36, 37], although in oxides in general care has to be taken to distinguish between electrostatic field-effect doping and field-induced changes in the oxygen stoichiometry due to the high mobility of the oxygen vacancies [38–43]. Among iron-based superconductors, low-carrier-density compound FeSe has been shown to develop a high-temperature ($T_c \gtrsim 40$ K) SC phase upon surface electron accumulation [44–47], and bulk gate-induced lithiation [48] and protonation [49]. While these results have been shown to be somewhat transferable to FeSe_{1-x}Te_x [50, 51] and (Li,Fe)OHFeSe [52], other iron-based compounds such as BaFe₂As₂ have been shown to be much less compliant [53], indicating that the ionic-gate tunability of iron-based superconductors is strongly dependent on the specific properties of each compound.


In contrast, the applicability of the ionic gating technique to conventional metallic superconductors has received significantly less attention, likely owing to their high intrinsic carrier density preventing the observation of large gate-induced changes to the intrinsic T_c or other strong changes to the ground state of the gated material. In this short review, I present the main results obtained so far concerning the tuning of the SC properties of metallic superconductors from both the experimental and the theoretical points of view, showing how the comparable simplicity of conventional metallic superconductors with respect to cuprates or iron-based compounds makes them an ideal playground to investigate the general physics of gate-induced perturbations to the SC state.

2. Ionic-gate-tuned superconductivity in niobium and niobium nitride films

The working principle of the EDL-FET architecture for an ion-gated metallic superconductor is sketched in figure 1(a). The active channel is separated from the gate counter-electrode by an electrolyte, which is usually either an ionic liquid [54] or an ion gel [55, 56]. When a positive/negative voltage V_G is applied to the gate electrode, cation/anions in the electrolyte accumulate at the surface of the sample and lead to the accumulation/depletion of electrons at its surface to maintain charge neutrality, building up the EDL. If no bulk electrochemical interactions are triggered (such as intercalation, protonation or formation of mobile vacancies), the application of an ionic gate thus results in a strong charge doping which is confined to a thin layer from the surface, with a thickness d_s that is set by the electrostatic screening length of the system, while the remaining bulk remains unperturbed [57]. The resulting modification to the electric transport properties of both the normal and SC state in the active channel can then be monitored by standard four-point resistivity measurements [54–56].

The first metallic superconductor to be investigated by means of the ionic gating technique was niobium (Nb), a standard electron-phonon superconductor with a bulk $T_c = 9.26$ K. Specifically, Choi *et al* reported that the T_c of niobium thin films could be reversibly modulated by gating through an ionic liquid [54]. The corresponding resistive transitions for an 8 nm thick film are shown in figure 1(b). From a qualitative standpoint, the results mirrored the early findings in indium thin films [1], with the accumulation of extra electrons in the system reducing the T_c and the depletion of electrons enhancing it. The magnitude of the effect was of course much larger thanks to the huge capacitance of the ionic gate, with the largest T_c shifts being around ~ 35 mK, i.e. $\approx 0.8\%$ of the intrinsic $T_c \simeq 4.3$ K [54]. The shape of the resistive transition was unaffected by the applied gate voltage, indicating that the ionic gate did not introduce additional inhomogeneity in the sample. Notably, the gate-induced modulations of T_c were volatile, i.e. fully reversible by simply removing the applied gate voltage and warming the sample above the melting point of the ionic liquid [54]. Additionally, it was also shown that the critical current I_c was also tunable by the ionic gate with the same behavior of T_c , indicating that not only the onset of the SC state, but also the superfluid density, could be enhanced and suppressed by electron depletion and accumulation respectively [54].

A second metallic superconductor, niobium nitride (NbN), was investigated via ionic gating shortly afterwards [55, 56]. With respect to pure Nb, NbN features a higher bulk $T_c \simeq 16$ K (making it more appealing for applications such as bolometers and single-photon detectors) and a shorter coherence length that allows thinning NbN films to few nanometers in thickness without major losses in T_c , all the while being mechanically



robust and chemically stable [58]. Furthermore, preliminary *ab initio* calculations suggested that its T_c could be nearly doubled if a sufficiently large number of electrons were to be added to its first unit cell from the surface [55]. In contrast with these predictions, it was experimentally shown that the gate-induced modulations of T_c in NbN thin films followed the same qualitative behavior observed in Nb thin films: As shown in figure 1(c), electron depletion and accumulation enhanced and suppressed T_c respectively, without affecting the shape of the transition, and the gate-induced shifts were fully volatile [55, 56]. From a quantitative standpoint, a larger maximum T_c shift ~ 85 mK was reported in 9.5 nm thick NbN films, which however corresponded to a smaller $\approx 0.6\%$ relative modulation due to the larger intrinsic $T_c \simeq 13.7$ K with respect to that of Nb [56].

In both ion-gated Nb and NbN thin films, the rigid shift of the resistive transition and the volatility of the T_c modulation were strongly suggestive of a (mostly) electrostatic origin of the charge doping. On the other hand, the observation of T_c suppressions in films of both materials with a thickness much larger than the electrostatic screening length is hardly compatible with a perturbation of the SC state occurring only at the surface, since the underlying unperturbed bulk would always reach a zero-resistance state at the same original T_c . Indeed, for T_c suppressions to be detected in the resistive transition, a suppression of the SC pairing must extend across the whole thickness of the film. In [54], the observation of T_c suppressions in NbN films as thick as 120 nm could not be justified in terms of pure surface charge doping, and the authors suggested that electro-mechanical effects due to the frozen ionic liquid may be responsible for the bulk modulations of SC. Conversely, corroborated by the fact that analogous bulk-like suppressions of T_c had been reported in gated indium films in the absence of any measurable strain [1], in [55] it was suggested that the electrostatic screening responsible for the surface confinement of the charge doping may deviate strongly in a superconductor from that found in a normal metal. Additionally, in [56] it was shown that the gate-tunability of T_c was strongly enhanced upon reducing of the thickness of the NbN thin films by means of ion milling (figure 1(c)). This ruled out a pure bulk origin of the modulation, which would be thickness-independent in the case of T_c suppressions, as well as a purely surface-bound phenomenon, which would be thickness-independent in the case of T_c enhancements, and hinted at a more complex interplay between surface charge doping and bulk perturbation of the SC pairing [56].




Figure 2. (a), Scheme of an ion-gated superconducting thin film. The EDL is composed by the Helmholtz layer of cations and the charge-doped surface layer (dark blue region). The unperturbed bulk of the film is indicated in light blue color. The input parameters of the proximity-effect model are indicated for both layers (see text for details). (b), Sketch of the SC order parameter profile (i.e. the SC energy gap) across a superconductor(S)/normal metal(N) junction, based on [63], for three values of the Gor'kov coherence length ξ . Dashed black line is the bulk regime ($\xi \ll l_s, l_n$) where proximity effect is negligible. Dotted blue line is the mesoscopic regime ($\xi \sim l_s, l_n$) where a sizeable penetration of the superfluid in the normal metal occurs. Solid red line is the Cooper limit ($\xi \gg l_s, l_n$) described in the text.

3. Surface-to-bulk coupling via superconducting proximity effect

The apparent contradiction between surface charge doping and bulk modulation of the SC pairing can be solved by considering the coherent nature of the SC condensate. Close to T_c , the superfluid density is small [59] and the electrostatic screening is dominated by unpaired electrons [60]. In the limit of weak and moderate electric fields, the thickness d_s within which the gate-induced charge doping is confined should then be comparable to the Thomas-Fermi length, i.e. few Å at most [57]. Conversely, perturbations to the SC order parameter cannot occur over length scales much smaller than the coherence length, which in metallic superconductors is at least of the order of few nanometers and can be as large as few microns [61]. As sketched in figure 2(a), gated SC thin films can then be conceptualized from the electronic point of view as a stack of a doped surface layer, where the electronic and vibrational properties are changed by the applied electric field, and an underlying bulk which remains unperturbed. The gate-induced perturbation to the SC pairing can then be described as a coupling between these two layers by means of SC proximity effect [56, 62]. This is a phenomenon that occurs at any interface between a superconductor and a normal metal, caused by the tunnelling of the Cooper pairs from the superconducting to the normal side (Andreev reflection) [63]. This leakage of Cooper pairs into the metallic bank can be thought of as an 'evanescent tail' of the SC order parameter, and close to the interface causes the appearance of a finite SC gap in the metal while suppressing it in the superconductor [61, 63], as sketched in figure 2(b). If the thicknesses of the two layers are small enough (Cooper limit [64]), as is often the case in gated thin films [54, 56, 62], the interface can be described as a single superconductor with an effective electron-phonon coupling constant $\langle \lambda \rangle$ that is a weighted average of the coupling constants in the normal (λ_n) and superconducting (λ_s) layers [61, 63].

Following the strong-coupling BCS theory for proximity effect [65], in [56] it was proposed that the T_c of a gated thin film could be obtained by:

$$T_c = \frac{\Theta}{1.45} \exp\left(-\frac{1 + \langle\lambda\rangle}{\langle\lambda\rangle - \mu^*}\right) \quad (1)$$

with

$$\langle\lambda\rangle = \frac{\lambda_s N_s d_s + \lambda_b N_b d_b}{N_s d_s + N_b d_b} \quad (2)$$


where the subscripts *s* and *b* referred to the surface and bulk layers of the film, $N_{s,b}$ are the densities of states (DOS) at the Fermi level, and $d_{s,b}$ are the thicknesses of the layers. Of course $d_s + d_b = t$ with *t* the total thickness of the film. It was then assumed that Θ (the representative temperature of the phonon spectrum) and μ^* (the Coulomb pseudopotential) were unchanged in the doped surface layer, and that T_c was modulated by charge doping mainly by shifting the Fermi level E_F : This in turn changes the DOS ratio N_s/N_b , calculated via density functional theory (DFT), so that $\lambda_s = \lambda_b \cdot N_s/N_b$ [56]. Despite these rough approximations, the experimentally-measured shifts of the T_c of gated thin NbN films as a function of both the induced charge density and of the film thickness could be accurately reproduced with the proximity effect model [56]. These findings showed that, even when the gate-induced electric field is confined in a thin layer at the surface by electrostatic screening, the coherent nature of the SC condensate forces the gate-induced perturbation to the SC state to extend in a region much larger than a single unit cell [56]. Indeed, critical-current measurements in gated mesoscopic samples of metallic superconductors later showed that, at temperatures much lower than T_c , the gate-induced suppressions of the SC state extended even further inside the bulk, approaching the London penetration depth of the material [66–68]. In these latter cases, however, it must be noted that the source of the suppression appears to be unrelated with charge doping (which is negligible due to the low capacitance of gating through a vacuum) and is still debated in the literature, with some authors suggesting that the penetration of the electric field may itself be detrimental to mesoscopic superconductors [66, 67], while others propose instead that the SC state is being destroyed by surface injection of high-energy electrons tunnelling from the gate [68, 69]. Critical current enhancements have also been recently reported in gated NbN nanobridges [70].

4. Anomalous electrostatic screening at ultrahigh electric fields

The good agreement between the experimental results on NbN thin films and the strong-coupling BCS model for the proximity effect in [17] also allowed to map the thickness of the electronically-perturbed surface layer d_s (i.e. the screening length of the electric field) as a function of the induced charge density and of the film thickness. As shown in figure 3(a) (filled circles), d_s was found to be independent on the film thickness and smaller than one unit cell at low induced charge density [56]. These two findings are important checks for the consistency of the model, since on the one hand electrostatic screening is a purely surface property that does not depend on the thickness of a material as long as the latter is larger than the screening length [57], and on the other hand a good agreement is found with the standard Thomas-Fermi theory of screening ($d_{TF} \sim 2 \text{ \AA}$ in NbN [56]) which is valid in the limit of low electric fields [57]. Surprisingly, however, d_s was found to strongly increase at large induced charge density (thus, at large gate electric fields), extending for over 5 unit cells for the highest induced values of charge doping [56], in contrast with the simple Thomas-Fermi picture in which the thickness of a surface accumulation layer is expected to decrease strongly at the increase of the electric field, due to the gate potential well becoming deeper and narrower [57, 71]. This was the first time that such an increase in the electrostatic screening length was reported in a conventional metal, although anomalously large thicknesses of the surface accumulation layer had previously been reported in ion-gated YBa₂Cu₃O₇ [72] and SrTiO₃ [73]. Notably, a very similar behavior of d_s versus the induced charge density was later reported in SrTiO₃ gated with a standard solid dielectric [74], ruling out that such a phenomenon could be associated to ion-gated surfaces only and suggesting that this would be a general behavior of any gated material once sufficiently large electric fields are achieved.

This unexpected feature could be partially accounted for by including non-linear corrections to the standard Thomas-Fermi screening model (solid black line in figure 3(a)), but even this extended model breaks down at larger electric fields [56]. A more complete theoretical description was given in [75] by employing a novel DFT method [76, 77] that treats the gate-induced charge doping more accurately than a uniform background charge [18, 27, 78] by fully accounting for the gate electric field of the FET configuration in a self-consistent way [79–85]. The DFT calculations in the FET configuration accurately reproduced the doping-dependence of the thickness of the surface accumulation layer (hollow red circles in figure 3(a)), although they became too computationally costly to investigate the largest values of induced charge density [75]. Furthermore, a crucial physical insight on the origin of the breakdown of the Thomas-Fermi approximation could be obtained by considering the spatial dependence of the screening charge for increasing field-induced electron doping.

As shown in figure 3(c), the total screening charge was composed of two main contributions, i.e. the accumulation layer where the extra induced carriers were confined, and an additional polarization of the pre-existent electron density [75]. The first contribution—analogue to the Thomas-Fermi screening prediction—is




always localized within the first atomic layer and dominates the total screening charge at low and moderate fields. The second contribution consists instead in the formation of charge dipoles arising from the polarization of the pristine atomic orbitals, and extends for an increasing number of atomic layers from the surface as the gate electric field is increased, eventually reaching well beyond the first unit cell from the surface. This displaced charge density was found to be negligible at low and moderate applied fields, but became comparable to that confined within the accumulation layer upon the application of sufficiently large electric fields [75], as shown in figure 3(b).

The findings reported in [75] thus fully confirmed the validity of the proximity-effect model developed in [56] for how the gate-induced surface perturbation of the electronic properties of a thin film of a metallic superconductor results in a bulk perturbation of its SC properties. Additionally, they also firmly established that a proper treatment beyond the Thomas-Fermi approximation is mandatory to describe the electrostatic screening in the presence of the ultrahigh electric fields typical of the ionic gate technique, even in the case of conventional metallic systems.

5. Eliashberg theory of gated superconducting films

Despite its success in describing the observed behavior of gated NbN thin films, the proximity-effect model developed in [56] described the modulations to the SC state purely in terms of doping-induced changes to the electronic properties of the system, namely the density of states at the Fermi level. While this was proven to be a good approximation for NbN, in general field-effect doping affects both the electronic [76, 77] and the vibrational [80, 81, 85] properties of a gated material, and a complete model must account for both contributions. This challenge was tackled in [62] by developing a method to determine the T_c of any gated thin film of a single-band metallic superconductor purely from first principles, by combining DFT calculations with the full Migdal-Eliashberg theory of proximity effect. In this method, the electron-phonon spectral function $\alpha^2 F(\omega)$ of the gated material, which describes its frequency-dependent electron-phonon coupling, is determined as a function of charge doping by DFT calculations. The $\alpha^2 F(\omega)$ of the doped surface layer and that of the unperturbed bulk are then used as input for the proximity Migdal-Eliashberg equations, which allow to determine T_c —and, in principle, also other SC properties—for the complete structure with arbitrary thickness. If the DFT calculations are performed using a uniform doping [18, 27, 62, 78], a selected thickness of the perturbed surface layer must also be included as an input parameter. Conversely, if the DFT calculations are performed within the FET geometry [80, 81, 85], the model has no free parameters except for the total thickness



of the film and the unperturbed value of μ^* . The Eliashberg formalism also allows to directly probe whether the gate-induced tuning of the SC state is mostly caused by a modulation of the electron-phonon coupling λ or the representative phonon frequency ω_{in} , since they can both be easily obtained from the $\alpha^2 F(\omega)$ [62]:

$$\lambda = 2 \int_0^{+\infty} \frac{\alpha^2 F(\omega)}{\omega} d\omega \quad (3)$$

and

$$\omega_{\text{in}} = \exp \left[\frac{2}{\lambda} \int_0^{+\infty} \ln(\omega) \frac{\alpha^2 F(\omega)}{\omega} d\omega \right] \quad (4)$$

and their doping-dependence compared to that of T_c .

In [62] this method was benchmarked by calculating the T_c of gated lead (Pb) thin films, as a function of the thicknesses of both the film and the perturbed surface layer. It was first shown that, unlike in In, Nb and NbN thin films, but analogously to Sn thin films, electron accumulation lead to an increase in T_c (see figure 4(c)). This increase was driven by a strong softening of the phonon modes, as evidenced by the doping-dependence of the $\alpha^2 F(\omega)$ (figure 4(a)), which strongly increased λ while only weakly reducing ω_{in} (figure 4(b)) [62]. Most importantly, it was found that proximity effect is strongly detrimental to the T_c tunability achieved by field-effect doping: In the absence of an unperturbed bulk layer, the calculations indicated that the T_c of Pb could be increased by nearly 2 K for a doping of 0.4 electrons per unit cell. In a 5 nm thick film this increase was already reduced by $\sim 90\%$, and by $\sim 99.4\%$ in a 40 nm thick film [62].

Using a realistic dependence of the screening length on the induced charge density, mirroring the one found in NbN (see figure 4(d)), it was also shown that the mechanism of T_c tuning of a superconducting film could be separated in two regimes [62]: At low electric fields, where Thomas-Fermi screening holds and the screening length is nearly constant, T_c is tuned by field-effect doping directly affecting the $\alpha^2 F(\omega)$. Whereas at high electric fields, where the Thomas-Fermi model breaks down and the screening length increases with the electric field,

$\alpha^2F(\omega)$ remains nearly unchanged and T_c is tuned via proximity effect only, via the change in the thickness of the perturbed surface layer. As shown in figure 4(e), the calculations indicated that this second, indirect tuning allows attaining nearly the same T_c shift achieved in the absence of the unperturbed bulk layer, but requires nearly 20 times the amount of induced charge density per unit surface [62]. In both regimes, increasing the film thickness dramatically reduces the tunability of T_c . As such, the findings reported in [62] clearly indicated how ultrathin films are mandatory to obtain sizeable modulations of T_c in metallic superconductors, while also reducing the required values of induced charge density—thus requiring smaller gate voltages to drive the EDL-FETs, in turn allowing to much more easily maintain the electrostatic operation of the ionic gate [55, 56]. These results are consistent with the experimental findings reported in gated NbSe₂, where the T_c of encapsulated bilayers could be electrostatically tuned by nearly $\approx 40\%$ of its original value [32].

Beyond the benchmark on gated Pb thin films, which is theoretically well-established but for which no experimental data are yet available, the proximity-Eliashberg method allowed to quantitatively reproduce the original T_c shift observed in gated indium films [86], giving a solid theoretical explanation to a problem which had otherwise remained unsolved for nearly fifty years. Furthermore, an extension of this method to two-band metallic superconductor MgB₂ was later developed in [87], thus overcoming the strong assumption of the single-band approximation.

6. Summary and outlook

In this short review, I have discussed the non-trivial way in which ionic gating can affect the properties of thin films of conventional metallic superconductors. Despite the efficient electrostatic screening of metallic systems confining the gate-induced charge doping to a thin layer at the surface of the material, a bulk-like modulation of the superconducting properties is systematically observed across multiple independent experiments. This coupling of the quasi-2D perturbation of the electronic structure to the long-range ‘bulk’ modulation of the SC condensate stems from the intrinsically coherent nature of the latter, which cannot be perturbed over length scales smaller than its coherence length. I have examined how this coupling can be described in terms of a proximity effect between the perturbed surface layer and the unperturbed bulk, and discussed how gated thin films of metallic superconductors can be modelled to different degrees of approximation. I have discussed how both experimental findings and *ab-initio* calculations allowed to unveil an anomalous increase of the electrostatic screening length at the ultra-high electric fields attainable via the ionic gating technique, and reviewed a general framework by which the superconducting properties of any gated thin film of a conventional metallic superconductor can be determined purely from first principles.

A few promising avenues for future investigations may also be suggested. Since the proximity-effect induced ‘smearing’ of the modulations to the SC pairing is a general phenomenon occurring in any gated superconductor, it could hinder the possibility to obtain large T_c shifts in any film significantly thicker than the screening length. It is then pivotal to maximize the tunability of the SC state by minimizing the influence of the bulk, such as by employing ultrathin films of metallic superconductors, or by downscaling the devices in more than one direction and investigating gated nanowires, nanobeams or nanoconstrictions, as evidenced by recent experimental findings. It is also necessary to consider device geometries suitable for the measurement of gated SC properties other than the critical temperature, such as the critical current (related to the superfluid density) and the superconducting energy gap. It may also be beneficial to expand the list of metallic superconductors to which ionic gating can be applied, which is often hampered by susceptibility to irreversible electrochemical interactions with the electrolyte: In this context, the development of a scalable encapsulation technique that would preserve a high gate capacitance would be needed.

Finally, in the perspective of potential applications the capability to operate the gate at temperatures close or lower than the critical temperature of the superconducting film would be highly desirable, demanding further investigations towards the development of electrolytes with lower melting point, or highly reliable ferroelectric gates. This is because the necessity to warm up the devices above their transition temperature to change the ionic-gate polarization limits applications to reconfigurable SC circuits and devices such as resonators [88]. However, attaining sizeable gate modulations below their transition temperature would open up a plethora of tantalizing applications, including low-dissipation logic and memory elements [70], novel architectures for qubits, interferometers, amplifiers and photodetectors [67], as well as magnetometers and heat-mastering systems [89].

ORCID iDs

Erik Piatti  <https://orcid.org/0000-0001-8733-5230>

References

- [1] Glover R E and Sherrill M D 1960 Changes in superconducting critical temperature produced by electrostatic charging *Phys. Rev. Lett.* **5** 248
- [2] Stadler H L 1965 Changing properties of metals by ferroelectric polarization charging *Phys. Rev. Lett.* **14** 979
- [3] Mannhart J, Ströbel J, Bednorz J G and Gerber Ch 1993 Large electric field effects in $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$ films containing weak links *Appl. Phys. Lett.* **62** 630
- [4] Ahn C H, Gariglio S, Paruch P, Tybell T, Antognazza L and Triscone J-M 1999 Electrostatic Modulation of Superconductivity in Ultrathin $\text{GdBa}_2\text{Cu}_3\text{O}_{7-x}$ Films *Science* **284** 1152–5
- [5] Parendo K A, K H Sarwa, Tan B, Bhattacharya A, Eblen-Zayas M, Staley N E and Goldman A M 2005 Electrostatic Tuning of the Superconductor-Insulator Transition in Two Dimensions *Phys. Rev. Lett.* **94** 197004
- [6] Ye J T, Inoue S, Kobayashi K, Kasahara Y, Yuan H T, Shimotani H and Iwasa Y 2010 Liquid-gated interface superconductivity on an atomically flat film *Nat. Mater.* **9** 125–8
- [7] Ye J T, Zhang Y J, Akashi R, Bahramy M S, Arita R and Iwasa Y 2012 Superconducting Dome in a Gate-Tuned Band Insulator *Science* **338** 1193–6
- [8] Jo S, Costanzo D, Berger H and Morpurgo A F 2015 Electrostatically Induced Superconductivity at the Surface of WS_2 *Nano Lett.* **15** 1197–202
- [9] Shi W, Ye J T, Zhang Y, Suzuki R, Yoshida M, Miyazaki J, Inoue N, Saito Y and Iwasa Y 2015 Superconductivity Series in Transition Metal Dichalcogenides by Ionic Gating *Sci. Rep.* **5** 12534
- [10] Yu Y *et al* 2015 Gate-tunable phase transitions in thin flakes of 1T-TaS₂ *Nat. Nanotechnol.* **10** 270–6
- [11] Saito Y and Iwasa Y 2015 Ambipolar insulator-to-metal transition in black phosphorus by ionic-liquid gating *ACS Nano* **9** 3192–8
- [12] Gonnelli R S, Paolucci F, Piatti E, Sharda K, Sola A, Tortello M, Nair J R, Gerbaldi C, Bruna M and Borini S 2015 Temperature dependence of electric transport in few-layer graphene under large charge doping induced by electrochemical gating *Sci. Rep.* **5** 9554
- [13] Li L J, O'Farrel E C T, Loh K P, Eda G, Özyilmaz B and Castro Neto A H 2016 Controlling many-body states by the electric-field effect in a two-dimensional material *Nature* **529** 185–9
- [14] Ovchinnikov D, Gargiulo F, Allain A, Pasquier D J, Dumcenco D, Ho C-H, Yazyev O V and Kis A 2016 Disorder engineering and conductivity dome in ReS_2 with electrolyte gating *Nat. Commun.* **7** 12391
- [15] Piatti E, Galasso S, Tortello M, Nair J R, Gerbaldi C, Bruna M, Borini S, Daghero D and Gonnelli R S 2017 Carrier mobility and scattering lifetime in electric double-layer gated few-layer graphene *Appl. Surf. Sci.* **395** 37–41
- [16] Wang Y *et al* 2017 Structural phase transition in monolayer MoTe_2 driven by electrostatic doping *Nature* **550** 487–91
- [17] Piatti E, Chen Q and Ye J 2017 Strong dopant dependence of electric transport in ion-gated MoS_2 *Appl. Phys. Lett.* **111** 013106
- [18] Gonnelli R S *et al* 2017 Weak localization in electric-double-layer gated few-layer graphene *2D Mater* **4** 035006
- [19] Zeng J *et al* 2018 Gate-induced interfacial superconductivity in 1T-SnSe₂ *Nano Lett.* **18** 1410–5
- [20] Deng Y *et al* 2018 Gate-tunable room-temperature ferromagnetism in two-dimensional Fe_3GeTe_2 *Nature* **563** 94–9
- [21] Piatti E, De Fazio D, Daghero D, Tamalampudi S R, Yoon D, Ferrari A C and Gonnelli R S 2018 Multi-Valley Superconductivity in Ion-Gated MoS_2 Layers *Nano Lett.* **18** 4821–30
- [22] Piatti E, Chen Q, Tortello M, Ye J and Gonnelli R S 2018 Possible charge-density-wave signatures in the anomalous resistivity of Li-intercalated multilayer MoS_2 *Appl. Surf. Sci.* **461** 269–75
- [23] Wang Z *et al* 2018 Electric-field control of magnetism in a few-layered van der Waals ferromagnetic semiconductor *Nat. Nanotechnol.* **13** 554–9
- [24] Piatti E, Galanti F, Pippione G, Pasquarelli A and Gonnelli R S 2019 Towards the insulator-to-metal transition at the surface of ion-gated nanocrystalline diamond films *Eur. Phys. J. Spec. Top.* **228** 689–96
- [25] Ren X, Wang Y, Xie Z, Xue F, Leighton C and Frisbie C D 2019 Gate-Tuned Insulator-Metal Transition in Electrolyte-Gated Transistors Based on Tellurene *Nano Lett.* **19** 4738–44
- [26] Piatti E, Romanin D, Daghero D and Gonnelli R S 2019 Two-dimensional hole transport in ion-gated diamond surfaces: A brief review *Low Temp. Phys.* **45** 1143–55
- [27] Piatti E, Pasquarelli A and Gonnelli R S 2020 Orientation-dependent electric transport and band filling in hole co-doped epitaxial diamond films *Appl. Surf. Sci.* **528** 146795
- [28] Fujimoto T and Awaga K 2013 Electric-double-layer field-effect transistors with ionic liquids *Phys. Chem. Chem. Phys.* **15** 8983–9006
- [29] Ueno K, Shimotani H, Yuan H, Ye J, Kawasaki M and Iwasa I 2014 Field-Induced superconductivity in electric double layer transistors *J. Phys. Soc. Jpn.* **83** 032001
- [30] Daghero D, Paolucci F, Sola A, Tortello M, Ummanino G A, Agosto M, Gonnelli R S, Nair J R and Gerbaldi C 2012 Large conductance modulation of gold thin films by huge charge injection via electrochemical gating *Phys. Rev. Lett.* **108** 066807
- [31] Tortello M, Sola A, Sharda K, Paolucci F, Nair J R, Gerbaldi C, Daghero D and Gonnelli R S 2013 Huge field-effect surface charge injection and conductance modulation in metallic thin films by electrochemical gating *Appl. Surf. Sci.* **269** 17–22
- [32] Xi X, Berger H, Forró L, Shan J and Mak K F 2016 Gate tuning of electronic phase transitions in two-dimensional NbSe_2 *Phys. Rev. Lett.* **117** 106801
- [33] Li Z J, Gao B F, Zhao J L, Xie X M and Jiang M H 2014 Effect of electrolyte gating on the superconducting properties of thin 2H-NbSe₂ platelets *Supercond. Sci. Technol.* **27** 015004
- [34] Yoshida M, Ye J T, Nishizaki T, Kobayashi N and Iwasa Y 2016 Electrostatic and electrochemical tuning of superconductivity in two-dimensional NbSe_2 crystals *Appl. Phys. Lett.* **108** 202602
- [35] Bollinger A T, Dubuis G, Yoon J, Pavuna D, Misewich J and Božovic I 2011 Superconductor-insulator transition in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ at the pair quantum resistance *Nature* **472** 458–60
- [36] Leng X, Garcia-Barriocanal J, Bose S, Lee Y and Goldman A M 2011 Electrostatic Control of the Evolution from a Superconducting Phase to an Insulating Phase in Ultrathin $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Films *Phys. Rev. Lett.* **107** 027001
- [37] Leng X, Garcia-Barriocanal J, Yang B, Lee Y, Kinney J and Goldman A M 2012 Indications of an Electronic Phase Transition in Two-Dimensional Superconducting $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ Thin Films Induced by Electrostatic Doping *Phys. Rev. Lett.* **108** 067004
- [38] Jeong J, Aetukuri N, Graft T, Schladt T D, Samant M G and Parkin S S P 2013 Suppression of Metal-Insulator Transition in VO_2 by Electric Field-Induced Oxygen Vacancy Formation *Science* **339** 1402–5
- [39] Schladt T D, Graft T, Aetukuri N B, Li M, Fantini A, Jiang X, Samant M G and Parkin S S P 2013 Crystal-Facet-Dependent Metallization in Electrolyte-Gated Rutile TiO_2 Single Crystals *ACS Nano* **7** 8074–81
- [40] Walter J, Wang H, Luo B, Frisbie C D and Leighton C 2016 Electrostatic versus Electrochemical Doping and Control of Ferromagnetism in Ion-Gel-Gated Ultrathin $\text{La}_{0.5}\text{Sr}_{0.5}\text{CoO}_{3-\delta}$ *ACS Nano* **10** 7799–810

- [41] Zhang L *et al* 2017 The mechanism of electrolyte gating on High- T_c cuprates *ACS Nano* **11** 9950–6
- [42] Zeng S W *et al* 2018 Oxygen Electromigration and Energy Band Reconstruction Induced by Electrolyte Field Effect at Oxide Interfaces *Phys. Rev. Lett.* **121** 146802
- [43] Saleem M S *et al* 2019 Field control of phase transition and tunable resistive switching in $\text{SrFeO}_{2.5}$ *ACS Appl. Mater. Interfaces* **11** 6581–5688
- [44] Shiogai J, Ito Y, Mitsuhashi T, Nojima T and Tsukazaki A 2016 Electric-field-induced superconductivity in electrochemically-etched ultrathin FeSe films on SrTiO_3 and MgO *Nat. Phys.* **12** 42–6
- [45] Lei B, Cui J H, Xiang Z J, Shang C, Wang N Z, Ye G J, Luo X G, Wu T, Sun Z and Chen X H 2016 Evolution of high-temperature superconductivity from low- T_c phase tuned by carrier concentration in FeSe thin flakes *Phys. Rev. Lett.* **116** 077002
- [46] Hanzawa K, Sato H, Hiramatsu H, Kamiya T and Hosono H 2016 Electric field-induced superconducting transition of insulating FeSe thin film at 35 K *Proc. Natl. Acad. Sci. USA* **113** 3986
- [47] Miyakawa T *et al* 2018 Enhancement of superconducting transition temperature in FeSe electric-double-layer transistor with multivalent ionic liquids *Phys. Rev. Materials* **2** 031801(R)
- [48] Lei B *et al* 2017 Tuning phase transitions of FeSe thin flakes by field effect transistor with solid ion conductor as gate dielectric *Phys. Rev. B* **95** 020503(R)
- [49] Cui Y *et al* 2019 Ionic-Liquid-Gating Induced Protonation and Superconductivity in FeSe, $\text{FeSe}_{0.93}\text{S}_{0.07}$, ZrNCl , 1T-TaS_2 and Bi_2Se_3 *Chin. Phys. Lett.* **36** 077401
- [50] Kouno S, Sato Y, Katayama Y, Ichinose A, Asami D, Nabeshima F, Imai Y, Maeda A and Ueno K 2018 Superconductivity at 38 K in an electrochemical interface between ionic liquid and $\text{FeSe}_{0.8}\text{Te}_{0.2}$ on various substrates *Sci. Rep.* **8** 14731
- [51] Zhu C S *et al* 2017 Tuning electronic properties of $\text{FeSe}_{0.5}\text{Te}_{0.5}$ thin flakes by a novel field effect transistor *Phys. Rev. B* **95** 174513
- [52] Lei B *et al* 2016 Gate-tuned Superconductor-Insulator transition in $(\text{Li,Fe})\text{OHFeSe}$ *Phys. Rev. B* **93** 060501(R)
- [53] Piatti E *et al* 2019 Ambipolar suppression of superconductivity by ionic gating in optimally doped $\text{BaFe}_2(\text{As,P})_2$ ultrathin films *Phys. Rev. Materials* **3** 044801
- [54] Choi J, Pradheesh R, Kim H, Im H, Chong Y and Chae D H 2014 Electrical modulation of superconducting critical temperature in liquid-gated thin niobium films *Appl. Phys. Lett.* **105** 012601
- [55] Piatti E, Sola A, Daghero D, Ummarino G A, Laviano F, Nair J R, Gerbaldi C, Cristiano R, Casaburi A and Gonnelli R S 2016 Superconducting Transition Temperature Modulation in NbN via EDL Gating *J. Supercond. Novel Magn.* **29** 587–91
- [56] Piatti E, Daghero D, Ummarino G A, Laviano F, Nair J R, Cristiano R, Casaburi A, Portesi C, Sola A and Gonnelli R S 2017 Control of bulk superconductivity in a BCS superconductor by surface charge doping via electrochemical gating *Phys. Rev. B* **95** 140501(R)
- [57] Chazalviel J-N 1999 *Coulomb Screening by Mobile Charges: Applications to Materials Science, Chemistry, and Biology* (New York, NY: Springer) (<https://doi.org/10.1007/978-1-4612-1762-6>)
- [58] Chockalingam S P, Chand M, Jesudasan J, Tripathi V and Raychaudhuri P 2008 Superconducting properties and Hall effect of epitaxial NbN thin films *Phys. Rev. B* **77** 214503
- [59] Hirsch J E 2004 Reply to Comment on Charge expulsion and electric field in superconductors *Phys. Rev. B* **70** 226504
- [60] Koyama T 2004 Comment on Charge expulsion and electric field in superconductors *Phys. Rev. B* **70** 226503
- [61] de Gennes P G 1964 Boundary Effects in Superconductors *Rev. Mod. Phys.* **36** 225
- [62] Ummarino G A, Piatti E, Daghero D, Gonnelli R S, Yu I, Sklyadneva, Chulkov E V and Heid R 2017 Proximity Eliashberg theory of electrostatic field-effect doping in superconducting films *Phys. Rev. B* **96** 064509
- [63] Klapwijk T M 2004 Proximity effect from an andreev perspective *J. Supercond.* **17** 593
- [64] Cooper L N 1961 Superconductivity in the neighborhood of metallic contacts *Phys. Rev. Lett.* **6** 689
- [65] Silvert W 1975 Superconducting proximity effect in the strong-coupling limit *Phys. Rev. B* **12** 4870
- [66] De Simoni G, Paolucci F, Solinas P, Strambini E and Giazotto F 2018 Metallic supercurrent field-effect transistor *Nat. Nanotechnol.* **13** 802–5
- [67] Paolucci F, De Simoni G, Solinas P, Strambini E, Ligato N, Virtanen P, Braggio A and Giazotto F 2019 Magnetotransport experiments on fully metallic superconducting dayem bridge field-effect transistors *Phys. Rev. Appl.* **11** 024061
- [68] Ritter M F, Fuhrer A, Haxwell D Z, Hart S, Gumann P, Riel H and Nichele F 2021 A superconducting switch actuated by injection of high-energy electrons *Nat. Commun.* **12** 1266
- [69] Kafanov S, Pashkin Y, Tsepelin V, Guthrie A and Golokolenov I 2021 On the origin of the controversial electrostatic field effect in superconductors *Nat. Commun.* **12** 2747
- [70] Rocci M, Suri D, Kamra A, Vilela G, Takamura Y, Nemes N M, Martinez J L, Garcia Hernandez M and Moodera J S 2021 Large enhancement of critical current in superconducting devices by gate voltage *Nano Lett.* **21** 216–21
- [71] Ando T, Fowler A B and Stern F 1982 Electronic properties of two-dimensional systems *Rev. Mod. Phys.* **54** 437–672
- [72] Fête A, Rossi L, Augieri A and Senatore C 2016 Ionic liquid gating of ultra-thin $\text{YBa}_2\text{Cu}_3\text{O}_7$ films *Appl. Phys. Lett.* **109** 192601
- [73] Ueno K, Nojima T, Yonezawa S, Kawasaki M, Iwasa Y and Maeno Y 2014 Effective thickness of two-dimensional superconductivity in a tunable triangular quantum well of SrTiO_3 *Phys. Rev. B* **89** 020508
- [74] Valentini D, Gariglio S, Fête A, Triscone J-M, Berthod C and van der Marel D 2017 Modulation of the superconducting critical temperature due to quantum confinement at the $\text{LaAlO}_3/\text{SrTiO}_3$ interface *Phys. Rev. B* **96** 094518
- [75] Piatti E, Romanin D, Gonnelli R S and Daghero D 2018 Anomalous screening of an electrostatic field at the surface of niobium nitride *Appl. Surf. Sci.* **461** 17–22
- [76] Brumme T, Calandra M and Mauri F 2014 Electrochemical doping of few-layer ZrNCl from first principles: Electronic and structural properties in field-effect configuration *Phys. Rev. B* **89** 245406
- [77] Brumme T, Calandra M and Mauri F 2015 First-principles theory of field-effect doping in transition-metal dichalcogenides: Structural properties, electronic structure, Hall coefficient, and electrical conductivity *Phys. Rev. B* **91** 155436
- [78] Ge Y and Liu A Y 2013 Phonon-mediated superconductivity in electron-doped single-layer MoS_2 : A first-principles prediction *Phys. Rev. B* **87** 241408
- [79] Brumme T, Calandra M and Mauri F 2016 Determination of scattering time and of valley occupation in transition-metal dichalcogenides doped by field effect *Phys. Rev. B* **93** 081407
- [80] Sohler T, Calandra M and Mauri F 2017 Density functional perturbation theory for gated two-dimensional heterostructures: Theoretical developments and application to flexural phonons in graphene *Phys. Rev. B* **96** 075448
- [81] Romanin D, Sohler Th, Daghero D, Mauri F, Gonnelli R S and Calandra M 2019 Electric field exfoliation and high- T_c superconductivity in field-effect hole-doped hydrogenated diamond (111) *Appl. Surf. Sci.* **496** 143709
- [82] Piatti E, Romanin D, Gonnelli R S and Daghero D 2019 Mapping multi-valley Lifshitz transitions induced by field-effect doping in strained MoS_2 nanolayers *J. Phys. Condens. Matter* **31** 114002

- [83] Romanin D 2020 Field-effect-induced superconductivity in surfaces of tetrahedrally coordinated semiconductors: The case of (111) hydrogenated silicon *Il Nuovo Cimento* **43** 115
- [84] Romanin D, Brumme T, Daghero D, Gonnelli R S and Piatti E 2020 Strong band-filling-dependence of the scattering lifetime in gated MoS₂ nanolayers induced by the opening of intervalley scattering channels *J. Appl. Phys.* **128** 063907
- [85] Romanin D, Ummarino G A and Piatti E 2021 Migdal-Eliashberg theory of multi-band high-temperature superconductivity in field-effect-doped hydrogenated (111) diamond *Appl. Surf. Sci.* **536** 147723
- [86] Ummarino G A and Romanin D 2020 Theoretical Explanation of Electric Field-Induced Superconductive Critical Temperature Shifts in Indium Thin Films *Phys. Status Solidi B* **257** 1900651
- [87] Ummarino G A and Romanin D 2019 Proximity two bands Eliashberg theory of electrostatic field-effect doping in a superconducting film of MgB₂ *J. Phys. Condens. Matter* **31** 024001
- [88] Zmuidzinas J 2012 Superconducting microresonators: Physics and applications *Annu. Rev. Condens. Matter Phys.* **3** 169–214
- [89] Paolucci F, De Simoni G, Solinas P, Strambini E, Puglia C, Ligato N and Giazotto F 2019 Field-effect control of metallic superconducting systems *AVS Quantum Sci.* **1** 016501