

Novel PBATBased Biocomposites Reinforced with Bioresorbable Phosphate Glass Microparticles

Original

Novel PBATBased Biocomposites Reinforced with Bioresorbable Phosphate Glass Microparticles / Togliatti, Elena; Pugliese, Diego; Giubilini, Alberto; Messori, Massimo; Milanese, Daniel; Sciancalepore, Corrado. - In: MACROMOLECULAR SYMPOSIA. - ISSN 1022-1360. - ELETTRONICO. - 405:1(2022), p. 2100238. [10.1002/masy.202100238]

Availability:

This version is available at: 11583/2972502 since: 2022-10-21T11:03:33Z

Publisher:

Wiley

Published

DOI:10.1002/masy.202100238

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

Novel PBAT-Based Biocomposites Reinforced with Bioresorbable Phosphate Glass Microparticles

Elena Togliatti, Diego Pugliese, Alberto Giubilini, Massimo Messori, Daniel Milanese, and Corrado Sciancalepore*

Biocomposites based on poly(butylene adipate terephthalate) (PBAT) and reinforced with micro-particles of inorganic biodegradable phosphate glass (PG) at 2, 10, and 40 wt% are prepared and characterized from a mechanical and morphological point of view. Scanning electron microscope (SEM) images show a good dispersion of the PG micro-grains, even at high concentrations, in the PBAT matrix, resulting in homogeneous composites. Tensile and dynamic-mechanical tests, respectively, indicate that Young's and storage moduli increase with PG concentration. The reinforcement of PBAT aims at modifying and tailoring the mechanical and viscoelastic properties of the material to expand its application field especially in the food and agricultural packaging sector, thanks to the similarity of PBAT performance with polyethylene.

1. Introduction

In the last century, plastic materials have been rapidly developed and widely employed in varieties of fields thanks to their peculiar properties and low costs. Unfortunately, most of these conventional plastics, such as polyethylene (PE), polypropylene (PP), and polystyrene (PS) have oil origin and their wastes cannot be biodegraded. Therefore, the increase in the production and consumption of traditional plastics results in oil consumption and

serious environmental pollution. These major problems caused by conventional plastics should be solved for sustainable development in future.^[1]

The present work aims at the preparation and subsequent microstructural, mechanical, and dynamic-mechanical characterization of biocomposites based on poly(butylene adipate terephthalate) (PBAT), loaded with micro-particles of inorganic biodegradable phosphate glass (PG)^[2] at 0, 2, 10, and 40 wt%, respectively named as PBAT, PBAT+2%PG, PBAT+10%PG, and PBAT+40%PG.

The reinforcement of flexible polymeric matrices such as PBAT has the purpose of modifying and tailoring the mechanical and viscoelastic properties of the material in order to expand its application field especially in the food and agricultural packaging sector,^[3] thanks to the similarity of PBAT performance with PE.^[4]

PBAT is an oil-based polymer that is expected to undergo complete biodegradation in soil over a period of 6 weeks.^[5] This behavior makes it an ideal sustainable replacement for PE. Moreover, experimental evidence shows the possibility to obtain PBAT monomers from renewable sources, making this polymer even more interesting in terms of environmental sustainability.^[6,7,8]

The PBAT-PG master batches are prepared by solvent casting, using chloroform as suitable solvent. Following a thermal drying process up to constant weight, the resulting composite pellets are used for the injection molding of model 1BA specimens, employed for tensile characterization, according to UNI EN ISO 527 standard.

The specimens are subjected to uniaxial tensile stress and the collected data are analyzed to obtain characteristic parameters such as the Young's modulus (E), the yield stress (σ_y), the stress at break (σ_B), the elongation at break (ϵ_B), and the toughness (T).

Following the ASTM D7028 standard, dynamic-mechanical analysis (DMA) is carried out on a DMA analyzer using a single cantilever clamp to determine the storage modulus (E'), loss modulus (E''), and loss factor ($\tan\delta$) of the composites.


The sample microstructure is then observed on cross-sectional surface by means of SEM.

2. Results and Discussion

SEM images display homogeneous dispersion and distribution of the filler particles in the polymer matrix with no aggregates or

E. Togliatti, D. Milanese, C. Sciancalepore
Dipartimento di Ingegneria e Architettura
Università di Parma
Parco Area delle Scienze 181/A, Parma 43124, Italia
E-mail: corrado.sciancalepore@unipr.it

E. Togliatti, D. Pugliese, A. Giubilini, M. Messori, D. Milanese,
C. Sciancalepore
INSTM
Consorzio Interuniversitario Nazionale di Scienza e Tecnologia dei
Materiali
Via G. Giusti 9, Firenze 50121, Italia
D. Pugliese, A. Giubilini, M. Messori
Dipartimento di Scienza Applicata e Tecnologia
Politecnico di Torino
Corso Duca degli Abruzzi 24, Torino 10129, Italia

 The ORCID identification number(s) for the author(s) of this article can be found under <https://doi.org/10.1002/masy.202100238>

© 2022 The Authors. Macromolecular Symposia published by Wiley-VCH GmbH. This is an open access article under the terms of the Creative Commons Attribution License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

DOI: 10.1002/masy.202100238

Novel PBATBased Biocomposites Reinforced with Bioresorbable Phosphate Glass Microparticles

Original

Novel PBATBased Biocomposites Reinforced with Bioresorbable Phosphate Glass Microparticles / Togliatti, Elena; Pugliese, Diego; Giubilini, Alberto; Messori, Massimo; Milanese, Daniel; Sciancalepore, Corrado. - In: MACROMOLECULAR SYMPOSIA. - ISSN 1022-1360. - ELETTRONICO. - 405:1(2022), p. 2100238. [10.1002/masy.202100238]

Availability:

This version is available at: 11583/2972502 since: 2022-10-21T11:03:33Z

Publisher:

Wiley

Published

DOI:10.1002/masy.202100238

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

Table 2. Dynamic-mechanical properties of PBAT-PG composites.

Sample	E' (-40°C) [MPa]	E' (10°C) [MPa]	E' (20°C) [MPa]	E' (40°C) [MPa]	T _g [°C]
PBAT	2800 ± 20	203 ± 20	178 ± 20	135 ± 20	-17.8 ± 0.5
PBAT+2%PG	2995 ± 20	251 ± 20	223 ± 20	181 ± 20	-17.4 ± 0.5
PBAT+10%PG	3310 ± 20	284 ± 20	252 ± 20	206 ± 20	-16.9 ± 0.5
PBAT+40%PG	5350 ± 20	575 ± 20	496 ± 20	359 ± 20	-17.2 ± 0.5

Conflict of Interest

The authors declare no conflict of interest.

Data Availability Statement

The data that support the findings of this study are available from the corresponding author upon reasonable request.

Keywords

biopolymers, composites, phosphate glass, poly(butylene adipate terephthalate)

Received: June 15, 2021

Revised: August 5, 2021

- [1] R. Hurley, A. Horton, A. Lusher, L. Nizzetto, in *Plastic Waste and Recycling*, **2020**, pp. 163-193.

- [2] V. M. Sglavo, D. Pugliese, F. Sartori, N. G. Boetti, E. Ceci-Ginistrelli, G. Franco, D. Milanese, *J. Alloys Compd.* **2019**, *778*, 410.
- [3] F. V. Ferreira, L. S. Cividanes, R. F. Gouveia, L. M. F. Lona, *Polym. Eng. Sci.* **2019**, *59*, E7.
- [4] V. Nagarajan, M. Misra, A. K. Mohanty, *Ind. Crops Prod.* **2013**, *42*, 461.
- [5] J. Jian, Z. Xiangbin, H. Xianbo, *Adv. Ind. Eng. Polym. Res.* **2020**, *3*, 19.
- [6] E. Skoog, J. H. Shin, V. Saez-Jimenez, V. Mapelli, L. Olsson, *Biotechnol. Adv.* **2018**, *36*, 2248.
- [7] R. G. C. Silva, T. F. Ferreira, É. R. Borges, *J. Chem. Technol. Biotechnol.* **2020**, *95*, 3057.
- [8] M. Volanti, D. Cespi, F. Passarini, E. Neri, F. Cavani, P. Mizsey, D. Fozzer, *Green Chem.* **2019**, *21*, 885.
- [9] S. L. Bazhenov, G. P. Goncharuk, V. G. Oshmyan, O. A. Serenko, *Polym. Sci. – Ser. B* **2006**, *48*, 70.
- [10] R. Taurino, C. Sciancalepore, L. Collini, M. Bondi, F. Bondioli, *Compos. Part B Eng.* **2018**, *149*, 240.
- [11] G. A. M. Falcão, T. G. Almeida, M. A. G. Bardi, L. H. Carvalho, E. L. Canedo, *Polym. Bull.* **2019**, *76*, 291.
- [12] N. E. Marcovich, M. M. Reboredo, M. I. Aranguren, *Thermochim. Acta* **2001**, *372*, 45.
- [13] M. W. Lee, S. O. Han, Y. B. Seo, *Compos. Sci. Technol.* **2008**, *68*, 1266.
- [14] M. S. Huda, A. K. Mohanty, L. T. Drzal, E. Schut, M. Misra, *J. Mater. Sci.* **2005**, *40*, 4221.