POLITECNICO DI TORINO Repository ISTITUZIONALE

The link between s and d components of electron boson coupling constants in one band d wave Eliashberg theory for high Tc superconductors

Original

The link between s and d components of electron boson coupling constants in one band d wave Eliashberg theory for high Tc superconductors / Ummarino, G. A.. - In: ANNALS OF MATHEMATICS AND PHYSICS. - ISSN 2689-7636. - 6:1(2023), pp. 048-051. [10.17352/amp.000077]

Availability: This version is available at: 11583/2977971 since: 2023-04-16T14:08:48Z

Publisher: Peertechz Publications

Published DOI:10.17352/amp.000077

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

Peertechz



Mathematics and Physics O SOUNAGCESS

ISSN: 2689-7636

Research Article

The link between *s* and *d* components of electron boson coupling constants in one band *d* wave Eliashberg theory for high *T_c* superconductors

GA Ummarino^{1,2*}

¹Institute of Engineering and Physics of Materials, Department of Applied Science and Technology, Polytechnic University of Turin, Corso Duca degli Abruzzi 24, 10129 Turin, Italy

²National Research Nuclear University MEPhI (Moscow Engineering Physics Institute), Kashira Hwy 31, Moskva 115409, Russia Received: 08 March, 2023 Accepted: 06 April, 2023 Published: 07 April, 2023

*Corresponding author: GA Ummarino, Institute of Engineering and Physics of Materials, Department of Applied Science and Technology, Polytechnic University of Turin, Corso Duca degli Abruzzi 24, 10129 Turin, Italy, E-mail: giovanni.ummarino@polito.it

Copyright License: © 2023 Ummarino GA. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

https://www.peertechzpublications.com

() Check for updates

Abstract

The phenomenology of overdoped high T_c uperconductors can be described by a one band *d* wave Eliashberg theory where the mechanism of superconducting coupling is mediated by antiferromagnetic spin fluctuations and whose characteristic energy Ω_0 scales with T_c according to the empirical law $\Omega_0 = 5.8 k_B T_c$. This model presents universal characteristics that are independent of the critical temperature such as the link between the *s* and *d* components of electron boson coupling constants and the invariance of the ratio $2\Delta/k_B T_c$. This situation arises from the particular structure of Eliashberg's equations which, despite being non-linear equations, present solutions with these simple properties.

Introduction

Eliashberg's theory [1] was born as a generalization of the BCS theory to explain some anomalies in the experimental data concerning lead. Subsequently, it was seen that the theory can be successfully applied to explain the experimental data of practically almost all superconducting materials [2,3], first of all low T_c phononic superconductors [4], then magnesium diboride [5,6], graphite intercalated compound CaC₆ [7], ironbased superconductors [8-12]. This theory can be applied to describe particular systems such as proximized systems [13] and field effect junctions [14-16]. For what concerns the high T_c superconductors [17–21], their properties strongly depend on their oxygen content. It is possible to identify three different regimes: under, optimal and overdoping. While the discussion is still open as regards the underdoping regime, it is almost certain that the fundamental mechanism in the optimal and over regime is due to antiferromagnetic spin fluctuations,

and especially in the over regime, the experimental data can be described satisfactorily by one band *d* - wave Eliashbeg's theory [22,23]. Detailed studies are present in the literature on cuprates and precisely on tunneling spectra that can be reproduced by using the framework of d - wave Eliashbeg's theory [24-26]. In this paper, we provide an extensive investigation of the consequences of a different symmetry of coupling in the two components of self-energy: the renormalization function $Z(i\omega_n)$ (s-wave symmetry) and the gap function $\Delta(i\omega_n)$ (d-wave symmetry) and if some link exists between them. We focus here on physical quantities which can be evaluated in the imaginary axis formalism. Furthermore, it has been experimentally determined that, in cuprates, a link [27] exists between magnetic resonance energy Ω_0 and critical temperature. So we will study the properties of one band *d*-wave Eliashbeg's theory where a fundamental role will be played by the assumption that the representative energy Ω_0 of these systems is related to the critical temperature by

048

Citation: Ummarino GA (2023) The link between *s* and *d* components of electron boson coupling constants in one band *d* wave Eliashberg theory for high T_c superconductors. Ann Math Phys 6(1): 048-051. DOI: https://dx.doi.org/10.17352/amp.000077

a universal relationship [27] $\Omega_0 = 5.8 k_B T_c$. This assumption represents a very strong constraint in correlating the values of the two-electron boson coupling constants λ_d and λ_s . For each value, λ_s we will look for the value λ_d which exactly reproduces the T_c superconductor and we will study which relation exists between the *d* and *s* components of the electron boson coupling constant. Finally, we will see that this model has the particular property that the relationship between the gap and the critical temperature ($\frac{2\Delta_d}{k_B T_c}$) is independent of the particular value of the critical temperature.

Model

The one-band d-wave Eliashberg equations [23,30–35] are two coupled equations: one for the gap $\Delta(i\omega_n, \phi)$ and one for the renormalization functions $Z(i\omega_n, \phi)$. These equations, in the imaginary axis representation (here ω_n denote the Matsubara frequencies), when the Migdal theorem holds [29], are:

$$\omega_n Z(\omega_n, \phi) = \omega_n + \pi T \sum_m [0^{2\pi} \frac{d\phi'}{2\pi} \Lambda(\omega_n, \omega_m, \phi, \phi') N_Z(\omega_m, \phi') \quad (1)$$

$$Z(\omega_n, \phi)\Delta(\omega_n, \phi) = \pi T \sum_m [0^{2\pi} \frac{d\phi'}{2\pi} [\Lambda(\omega_n, \omega_m, \phi, \phi') - \mu^*(\phi, \phi')] \times \\ \times \Theta(\omega_c - |\omega_m|) N_{\Delta}(\omega_m, \phi')$$
(2)

where $\Theta(\omega_c - \omega_m)$ is the Heaviside function, ω_c is cut-off energy and

$$\Lambda(\omega_n, \omega_m, \phi, \phi') = 2 \int_0^{+\infty} \Omega d\Omega \alpha^2 F(\Omega, \phi, \phi') / [(\omega_n - \omega_m)^2 + \Omega^2]$$
(3)

$$N_Z(\omega_m,\phi) = \frac{\omega_m}{\sqrt{\omega_m^2 + \Delta(\omega_m,\phi)^2}}$$
(4)

$$N_{\Delta}(\omega_m, \phi) = \frac{\Delta(\omega_m, \phi)}{\sqrt{\omega_m^2 + \Delta(\omega_m, \phi)^2}} \quad (5)$$

We assume [2,23,30-35] that the electron boson spectral function $\alpha^2(\Omega)F(\Omega,\phi,\phi')$ and the Coulomb pseudopotential $\mu^*(\phi,\phi')$ at the lowest order contain separated *s* and *d*-wave contributions,

$$\alpha^2 F(\Omega, \phi, \phi') = \lambda_s \alpha^2 F_s(\Omega) + \lambda_d \alpha^2 F_d(\Omega) \sqrt{2} \cos(2\phi) \sqrt{2} \cos(2\phi')$$
(6)

$$\mu^{*}(\phi,\phi') = \mu_{s}^{*} + \mu_{d}^{*}\sqrt{2}cos(2\phi)\sqrt{2}cos(2\phi')$$
(7)

as well as the self-energy functions:

$$Z(\omega_n, \phi) = Z_S(\omega_n) + Z_d(\omega_n)\cos(2\phi)$$
(8)

$$\Delta(\omega_n, \phi) = \Delta_s(\omega_n) + \Delta_d(\omega_n) \cos(2\phi) \tag{9}$$

We put the factor $\sqrt{2}$ inside the definition $\Delta_d(\omega_n)$ because, experimentally, the peak of the density of the state is, usually, identified $\Delta_d(\omega_{n=o})$ while, as we will see, $Z_d(\omega_n)$ is always zero. The spectral functions $\alpha^2 F_{s,d}(\Omega)$ are normalized in the way that $2j_0^{+\infty} \frac{\alpha^2 F_{s,d}(\Omega)}{\Omega} d\Omega = 1$ and of course, in this model the renormalization function is pure *s*-wave ($Z(\omega_n, \phi) = Z_s((\omega_n))$) while the gap function is pure *d*-wave ($\Delta(\omega_n, \phi) = \Delta_d(\omega_n)\cos(2\phi)$). We consider just solutions of the Eliashberg equations in pure https://www.peertechzpublications.com/journals/annals-of-mathematics-and-physics

d -waveform because this is the indication of the experimental data. This means that the s component of the gap function is zero and this situation happens because, usually [36], $\mu_s^* >> \mu_d^*$). In the more general case, in principle, the gap function has d and s components. The renormalization function $Z(\omega, \phi') = Z_s(\omega)$ has just the s component because the equation $Z_d(\omega_n)$ is a homogeneous integral equation with just the solution $Z_d(\omega_n) = 0$ [37]. For simplicity, we also assume that $\alpha^2 F_s(\Omega) = \alpha^2 F_d(\Omega)$ the spectral functions are the difference between two Lorentzian, i.e. $\alpha^2 F_{s,d}(\Omega) = C[L(\Omega + \Omega_0, \Upsilon) - L(\Omega - \Omega_0, \Upsilon)]$ where

$$L(\Omega \pm \Omega_0, \Upsilon)) = [(\Omega \pm \Omega_0)^2 + (\Upsilon)^2]^{-1}$$
, *C* is the normalization
constant necessary to obtain $2\int_0^\infty \frac{\alpha^2 F_{s,d}(\Omega)}{\Omega} d\Omega = 1$, o and γ are

the peak energy and half-width, respectively. The half-width is $=\Omega_0/2$. This choice of the shape of the spectral function and the fact that $\alpha^2 F_s(\Omega) = \alpha^2 F_d(\Omega)$, is a good approximation of the true spectral function [38] connected with antiferromagnetic spin fluctuations. The same thing also happens in the case of iron pnictides [39]. In any case, even making different choices for γ the link between λ_d and λ_s) remains the same but changes (very little) the coefficients of the linear fit. The cut-off energy is $\omega_c = 1000$ meV and the maximum quasiparticle energy is ω_{max} = 1100 meV. In the first approximation, we put $\mu_d^* = 0$ (if the s component of the gap is zero the value of μ_s^* is irrelevant). Now we fix the critical temperature and for any value, λ_s we seek the value λ_d that exactly reproduces the initial fixed critical temperature. After, via Padè approximants [40], we calculate the low-temperature value ($T = T_c/10$ K) of the gap because, in presence of a strong coupling interaction, the value $\Delta_d(\omega_{n-2})$ obtained by solving the imaginary-axis Eliashberg equations can be very different from the value Δ_d obtained from the realaxis Eliashberg equations [31].

Results and discussions

We fix three different critical temperatures (70 K, 90 K and 110 K) and for any particular critical temperature, we choose different values λ_s and determine which value λ_d exactly reproduces the chosen critical temperature by numerical solution of Eliashberg equations. In Figure 1 we can see that





Citation: Ummarino GA (2023) The link between s and d components of electron boson coupling constants in one band d wave Eliashberg theory for high T_c superconductors. Ann Math Phys 6(1): 048-051. DOI: https://dx.doi.org/10.17352/amp.000077

the three curves λ_d versus λ_s are coincident. The inset of Figure 1 it is shown the linear fit of these results. We obtain a linear link between λ_d and λ_s

$$\lambda_d = 0.616\lambda_s + 0.732\tag{10}$$

These results are general and do not depend on the particular shape of the electron-boson spectral function. If we change the shape of the electron-boson spectral function and we choose, for example, $\alpha^2 F_{s,d}(\Omega) = 0.5\Omega_0 \delta(\Omega - \Omega_0)$ we find that the linear link between λ_a and λ_s changes very little and becomes $\lambda_d = 0.575\lambda_s + 0.655$. Even the introduction of a Coulomb potential different from zero, as we have verified, does not involve a substantial modification of our results. In principle, it is possible to obtain this result (the linear link between λ_s and λ_d) in a more simple but less general way. In fact, a similar conclusion relative to the linear connection between λ_s and λ_d may also be derived from the analysis of the approximate MacMillan formula for T_c [41] generalized to *d*-wave case [42]:

$$k_B T_C = \Omega_0 exp(-\frac{1+\lambda_S}{2\lambda_d}) \tag{11}$$

The problem is that the MacMillan equation works just in a weak coupling regime. Now we solve, for each couple of λ_d and λ_s values, the Eliashberg equations at $T = T_c/10$ and after, via Pade we calculate the value of superconductive gap (the energy $2\Delta_d$

of the density of states peak). In Figure 2 the rates $\frac{2\Delta_d}{k_B T_c}$ are

shown for three systems with different critical temperatures (70 K, 90 K and 110 K). The curves are exactly coincidental. We have also studied what happens when the ratio $\frac{\Omega_0}{k_D T_c}$ is

equal to two as in the case of the heavy fermion [43] UPd_2Al_3 with $T_c = 2$ K which could represent an extreme situation. In this case, the link remains linear and becomes $\lambda_d = 0.880\lambda_s + 0.966$ as it is possible to see in the inset of Figure 2. Finally, in the case of extremely strong coupling ($\frac{\Omega_0}{k_BT_c} <<1$) it is possible to



Figure 2: (Color online) $|\Delta_{|}/k_{_{B}}T_{_{c}}$ for $T_{_{c}}$ = 70 K (green up filled triangles circles), $T_{_{c}}$ = 90 K (red filled circles) and $T_{_{c}}$ = 110 K (black filled squares) versus| $\lambda_{_{1}}$. The lines are guides for eyes. In the inset $|\lambda_{_{d}}|$ versus | $_{_{d}}|$ when $T_{_{c}}$ = 2 K and $\Omega_{_{0}}$ = 2 $k_{_{B}}T_{_{c}}$ is shown (black open circles) with the linear fit (solid red line).

demonstrate in an analytical way, following the calculus of ref

26, when $\frac{\lambda_s}{2\lambda_d} > 1$, that $\lambda_d \approx \lambda_s$ i.e. the link remains linear.

Conclusion

In this article, it has been shown that one band d -wave Eliashbeg's theory presents universal aspects as the linear link between λ_d and λ_s or the values $2\Delta_d / k_B T_c$ that are independent of the particular critical temperature. These universal aspects are related to the assumption that the typical bosonic energy is correlated to the critical temperature as shown by experimental data ($\Omega_0 = 5.8 k_B T_c$). We here proved that in a fully numerical solution of the Eliashberg equation, such linear links hold with great accuracy. A generalization and development of our results can be obtained by explicitly considering the momentum dependence of the self-energy without average on the Fermi surface as was done by Kamila A. Szewczyk, et al. [44]. Obviously, we would include in the calculations, unlike them, as we have done now, the link, observed experimentally, between the critical temperature and the representative energy of the bosonic spectrum.

Acknowledgment

The author acknowledges support from the MEPhI Academic Excellence Project (Contract No. 02.a03.21.0005).

References

- 1. Eliashberg GM. Sov Phys. JETP. 1963; 3:696.
- Ummarino GA. Eliashberg Theory. In: Emergent Phenomena in Correlated Matter, edited by E. Pavarini, E. Koch, and U. Schollwöck, Forschungszentrum Jülich GmbH and Institute for Advanced Simulations. 2013; 13.
- Marsiglio F. Eliashberg theory: A short review. Annals of Physics. 2020; 417: 168102.
- Carbotte JP. Properties of boson-exchange superconductors. Rev Mod Phys. 1990; 62: 1027.
- Daghero D, Gonnelli RS, Ummarino GA, Kazakov SM, Karpinski J, Stepanov VA, Jun J. Point-contact spectroscopy in MgB2 single crystals in magnetic field. Physica C Superconductivity. 2003; 385: 255-263.
- Daghero D, Calzolari A, Ummarino GA, Tortello M, Gonnelli RS, Stepanov VA, Tarantini C, Manfrinetti P, Lehmann E. Point-contact spectroscopy in neutronirradiated Mg¹¹ B₂. Phys Rev B. 2006; 74: 174519.
- Sanna A, Pittalis S, Dewhurst JK, Monni M, Sharma S, Ummarino G, Massidda S, Gross EKU. Phononic self-energy effects and superconductivity in CaC₆. Phys Rev B. 2012; 85: 184514.
- Torsello D, Ummarino GA, Gozzelino L, Tamegai T, Ghigo G. Comprehensive Eliashberg analysis of microwave conductivity and penetration depth of K-, Co-, and P-substituted BaFe₂ As₂. Phys Rev B. 2019; 99: 134518.
- Torsello D, Ummarino GA, Bekaert J, Gozzelino L, Gerbaldo R, Tanatar MA, Canfield PC, Prozorov R, Ghigo G. Tuning the Intrinsic Anisotropy with Disorder in the CaKFe₄As₄Superconductor. Phys Rev Appl. 2020; 13: 064046.
- Ghigo G, Ummarino GA, L. Gozzelino, and T. Tamegai. Phys. Rev. B 96, 014501 (2017).
- Torsello D, Cho K, Joshi KR, Ghimire S, Ummarino GA, Nusran NM, Tanatar MA, Meier WR, Xu M, Budko SL, Canfield PC, Ghigo G, Prozorov R. Tuning the Intrinsic Anisotropy with Disorder in the CaKFe₄As₄ Superconductor. Phys Rev B . 2019;100: 094513.

050

Citation: Ummarino GA (2023) The link between s and d components of electron boson coupling constants in one band d wave Eliashberg theory for high T_c superconductors. Ann Math Phys 6(1): 048-051. DOI: https://dx.doi.org/10.17352/amp.000077

- 12. Ummarino GA. Mathematical and Physical Properties of Three-Band s± Eliashberg Theory for Iron Pnictides. Magnetochemistry. 2023;9: 28.
- Ummarino GA. Superconductive critical temperature of Pb/Ag heterostructures. Physica C. 2020; 568:1353566.
- Ummarino GA, Piatti E, Daghero D, Gonnelli RS, Sklyadneva YI, Chulkov EV, Heid R. Proximity Eliashberg theory of electrostatic field-effect doping in superconducting films. Physical Review B. 2017; 96: 064509.
- Ummarino GA, Romanin D. Theoretical Explanation of Electric Field-Induced Superconductive Critical Temperature Shifts in Indium Thin Films. Phys Status Solidi B. 2020; 2020;1900651.
- Ummarino GA, Romanin D. Proximity two bands Eliashberg theory of electrostatic field-effect doping in a superconducting film of MgB2. J Phys. Condens Matter. 2019; 31: 024001.
- Gonnelli RS, A. Calzolari, D. Daghero, L. Natale, G.A. Ummarino, V.A. Stepanov, M. Ferretti, European Physical Journal B. 2001; 22: 41.
- Alikhanzadeh-Arani S, Salavati-Niasari M, Almasi-Kashi M. Influence of the utilized precursors on the morphology and properties of YBa2Cu307-y superconducting nanostructures. Physica C Superconductivity. 2013; 488: 30.
- Alikhanzadeh-Arani S, Salavati-Niasari M, Almasi-Kashi M. Growth of the Dysprosium–Barium–Copper Oxide Superconductor Nanoclusters in Biopolymer Gels. Journal of Inorganic and Organometallic Polymers and Materials. 2012; 22: 1081..
- Alikhanzadeh-Arani S, Kargar M, Salavati-Niasari M. Biopolymer-protected GdBa2Cu307-x nanoparticles: Morphology, structure and superconducting properties. Journal of Alloys and Compounds. 2014; 614: 35.
- Kargar M, Alikhanzadeh-Arani S, Pezeshki-Nejad Z, Salavati-Niasari M. Improvement of the Superconducting Properties of Ho123 Nanoparticles via a Polymer Mediated Sol-Gel Method. Journal of Superconductivity and Novel Magnetism. 2015; 28: 13.
- Ummarino GA. Standard Behaviour of Bi₂Sr₂CaCu₂O₈₊₆ Overdoped. Condens Matter. 2021; 6: 13.
- Rieck CT, Fay D, Tewordt L. Energy gap, T_c and density of states in hightemperature superconductors for retarded s- and d-wave interactions. Phys Rev B. 1989; 41: 7289.
- Jiang C, Carbotte JP, Dynes RC. Boson structure in the quasiparticle density of states of superconductors with nodes in the gap. Phys Rev B. 1993; 47: 5325.
- Zasadzinski JF, Coffey L, Romano P, Yusof Z. Tunneling spectroscopy of Bi₂Sr₂CaCu₂O₈₊₆: Eliashberg analysis of the spectral dip feature. Phys Rev B. 2003; 68: 180504(R).
- Ahmadi O, Coffey L, Zasadzinski JF, Miyakawa N, Ozyuzer L. Eliashberg Analysis of Tunneling Experiments: Support for the Pairing Glue Hypothesis in Cuprate Superconductors. Phys Rev Lett. 2011; 106: 167005.
- Yu G, Li Y, Motoyama EM, Greven M. A universal relationship between magnetic resonance and superconducting gap in unconventional superconductors. Nature Physics. 2009; 5: 873.
- Ghigo G, Ummarino GA, Gozzelino L, Gerbaldo R, Laviano F, Torsello D, Tamegai T. Effects of disorder induced by heavy-ion irradiation on (Ba₁- K_x)Fe₂As₂ single crystals, within the three-band Eliashberg s± wave model. Sci Rep 2017; 7: 13029.
- Ummarino GA, Gonnelli RS. Breakdown of Migdal's theorem and intensity of electron-phonon coupling in high-Tc superconductors. Phys Rev B. 1997; 56: 14279.
- Ummarino GA, Gonnelli RS. Real-axis direct solution of the d-wave Eliashberg equations and the tunneling density of states in optimally doped Bi₂Sr₂CaCu₂O_{8+x}. Physica C Superconductivity. 1999; 328: 189.
- 31. Ummarino GA, Gonnelli RS. Two-band Eliashberg equations and the experimental T_e of the diboride $Mg_{1-x}Al_xB_2$. Physica C Superconductivity. 2000; 295: 341-348.

- Ummarino GA, Gonnelli RS, Daghero D. Tunneling conductance of SIN junctions with different gap symmetries and non-magnetic impurities by direct solution of real-axis Eliashberg equations. Physica C Superconductivity. 2002; 377: 292.
- Cappelluti E, Ummarino GA. Strong-coupling properties of unbalanced Eliashberg superconductors. Phys Rev B. 2007; 76: 104522.
- Jutier F, Ummarino GA, Griveau JC, Wastin F, Colineau E, Rebizant J, Magnani N, Caciuffo R. Possible mechanism of superconductivity in PuCoGa_s probed by self-irradiation damage. Phys Rev B. 2008; 77: 024521.
- Ummarino GA, Caciuffo R, Chudo H, Kambe S. Energy scale of the electronboson spectral function and superconductivity in NpPd₅Al₂. Phys Rev B. 2010; 82: 104510.
- 36. Varelogiannis G. Solid State Communications. 1998; 107: 427.
- Musaelian KA, Betouras J, Chubukov AV, Joynt R. Mixed-symmetry superconductivity in two-dimensional Fermi liquids. Phys Rev B. 1996; 53: 3598.
- Bok JM, Bae JJ, Choi HY, Varma CM, Zhang W, He J, Zhang Y, Yu L, Zhou XJ. Quantitative determination of pairing interactions for high-temperature superconductivity in cuprates. Sci Adv. 2016; 2: 1501329.
- Ummarino GA. Multiband s± Eliashberg theory and temperature-dependent spin-resonance energy in iron pnictide superconductors. Phys Rev B. 2011; 83: 092508.
- Vidberg H, Serene J. Solving the Eliashberg equations by means of N-point Padé approximants. J Low Temp Phys. 1977; 29: 179.
- McMillan WL. Transition Temperature of Strong-Coupled Superconductors. Phys Rev. 1968; 167: 331.
- Hwang J, Schachinger E, Carbotte JP, Gao F, Tanner DB, Timusk T. Bosonic Spectral Density of Epitaxial Thin-Film La_{1.83}Sr_{0.17}CuO₄ Superconductors from Infrared Conductivity Measurements. Phys Rev Lett. 2008; 100:137005.
- Sato NK, Aso N, Miyake K, Shiina R, Thalmeier P, Varelogiannis G, Geibel C, Steglich F, Fulde P, Komatsubara T. Strong coupling between local moments and superconducting 'heavy' electrons in UPd₂Al₃. Nature. 2001; 410: 340.
- Szewczyk KA, Szczesniak R, Szczesniak D. Annalen der Physik. 2018; 530: 1800139.

Discover a bigger Impact and Visibility of your article publication with Peertechz Publications

Highlights

- Signatory publisher of ORCID
- Signatory Publisher of DORA (San Francisco Declaration on Research Assessment)
- Articles archived in worlds' renowned service providers such as Portico, CNKI, AGRIS, TDNet, Base (Bielefeld University Library), CrossRef, Scilit, J-Gate etc.
- Survey of the second se
- OAI-PMH (Open Archives Initiative Protocol for Metadata Harvesting)
- Dedicated Editorial Board for every journal
- Accurate and rapid peer-review process
- Increased citations of published articles through promotions
- Reduced timeline for article publication

Submit your articles and experience a new surge in publication services (https://www.peertechz.com/submission).

Peertechz journals wishes everlasting success in your every endeavours.

051

Citation: Ummarino GA (2023) The link between s and d components of electron boson coupling constants in one band d wave Eliashberg theory for high T_c superconductors. Ann Math Phys 6(1): 048-051. DOI: https://dx.doi.org/10.17352/amp.000077