POLITECNICO DI TORINO Repository ISTITUZIONALE

Multiphysics Simulation of a Superconducting Neutron Detector

Original

Multiphysics Simulation of a Superconducting Neutron Detector / Sparacio, Simone; Celentano, Giuseppe; Pietropaolo, Antonino; Torsello, Daniele; Laviano, Francesco. - In: IEEE TRANSACTIONS ON APPLIED SUPERCONDUCTIVITY. - ISSN 1051-8223. - (2024), pp. 1-6. [10.1109/tasc.2024.3504844]

Availability: This version is available at: 11583/2995266 since: 2024-12-12T15:17:53Z

Publisher: Institute of Electrical and Electronics Engineers

Published DOI:10.1109/tasc.2024.3504844

Terms of use:

This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

IEEE TRANSACTIONS ON APPLIED SUPERCONDUCTIVITY, VOL. X, NO. Y, DATE

Multiphysics Simulation of a Superconducting Neutron Detector

Simone Sparacio, Giuseppe Celentano, Antonino Pietropaolo, Daniele Torsello, Francesco Laviano

Abstract-The detection of neutrons is crucial for both the operation of nuclear devices and the development of advanced imaging techniques. Recently, a hybrid superconducting niobiumboron sensor on a Si/SiO₂ substrate has been developed, aiming for high pulse shape discrimination and controllability of the relaxation time. This device detects thermal neutrons by leveraging the ${}^{10}B(n,\alpha)^7Li$ reaction in the B layer and the interaction of the charged products with the Nb strip. To critically assess the operation of the Nb-B thermal neutron detector, a multiphysics modeling approach is presented here. The software COMSOL Multiphysics[®] is used to provide thermal and electrical responses of this device during the transition-to-normal state and its recovery phase. The study takes into account the impact of the thermal irradiation of the cryostat lid and the joule heating on the operating conditions of the Nb strip. Moreover, a pulsed heat load is introduced in the model to simulate the energy released by either the α or the Li reaction products in the current-biased Nb strip. The SRIM software is used to obtain the deposited power density profiles and their mean volume of interaction within the sample. For simplicity, the reaction is assumed to take place at the half-thickness of the B layer and the particles propagate perpendicularly to the sample surface. Finally, an iterative procedure was applied to find the most favorable conditions to employ the device in a self-recovering mode by varying both the bias current and the cold finger temperature. This study presents a comprehensive understanding of the working mechanism of the Nb-B thermal neutron detector and proposes a computational approach to find the optimal working point of superconducting neutron detectors.

Index Terms—multiphysics simulation, FEM, neutron detector, superconducting sensor, niobium strip.

I. INTRODUCTION

N EUTRON detection technology has been actively developed for almost a century (a comprehensive review can be found in [1]), and superconducting neutron detectors were introduced in 1977 by A. K. Drukier et al., who suggested to use a superheated superconducting colloid (SSC) [2]. This consisted of sedimented spherical grains of indium on a parafine wax, loaded with a natural boron compound, B_4C . Although different superconducting detector configurations (such as Superconducting Tunneling Junctions (STJ), Transition-Edge Sensors/Bolometers (TES/TEB), and Kinetic Inductance Detectors (KID) have been developed in the meantime for photons and charged particle detection, the SSC (see also [3], [4]) was the only one used for neutrons until 2003. In

G. Celentano is with the Superconductivity Laboratory, ENEA, Frascati, Rome, Italy.

A. Pietropaolo is with the Nuclear Technologies Laboratory, ENEA, Frascati, Rome, Italy. the same year, K. Takahashi et al. designed the first neutron TES prototype using the novel MgB₂ superconductor on a sapphire substrate [5]. A meander line layout was proposed with a DC voltage bias and considering the nuclear reaction ${}^{10}B(n,\alpha)^7Li$ directly in the MgB₂. In addition, M. Machida et al. [6] performed a numerical simulation, based on the time-dependent Ginzburg-Landau equation coupled with the Maxwell and heat diffusion equations, on a current-biased MgB₂ film. They found a threshold width of about 40ξ (T = 0) above which the neutral particle could not be detected since the normal region did not spread enough to break the wire electromagnetic symmetry. Between 2007 and 2012, T. Ishida et al. and M. Machida et al. performed, respectively, experimental [7]-[9] and numerical [10]-[13] evaluations on the thermal response and on the charged density profile of a microfabricated MgB₂ meander line on Si/SiN/SiO substrate and with different electrodes (i.e., Al and Nb). They claimed the ability of this device to count events at a rate much faster than 10^6 events/s due to its very fast dynamics (t<1 μ s). Moreover, they investigated the spatial dependence of the signal amplitude across the strip line and found a carrier imbalance due to a spin imbalanced superconductor confinement. An extensive research on TES for thermal neutron detection was also performed in the period 2015-2018 by V. Merlo et al. [14]-[17]. Their experimental progresses were first centered on a current-biased Nb superconducting strip and then on a NbN one on a silicon buffer and coated by a boron layer. The steep dR/dT curve of these materials near the critical temperature, T_c , lead to a readable superconducting-to-normal transition even with a small temperature increment. H. Shishido and coworkers, presented a similar device (i.e., a Nb-based meander line of 64 strips of 1 μ m-width and 40 nm-thick) using a current biased kinetic inductance (CB-KID) approach which allowed a wider I-T region operation preserving the high-speed detection. In [18]-[34] they demonstrated its operability with a detection range of tens of ns. This resulted in the identification of single neutrons but also time-dependent particle fluxes, their impact position, and the temperature dependence of the signal. The last developments on superconducting neutron detection schemes came from M. Brock et al., which in 2023 presented the first high-temperature CB-TES based on $YBa_2Cu_3O_{7-x}$ meander line, deposited on a metallic substrate and covered by 4 μ m thick B₄C [35]-[36]. Despite their shorter and heterogeneous historical development, superconducting neutron detectors offer high time resolution, exceptional spatial resolution, high efficiency for thermal neutrons, and high rate capability, with respect to other neutron detectors. A quick overview of the capability ranges of the different architectures

1

S. Sparacio, D. Torsello, F. Laviano are with the Department of Applied Science and Technology, Politecnico di Torino, and INFN - Sez. Torino, Torino, Italy (e-mail: simone.sparacio@polito.it).

IEEE TRANSACTIONS ON APPLIED SUPERCONDUCTIVITY, VOL. X, NO. Y, DATE

Architecture	Time resol. [µs]	Spatial resol. [µm]	Efficiency	Rate capab. [MHz]	Ref.
Gas-filled Detectors (e.g., ³ He, and ¹⁰ B tubes)	1	$1-10^{3}$	Moderate-high for thermal neutron Very low for fast neutron	10^{-3}	[37]–[39]
Scintillator Detectors (e.g., ZnS/ ⁶ Li with LiF, Li-glass, and plastic scintil.)	10^{-3}	10 ³	High for thermal neutrons Moderate for fast neutron	1	[40]–[41]
Solid-State Detectors (e.g., Silicon, ¹⁰ B, or ⁶ Li thin-film detectors)	$10^{-6} - 10^{-3}$	10 ³	Low-moderate for both thermal and fast neutrons	1	[42]–[43]
Proportional Counters and Multi-wire Proportional Chambers (MWPCs)	1	10 ³	Moderate-high for thermal neutrons Low for fast neutron	10^{-3}	[44]
Semiconductor-based Detectors (e.g., Diamond detectors)	10^{-3}	10 ³	Low for thermal neutrons Moderate for fast neutron	1	[45]–[46]
Neutron-sensitive CCD/CMOS-based detectors	1-10 ³	1	Low-moderate for thermal neutrons Very low for fast neutron	10^{-6}	[47]
Superconducting Neutron Detectors (STJs, SNSPDs)	$10^{-6} - 10^{-3}$	$10^{-3}-1$	High for thermal neutrons Moderate-high for fast neutron	1	[48]

TABLE I

COMPARISON OF NEUTRON DETECTOR ARCHITECTURES.

is reported in TABLE I.

In this research, starting from the experimental apparatus described in [14], we present a 3D multiphysics simulation of the sensor and its operating environment, devoting our attention on the effective operating temperature following the surface-to-surface radiation with the 80 K cryostat thermalscreen walls and the Joule heating produced by the resistive transport current during operation. We then studied the spatial and the temporal evolution of the device temperature, the electric field, and the current density distribution during the particle detection, validating the model with the experimental results and estimating the relative figure of merits. Finally, based on this validated setup, we found an experimentally feasible combination of bias current and operation temperature that allows the self-recovery of the superconducting state after neutron detection without the need to shunt the device or to externally interrupt the bias current.

II. EXPERIMENTAL SETUP AND CONSIDERATIONS

The detector was created using lift-off techniques, depositing a 150 nm thick layer of Nb on a 1×1 cm² silicon wafer with a 1 μ m thick SiO₂ surface layer. On top of the patterned Nb strip, 450 nm of natural boron was deposited using ebeam evaporation. In the boron layer, the absorption reaction produces a 1.5 MeV alpha particle and a 0.8 MeV lithium particle with opposite momenta. This means that either the alpha or the lithium particle will strike the microstrip for each neutron conversion. The sample was mounted at the end of an actively cooled cryostat using ⁴He, and the V-I and Vt measurements were performed on the INES beam-line at the ISIS pulsed neutron source in the Rutherford-Appleton Laboratory in the UK. A photograph of the experimental scheme is reported in the left panel of Fig. 1 while the top part of Fig. 2 shows the V-t measurement for a sample with a



Fig. 1. Left panel: photograph of the sample - from the top: boron (dark blue), niobium (light blue), Si/SiO_2 substrate (blue) - sample holder, and cold finger. Right panel: frontal and top schematic view of the cryostat head, with the cold finger end, the screws, the sample holder, and the detail of the sample.

width of 10 μ m and a length of 600 μ m, biased with a current of 4.5 mA, at the operating temperature of 8.12 K.

The interaction of the reaction products with the device materials heats a section of the wire (approximately a cylinder with radius equal to the mean particle lateral deviation in Nb) to above the superconducting transition temperature. The bias current avoids the normal region, increasing its density in the remaining width of the wire, and eventually triggering a quench. As the joule heating spreads across the wire, the temperature increment due to the steep transition, dR/dT, is converted to a larger, local, increase in the resistance of the superconductor. This change of resistance can then be measured by intercepting the voltage across the wire length, as a proof of particle detection.

III. NUMERICAL MODELING

A detailed 3D electro-thermal model of the cryogenic head is implemented on COMSOL Multiphysics®[49]. In Fig. 1 the frontal and the top view of the simulated domain is reported. Because of the high aspect ratio between the sample and the other components, a *layered shell approximation* is adopted for the sample in both the thermal end the electrical analysis. The coupling term between the two physics are the joule heating and the temperature dependent properties.

A. Thermal Model

The temperature profile is solved both in time and space by means of the classical Fourier equation, as reported in (1). The analysis considers both the energy contribution of the particle collision and the Joule losses, and particular attention is also devoted to the effects of the surface-to-surface radiation between the cryostat thermal shield at 80 K and the internal surfaces.

$$\rho C_p \frac{\partial T}{\partial t} + \nabla_t \cdot \left(-k \left(\nabla_t T + \nabla_n T\right)\right) = Q \qquad (1)$$
$$Q = Q_p + Q_J + Q_{irr}$$

Here, ρ , C_p , k are, respectively, the density, the specif heat, and the thermal conductivity of each material. ∇_t and ∇_n are the tangential and the normal component of the spatial derivative in the thin shell approximation. Q is the sum of the heat released by the traversing charged particle, Q_p , the electromagnetic heating, $Q_J = E \cdot J$, and the thermal irradiation, $Q_{irr} = \epsilon \sigma (T_{ref}^4 - T^4) \cdot A/V$, from the surrounding surfaces. In the latter, ϵ is the material thermal emissivity, $\sigma = 5.67 \times 10^{-8} [Js^{-1}m^2K^4]$ is the Stefan-Boltzmann constant, $T_{ref} = 80K$ is the considered cryostat thermal shield temperature, and A/V is the surface-to-volume ratio of the object.

The heat deposited by the charged particle has the characteristic profile along the path showing the Bragg peak near the implantation region. The profiles for the α and ⁷Li particles used in this simulation were evaluated by using the SRIM software [50]. The cold finger interface facing the helium flow is fixed at the operating temperature, while the initial temperature accounts also for the contribution of Q_J and Q_{irr} prior to the particle impact.

B. Electric Model

The electrical analysis takes into account current conservation based on the Ohm's law (i.e., neglecting the inductive effects), and implements an experimental resistivity, $\rho(T)$. Based on these assumptions, a known current source is injected into the Nb bridge by using two terminals, and the voltage drop is evaluated over the distance L between the voltage taps.

$$\nabla_t \cdot d\left(\frac{1}{\rho}\nabla_t V - \mathbf{J}_\mathbf{e}\right) = dQ_J \tag{2}$$

In (2), d is the shell thickness, ρ is the electrical resistivity, V is the scalar potential - which tangential gradient defines the electric field **E** along the shell -, and $\mathbf{J}_{\mathbf{e}}$ and Q_J stands for the externally generated current density in the conducting material and the external current source, respectively.



Fig. 2. Upper panel: experimental V-t measurements an biased current. Lower panel: simulated V-t data (blue), biased current (red), and average temperature of the Nb microstrip between the voltage contacts (black).

IV. MODEL VALIDATION

A first comprehensive analysis is intended to compare the model and the experimental results. Fig. 2 shows the time evolution of V for a sample with w = 10 μ m and L = 600 μ m. In both experiments and simulations the cold finger temperature was kept at T = 8.12 K and the sample biased with a current I = 4.5 mA. The absence of a current diverting resistance, together with the chosen operating condition, induces the Joule self-heating of the resistive domain to expand over the whole strip length and produce a positive electro-thermal feedback (ETF). Indeed, both the measured (upper panel of Fig. 2) and

IEEE TRANSACTIONS ON APPLIED SUPERCONDUCTIVITY, VOL. X, NO. Y, DATE

the simulated (lower panel of Fig. 2) voltage signals revealed a latching state of about 150 mV until the current is switchedoff. Also the time delay covered by the boundaries of the initial resistive region to propagate to the ends of the film - which is of the order of tens of μ s in the present and described by the t_{onset} of the voltage drop in the lower panel of Fig. 2 depends on the electro-thermal cycle of the system (including the thermal contact resistances). To better support this, the trace of the quench dynamics in terms of the imparted energy and its tight interconnection with the electric field profile is plotted in Fig. 3.



Fig. 3. Time evolution of the maximum local thermal energy in the Nb layer (up) and, for the same times, the electric field distribution (down) across the sample width.

The femtosecond particle interaction time-scale cannot be directly described with reference to the equilibrium temperature unless considering more sophisticated models [51]; conversely, the energetic description provides a clear qualitative understanding on the superconductivity depression. Fig. 3 is related to the interaction with ⁷Li, which has an average timeof-flight (tave in the figure) of about 0.56 ps. A ns-range is required for the imparted energy to spread apart over the entire sample width and break the electric field symmetry. In the same time the electronic bath is thermalized with the sublattice ($\tau_{e-p} \sim 330$ ps) and the mean temperature starts increasing together with the electrical resistivity, while the normal zone expands along the Nb length. Fig. 2 highlights the average temperature of the superconducting volume between the voltage contacts. The chosen bias current makes the thermal sink ineffective and brings the temperature far above the material critical temperature.

V. SELF-RECOVERING OPTION

In order to design a continuously working particle counting device, the simplest approach is to modify the operating conditions to reverse the electro-thermal feedback and allow self recovery. In other words, one can choose the conditions that modify the device timescales in such a way that either the Joule self-heating is reduced or the extracted power per unit input power is increased. Since both the bias current and the cold finger temperature also affect the figures of merit of the apparatus, the simplest approach is to find an experimentally feasible condition which allows self recovery while preserving as much as possible its responsivity (r) [53] and noise-toequivalent power (NEP) [54].



Fig. 4. Responsivity (up) and NEP (down on log scale) profiles over a broad range of cold finger temepratures and bias currents.

The estimation of these over a broad range of values can be obtained from eq. (3) and eq. (4), respectively:

$$NEP = NEP_J + NEP_t$$

$$NEP_J = \frac{4\kappa_B TR}{r^2}$$

$$NEP_t = 4\kappa_B T^2 G$$
(4)

Here, I is the bias current, G is the substrate conductance, and $\frac{\partial R}{\partial T}$ is the electrical resistance curve slop as a function of temperature. NEP_J stands for the Johnson noise voltage, while NEP_t accounts for the noise power due to thermal fluctuation.

In Fig. 4 the calculated responsivity and NEP are presented as a function of the two operational variables. It is clear that, while the responsivity has a non-linear dependence on temperature and a linear response in current, the NEP has a less obvious behavior being also affected by the inverse squared of the responsivity itself. However, the strong effect caused by the temperature is mostly related to the dR/dT shape; indeed, the materials properties remain almost constant in the considered temperature range.



Fig. 5. Improved V-t simulation results for continuous particle detection.

As a result, reducing the transport current is more effective than reducing the cold finger temperature to reverse the electro-thermal feedback, and less impacting on the figure of merits. For instance, decreasing the current to a value of 3.6 mA, the responsivity is only slightly reduced to 1.9 mV· W⁻¹ (with respect the 2.3 mV· W⁻¹ in the original case) and the NEP slightly increased to 6.7×10^{-15} W· Hz^{-1/2} (with respect the 4.3×10^{-15} W· Hz^{-1/2} in the original case), while the particle-assisted vortex motion self-contracts on a μ s timescale, restoring superconductivity (see Fig. 5).

VI. CONCLUSION

The finite element modeling turned out to be a valuable tool to characterize and evaluate the performance of superconducting neutron detectors. The dynamic response to single particle radiation has been obtained by considering both time and spatial evolution of temperature and current. The model has been validated against experimental data, the figures of merit have been estimated, and the operating conditions improved finding a self-recovery configuration. Notwithstanding the limits of the classical approach - which requires a critical thinking on the properties definition on very short time-scales - the results of this analysis well agree with the experimental data and are comparable with other data present in literature. This allows to get a reliable description of the apparatus with a computationally effortless model.

VII. ACKNOWLEDGMENTS

This work is partially supported by the Ministry of Education, Universities and Research through the "Programma Operativo Nazionale (PON) Ricerca e Innovazione 2014–2020", by the Italian Ministry of Foreign Affairs and International Cooperation, grant number US23GR16, and by Eni S.p.A.

REFERENCES

5

- A. Pietropaolo et al., "Neutron detection techniques from µeV to GeV", in *Physics Reports*, 875, pp. 1-65, 2020.
- [2] A. K. Drukier et al., "A new detector of neutrons", in *Nuclrear Instru*ments and Methods, 154, pp. 91-94, 1978.
- [3] G. Meagher et al., "Neutron detection using a planar array of superheated superconductors" in *Nuclear Instruments and Methods in Physics Research A*, 230, pp. 8-10, 1996.
- [4] T. Ebisu et al., "Cryogenic detection of neutrons using superheated superconducting tin granules", in *Nuclear Instruments and Methods in Physics Research A*, 503, pp. 589-594, 2003.
 [5] K. Takahashi et al., "Design of neutron detector by using a novel
- [5] K. Takahashi et al., "Design of neutron detector by using a novel superconductor MgB₂", in Physica C, 392-396, pp. 1501-1503, 2003.
- [6] M. Machida et al., "Large-scale numerical simulations for superconducting neutron detector using MgB_2 and half quantized vortices in d-dot array", in *Annual Report of the Heart Simulator Center*, April 2023-March 2024.
- [7] T. Ishida et al., "Superconducting radiation detector by using a microfabricated MgB₂ meander line", in *Physica C*, 460-462, pp. 618-619, 2007.
- [8] T. Ishida et al., "Superconducting MgB₂ thin film detector for neutrons", in J Low Temp Phys, 151, pp. 1074-1079, 2008.
- [9] T. Ishida et al., "Position dependent response of superconducting MgB₂ neutron detectors studied by pulsed laser irradiation", in J Low Temp Phys, 167, pp. 447-454, 2012.
- [10] M. Nishikawa et al., "Numerical simulation for thermal relaxation of hot spot in MgB₂ neutron detector", in *Physica C*, 463-463, pp. 1115-1118, 2007.
- [11] M. Machida et al., "Direct numerical simulations for non equilibrium superconducting dynamics at the transition temperature edge: simulation for MgB₂ neutron detectors", in J Low Temp Phys, 151, pp. 58-63, 2008.
- [12] M. Machida et al., "Ultra-large scale simulations for superconductor MgB₂ device toward nuclear application and fundamental issues in nanostructured superconductors", in Annual Report of the Heart Simulator Center, April 2007-March 2008.
- [13] M. Machida et al., "Numerical experiments for heat diffusion and related non-equilibrium superconducting dynamics on MgB₂ neutron detector", in Nuclear Instruments and Methods in Physics A, 600, pp. 210-212, 2009.
- [14] V. Merlo et al., "Hybrid superconducting neutron detectors", in *Applied Physics Letters*, 106, 113502, 2015.
- [15] V. Merlo et al., "Superconducting thermal neutron detectors", in J. Phys.: Conf. Ser., 746, 012019, 2016.
- [16] V. Merlo et al., "Meta-material for nuclear particle detection", in J. Phys.: Conf. Ser., 50, 045601, 2017.
- [17] V. Merlo et al., "Superconducting Strips: A Concept in Thermal Neutron Detection", in *Instruments*, 2, 2010004, 2018.
- [18] H. Shishido et al., "Neutron detection using a current biased kinetic inductance detector", in *Appl. Phys. Lett.*, 107, 232601, 2015.
- [19] S. Miyajima et al., "Time-Dependent Flux from Pulsed Neutrons Revealed by Superconducting Nb Current-Biased Kinetic Inductance Detector with ¹⁰B Converter Operated at 4 K", in JPS Conf. Proc., 8, 051004, 2015.
- [20] Y. Narukami et al., "Signal from a Single Neutron by using Current-Biased Kinetic Inductance Detector made of Superconducting Nb Nanowire", in JPS Conf. Proc., 8, 051003, 2015.
- [21] H. Shishido et al., "Neutron detection using the superconducting Nbbased current-biased kinetic inductance detector", in *Supercond. Sci. Technol.*, 3, 094003, 2017.
- [22] H. Shishido et al., "High-Speed Neutron Imaging Using a Current-Biased Delay-Line Detector of Kinetic Inductance", in *PHYSICAL RE-VIEW APPLIED*, 10, 044044, 2018.
- [23] Y. Iizawa et al., "Physical characteristics of delay-line current-biased kinetic inductance detector", in *IOP Conf. Series: Journal of Physics: Conf. Series*, 1054, 012056, 2018.
- [24] Y. Miki et al., "Neutron signal features of Nb-based kinetic inductance detector with ¹⁰B convertor", in *IOP Conf. Series: Journal of Physics: Conf. Series*, 1054, 012054, 2018.
- [25] Y. Iizawa et al., "Energy-resolved neutron imaging with high spatial resolution using a superconducting delay-line kinetic inductance detector", in *Supercond. Sci. Technol.*, 32, 125009, 2019.
- [26] T. D. Vu et al., "Kinetic inductance neutron detector operated at near critical temperature", in J. Phys.: Conf. Ser., 1590, 012036, 2020.
- [27] H. Shishido et al., "Energy-Resolved Neutron Imaging using a Delay Line Current-Biased Kinetic-Inductance Detector", in J. Phys.: Conf. Ser., 1590, 012033, 2020.

- [28] T. Ishida et al., "Superconducting Neutron Detectors and Their Application to Imaging", in *IEICE TRANS. ELECTRON.*, VOL.E103–C, NO.5 MAY 2020.
- [29] T. D. Vu et al., "Homogeneity of neutron transmission imaging over a large sensitive area with a four-channel superconducting detector", in *Supercond. Sci. Technol.*, 34, 015010, 2021.
- [30] T. D. Vu et al., "Practical tests of neutron transmission imaging with a superconducting kinetic-inductance sensor", in *Nuclear Inst. and Methods* in *Physics Research A*, 1006, 165411, 2021.
- [31] H. Shishido et al., "High Spatial Resolution Neutron Transmission Imaging Using a Superconducting Two-Dimensional Detector", in *JOUR-NAL OF IEEE TRANSACTIONS OF APPLIED SUPERCONDUCTIVITY*, VOL. 31, NO. 9, 2021.
- [32] H. Shishido et al., "Neutron Imaging for Intermetallic Alloy using a Delay Line Current-Biased Kinetic-Inductance Detector", in J. Phys.: Conf. Ser., 1975, 012023, 2021.
- [33] T. D. Vu et al., "Narrow-area Bragg-edge transmission of ironsamples using superconducting neutron sensor", in J. Phys.: Conf. Ser., 2323 012028, 2022.
- [34] H. Shishido et al., "Neutron Imaging toward Epithermal Regime using a Delay Line Current-Biased Kinetic-Inductance Detector", in J. Phys.: Conf. Ser., 2323 012029, 2022.
- [35] M. Brock et al., "Superconducting transition edge bolometer for high-flux neutron detection", in *Scientific Reports on Nature Portfolio*, 13, 22266, 2023.
- [36] M. Brock et al., "Effective Thermal Properties of a HTS Transition Edge Bolometer for High-Flux Neutron Detection", in Adv. Electron. Mater., 10, 2300420, 2024.
- [37] K. Boretzky et al., "NeuLAND: The high-resolution neutron time-offlight spectrometer for R3B at FAIR" in *Nuclear Inst. and Methods in Physics Research, A* 1014 (2021) 165701653 ISSN 0020-4412.
- [38] S.V. Afanas'ev et al., "The Time Resolution of a Prototype Neutron Detector" in *Instruments and Experimental Techniques*, 2016, Vol. 59, No. 5, pp. 653–657.
- [39] A Tengattini et al., "Compact and versatile neutron imaging detector with sub-4 μ m spatial resolution based on a single-crystal thin-film scintillator" in *Optics Express*, Vol. 30, Issue 9, pp. 14461-14477 (2022).
- [40] G. Albani et al.,, "High-rate thermal neutron gaseous detector for use at neutron spallation sources", *Tesi di Dottorato* 2016-2017.
- [41] Cancelli, S., Caruggi, F., Perelli Cippo, E. et al., "Development of a multi-layer high-efficiency GEM-based neutron detector for spallation sources." in *Sci Rep* 14, 23954 (2024). https://doi.org/10.1038/s41598-024-74958-5
- [42] C Petrillo et al., "Solid state neutron detectors" in Nuclear Instruments and Methods in Physics Research Section A: Accelerators, Spectrometers, Detectors and Associated Equipment, Vol. 378, Issue 3, pp. 541-551 (1996).
- [43] K. Ahmed et al., "Solid-state neutron detectors based on thickness scalable hexagonal boron nitride" in *Appl. Phys. Lett.*, 110, 023503 (2017). https://doi.org/10.1063/1.4973927.
- [44] K Toh et al., "Performance evaluation of high-pressure MWPC with individual line readout under Cf-252 neutron irradiation" in J. Phys.: Conf. Ser. 528, 012045 (2014).
- [45] Angelone, M.; Verona, C. "Properties of Diamond-Based Neutron Detectors Operated in Harsh Environments." in J. Nucl. Eng. Vol. 2, pp. 422–470 (2021). https://doi.org/10.3390/jne2040032.
- [46] Youngseok Lee et al., "Diamond fast-neutron detector applied to the KSTAR tokamak" in *Fusion Engineering and Design*, Vol. 153, (2020), 111452.
- [47] Martín Pérez et al., "Thermal neutron detector based on COTS CMOS imagers and a conversion layer containing Gadolinium" in *Nuclear Inst.* and Methods in Physics Research, A, Vol. 893, pp. 157–163 (2018).
- [48] Vittorio Merlo, "Superconducting Strips: A Concept in Thermal Neutron Detection" in MDPI Journal Instruments.
- [49] COMSOL Multiphysics[®]. www.comsol.com. COMSOL AB, Stockholm, Sweden.
- [50] J. F. Ziegler, M. D. Ziegler, and J. P. Biersack, in Nuclear Instruments and Methods in Physics Research Section B: Beam Interactions with Materials and Atoms, 268, 1818.
- [51] J. Wenlei Yin et al., "Heat transfer in superconducting nanowire single-photon detectors: mechanism and modulation", in Sci. Technol.Supercond., 2024, in press https://doi.org/10.1088/1361-6668/ad54f2.
- [52] A. Napolitano et al., "Study of the thermal distribution for YBCO based Transition Edge Bolometers working above 77 K," in *IEEE 14th Workshop on Low Temperature Electronics (WOLTE)*, Matera, Italy, 2021, pp. 1-4, doi: 10.1109/WOLTE49037.2021.9555450.

- [53] M. K. Maul et al., "Equivalent Circuit of a Superconducting Bolometer," in *Journal of Applied Physics*, 40, 2822 (1969); doi: 10.1063/1.1658082.
- [54] J. C. Mather et al., "Bolometer noise: nonequilibrium theory," in *APPLIED OPTICS*, Vol. 21, No. 6 1982