

From Waste to Technological Products: Bioplastics Production from Proteins Extracted from the Black Soldier Fly

Original

From Waste to Technological Products: Bioplastics Production from Proteins Extracted from the Black Soldier Fly / Di Pasquale, A., Zoccola, M., Mohod, A., Dalla Fontana, G., Anceschi, A., Dalle Vacche, S.. - In: POLYMERS. - ISSN 2073-4360. - 17:11(2025). [10.3390/polym17111582]

Availability:

This version is available at: 11583/3008854 since: 2026-03-17T10:13:15Z

Publisher:

Multidisciplinary Digital Publishing Institute (MDPI)

Published

DOI:10.3390/polym17111582

Terms of use:



This article is made available under terms and conditions as specified in the corresponding bibliographic description in the repository

Publisher copyright

(Article begins on next page)

Article

From Waste to Technological Products: Bioplastics Production from Proteins Extracted from the Black Soldier Fly

Alessia Di Pasquale ¹, Marina Zoccola ^{2,*}, Ashish Mohod ², Giulia Dalla Fontana ², Anastasia Anceschi ²
and Sara Dalle Vacche ¹

¹ Department of Applied Science and Technology, Politecnico di Torino, Corso Duca degli Abruzzi 24, 10129 Torino, Italy; aledipa9@gmail.com (A.D.P.); sara.dallevacche@polito.it (S.D.V.)

² CNR-STIIMA, Italian National Research Council, Institute of Intelligent Industrial Technologies and Systems for Advanced Manufacturing, Corso G. Pella 16, 13900 Biella, Italy; ashish.mohod@cnr.it (A.M.); giulia.dallafontana@cnr.it (G.D.F.); anastasia.anceschi@stiima.cnr.it (A.A.)

* Correspondence: marina.zoccola@cnr.it

Abstract: The need to find sustainable solutions to conventional plastics has driven research into alternative materials, including bioplastics, which represent a promising option for reducing pollution and enhancing the value of renewable resources. In this study, bioplastics made from polyvinyl alcohol (PVA) and proteins extracted from the larvae of Black Soldier Fly (BSF), an insect capable of converting organic waste into high-value biomass, were produced and characterized. The proteins were obtained by hydrolysis of defatted BSF larvae with superheated water, avoiding harsh chemical reagents. Next, polymer films were fabricated by mixing PVA and hydrolyzed BSF proteins in different proportions and analyzed for morphological, physical-chemical, mechanical and biodegradability characteristics. The results obtained show that as the BSF protein content increases, the films show a reduction in thermal stability and mechanical properties, and also, they exhibit higher biodegradability, correlated with higher wettability, solubility and ability to absorb moisture. This research highlights the value of using organic waste-fed insects as a resource for bioplastic production, offering an alternative to traditional polymers and contributing to the transition to sustainable materials.



Academic Editor: Valentina Beghetto

Received: 29 April 2025

Revised: 28 May 2025

Accepted: 3 June 2025

Published: 5 June 2025

Citation: Di Pasquale, A.; Zoccola, M.; Mohod, A.; Dalla Fontana, G.; Anceschi, A.; Dalle Vacche, S. From Waste to Technological Products: Bioplastics Production from Proteins Extracted from the Black Soldier Fly. *Polymers* **2025**, *17*, 1582. <https://doi.org/10.3390/polym17111582>

Copyright: © 2025 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

Keywords: bioplastics; Black Soldier Fly; proteins; polyvinyl alcohol; biofactory; high-value products

1. Introduction

Hermetia illucens, also known as the Black Soldier Fly, is an insect of the order Diptera and the family Stratiomyidae. This species is native to South America, but is currently widespread on a cosmopolitan level, due to its ability to adapt to many different environments and food sources [1]. The life cycle of BSF consists of four main stages, with the first stage being eggs laid near decomposing organic material. The larvae then come out of the eggs and grow rapidly, accumulating body mass. When they reach maturity, they become first prepupae, where they stop feeding and their skin hardens, and immediately after pupae, where they undergo the metamorphosis into winged adults, which concentrate exclusively on reproduction [2]. BSF larvae have the potential to bioconvert a large variety of organic substrates in their body mass, and they can be used in waste management, requiring a relatively low amount of water, land and energy to be reared [3–5].

As insects are ‘farmed animals’ [6], the EU legislation does not allow us to feed them with organic waste [7]. However, to implement the circularity level of the EU insect sector

and help it to reach its full potential, the International Platform of Insects for Food and Feed [8] has identified as a key research priority the diversification of the allowed growing substrates. Moreover, around the world, such legislation does not apply and BSF larvae are a very valuable tool for waste management [9–13]. This process has several advantages compared to traditional organic waste treatment strategies. It could make a very meaningful contribution to meeting several of the UN Sustainable Development Goals (SDGs) for 2030 and thereafter.

The present work focused on extracting proteins from BSF larvae raised on food scraps and their use for technological purposes for bioplastic production.

The European Union generated 59.2 million tons of food waste in 2022, corresponding to around 132 kg per inhabitant [14]. The recycling of food waste to produce commercial products and energy is fast picking up in the scientific community as a sustainable option [15]. Food waste is characterized by a variable chemical composition depending on its origin of production, while feeding insects with food waste allows for concentrating the waste in their body mass, which can be biorefined, obtaining fat, protein and chitin [16].

After the grease extraction, proteins can be extracted from the insect body mass using strong bases, in particular NaOH, which is the most widespread and widely established method [17,18], or enzymes [1,19].

In this study, to extract proteins from BSF larvae, superheated water at a temperature of 160 °C corresponding to a pressure of 4.5 bar was used, which offers the advantages of being an environmentally sustainable process, not requiring complex and expensive purification steps, as well as sterilizing the material and ensuring a safe protein end product.

Superheated water is defined as liquid water under pressure at a temperature between 100 °C (boiling temperature at atmospheric pressure) and 374 °C (critical water temperature) [20]. As far as the protein is concerned, superheated water has been used to obtain keratins from wool and feathers [21,22] and to extract protein from insects to obtain natural dyes [23] or to remove proteins and isolate chitin from BSF exuviae [24].

In this study, the proteins extracted from BSF with superheated water were blended with PVA for bioplastic production to overcome the disadvantages of the protein's fragile structure and poor mechanical properties [25]. Other authors had already used the protein extracted from BSF prepupae to produce bioplastics in a mixture with glycerol [26] or glycerol as a plasticizer and citric acid as a cross-linking agent [27]. In our work, PVA was chosen because it is a hydrophilic polymer, water soluble, with a good film-forming ability [28] and compatible with proteins in film production [29,30]. Moreover, PVA shows high mechanical properties and good chemical resistance but poor thermal properties, although its properties depend largely on the molecular weight and degree of hydrolysis. PVA is not considered a biodegradable polymer in all environments, as its biodegradability depends on the microorganisms present, and environmental conditions of temperature, pH and humidity [31].

The bioplastic production from insect larvae feeding on food waste reduces dependence on polymers from fossil sources. The most widely used polymers are low-density polyethylene (LDPE), high-density polyethylene (HDPE), polyvinyl chloride, polystyrene and polypropylene and polyethylene terephthalate (PET). A major problem related to their high durability is the accumulation in soil and water [32]. In addition, the synthetic polymers are derived from non-renewable sources, particularly based on petroleum resources. Moreover, there are some problems related to their recycling; For example, fusion-based recycling to produce new polymeric material can lead to significant deterioration of the material obtained due to the presence of moisture content and residual catalysis in treated waste polymer [33].

Instead, biopolymers are characterized by their derivation from renewable resources or because they are biodegradable, which means they can degrade in natural environments or under specific industrial conditions [34,35]. In the case of insect proteins, both requirements are met.

Biodegradable polymers are transformed into water, carbon dioxide, methane or biomass through biological processes, making them particularly useful for applications such as single-use materials where end-of-life management is challenging [36]. Bioplastics may be produced synthetically as polylactic acid (PLA) or as natural biopolymers such as cellulose and its derivatives, starch, proteins or mixtures thereof [37]. The mechanical characteristics of biopolymers are widely variable from poly(glycolic acid) (PGA), which has a high tensile strength of 60 MPa, to starch, which has a tensile strength of 5 MPa. Often, tensile strength and elongation are inversely related, and generally, biopolymers have lower mechanical properties than synthetic polymers [38]. The biodegradability of bioplastics is difficult to quantify as it depends not only on the type of polymer but also on the additives used in its formulation, which increase the durability of the material. Additionally, of course, it depends on the characteristics of the environment in which biodegradability is tested [39]. The bioplastics produced in this study could find application as packaging materials or in agriculture, where traditional plastics, such as low-density polyethylene (LDPE), are widely used as mulching films. Although appreciated for their low cost and good mechanical and optical performance, during the degradation process, they reduce into fragments that have to be removed [40].

On the other hand, bioplastics from proteins are designed not only to degrade completely without leaving harmful residues but also to release carbon and organic nitrogen that fertilize the soil and support crop growth [26,41,42]. In this study, bioplastics were obtained from BSF larvae proteins extracted by a green method using only water under pressure and mixed with PVA in different proportions using water as a common solvent. The bioplastics were characterized via chemical (spectroscopy in the medium infrared—FTIR) thermal, mechanical, and morphological analyses, and parameters such as water solubility, moisture absorption, contact angle, and biodegradability in soil were measured, aiming to characterize the different films and direct them towards specific uses.

2. Materials and Methods

2.1. Materials

The proteins were extracted from BSF larvae reared at the experimental center of the Department of Zootechnical Sciences of the University of Turin in Carmagnola (Turin), in a climate chamber with controlled temperature and humidity (29 ± 0.5 °C, relative humidity $60 \pm 5\%$) and constant ventilation. PVA was supplied by the company F.lli Citterio S.p.A. (Monza-Italy—average m.w. 100,000) in filament form. Distilled water was prepared using the Millipore apparatus. Hexane, petroleum ether and hydrochloric acid were of analytical grade and were purchased from Merck (Milano—Italy).

2.2. Methods

2.2.1. BSF Larvae and PVA Preparation

BSF larvae at the last larval age were dried (see Figure 1), washed 3 times in deionized water, further dried at 55 °C for 24 h and finely ground in a blender.

The larval powder was then extracted in a Soxhlet apparatus for 4 h using hexane as a solvent to remove larval fat. From the defatted larvae, the proteins were extracted. The PVA yarn was extracted in a Soxhlet apparatus for 4 h using petroleum ether as a solvent to remove fats and finishing products.



Figure 1. Dried BSF larvae.

2.2.2. Protein Extraction from BSF Larvae and Their Characterization

Superheated water was used for protein extraction in a laboratory reactor (Amar Equipment, Mumbai, India, model number 1-T-A-CE), which had a capacity of 5 L and was equipped with a magnetically coupled stirrer driving a paddle turbine. Specifically, 50 g of ground and defatted BSF larvae were suspended in 1 L of distilled water, and hydrolysis was conducted for 1 h and under stirring at 400 rpm.

Three hydrolysis tests were carried out: the first at a temperature of 160 °C (pressure 4.5 bar), the second at the same temperature of 160 °C and it was preceded by pretreatment with HCl (2N) for 24 h at room temperature and material to liquor ratio of 1/10 in a conical flask under stirring of 130 shakes/min. After filtration on wire mesh, neutralization with ammonia and rinsing with tap water, the solid part was hydrolyzed in an autoclave. The third test was conducted on grounded and defatted BSF larvae at a temperature of 180 °C corresponding to a pressure of 10 bar.

Each hydrolysate was filtered on a wire mesh, and the protein-rich liquid was further centrifuged at 8000 rpm for 15 min to remove precipitated solid material.

To determine the protein concentration, 10 mL from each liquid extract was dried in an oven at 105 °C for 4 h, and the dry weight was measured.

By measuring the final volume of each extract, the extraction yield was calculated using the formula:

$$\text{Extraction yield (\%)} = \frac{W_f}{W_i} \times 100 \quad (1)$$

where:

w_f: dry weight of hydrolyzed proteins

w_i: dry weight of defatted BSF larvae before hydrolysis

2.2.3. Preparation of PVA/BSF Protein Blend Films

The protein hydrolysate from BSF larvae obtained from superheated hydrolysis at 160 °C for 1 h, having a protein concentration of 21 g/L, was placed in a flask in a thermostated bath at 65 °C for 1 h under stirring (130 shakes/min). PVA filament in water was treated under the same conditions and dissolved completely. The two solutions were mixed in the proportions PVA/BSF protein % *w/w* 100/0, 90/10, 70/30, 50/50, 30/70, 10/90 and 100/0 in a volume of 10 mL for each blend. The solutions at the different PVA/BSF protein concentrations were further mixed in a thermostatically controlled bath at 65 °C for 1 h under stirring (130 shaking/min) and then cast onto polyester plates and allowed to dry at room temperature for 48 h until complete water evaporation.

2.3. Characterization of PVA/BSF Protein Blend Films and BSF Protein Hydrolyzates FT-IR Spectroscopy

BSF larvae, liquid and solid fractions after hydrolysis, PVA/BSF protein films and PVA/BSF films after biodegradation in soil were characterized using FT-IR spectroscopy in ATR (Attenuated Total Reflectance) mode with a diamond crystal. The Thermo Nexus spectrometer (Nicolet) instrumentation was used, and the spectra were processed with Omnic 9 software. Spectra were acquired with 64 scans in the wavenumber range 4000–650 cm^{-1} with resolution 4 cm^{-1} and gain 8.

2.4. Characterization of PVA/BSF Protein Blend Films

2.4.1. Thermal Behaviour

Thermal characteristics were determined via Differential Scanning Calorimetry (DSC) and Thermogravimetric Analysis (TGA). A DSC 821e Mettler Toledo equipment (Schwerzenbach, Switzerland) was used, and data was processed using STARe SW 9.30 software. A 2–3 mg sample was inserted in an aluminium crucible and heated from 50 to 400 °C at a heating rate of 5 °C/min under a 10 mL/min nitrogen flow.

The relative crystallinity degree of PVA in the different films was calculated for reference to the pure PVA films by measuring the area of the melting peak corresponding to the melting enthalpy (ΔH_m) through the formula:

$$X_c(\%) = \frac{\Delta H_m}{\left(\frac{\%PVA}{100}\right) \times \Delta H_{m,100\%PVA}} \times 100 \quad (2)$$

where

X_c : relative crystallinity degree of PVA in films at different PVA concentrations

$\Delta H_{m,100\%PVA}$: PVA melting peak area in pure PVA sample

ΔH_m : PVA melting peak area in samples at different PVA concentrations

For TGA, thermograms were acquired using a TGA/DSC Mettler Toledo (Schwerzenbach, Switzerland) and processed using STARe SW 9.30. The software allows us to obtain both TGA curves and DTG derivatives. The analyses were carried out in 5–10 mg samples over a temperature range from 30 °C to 700 °C, with a constant heating rate of 10 °C/min under 70 mL/min nitrogen flow.

2.4.2. Solubility in Water

Films were dried in an oven at 50 °C until constant weight and then immersed in 50 mL distilled water at room temperature for 24 h under shaking (130 shaking/min). The films were then filtered under a vacuum to recover solid parts and dried at 50 °C until constant weight, as reported by Gontard et al. [43]. Each experiment was repeated in triplicate.

Solubility in water was calculated using the formula:

$$\text{Solubility in water}(\%) = \frac{w_i - w_f}{w_i} * 100 \quad (3)$$

where:

w_i : initial sample dry weight

w_f : final sample dry weight

2.4.3. Water Uptake

PVA/BSF protein films were dried in an oven at 50 °C and then conditioned in a room at 20 °C and 65% of relative humidity for at least 24 h before weighing each sample every hour for 8 h and then after 24 h, as reported by Patrucco et al. [44].

Experiments were conducted in triplicate and water uptake was calculated using the formula:

$$\text{Water Uptake}(\% w/w) = \frac{W_f - W_i}{W_i} * 100 \quad (4)$$

where:

W_i : initial dry weight

W_f : weight after *n hours in a conditioned environment

*n: 1, 2, 3, 4, 5, 6, 7, 8, 24 h

2.4.4. Morphological Characterization

Scanning Electron Microscopy (SEM) analysis was carried out on EVO 10 (CarlZeiss AG, Oberkochen, Germany) equipment using SmartSEM software with 20 µA of the current probe, an acceleration voltage of 20 kV, and 30 mm working distance. PVA/BSF protein films were mounted on aluminium stubs and made to adhere using a double-sided adhesive tape. Before analysis, samples were sputter-coated with a thin gold layer under a rarefied argon atmosphere.

2.4.5. Tensile Behaviour

Films were cut into strips 2 mm in width × 25 mm in length and were tested with a dynamometer ZwickRoell (GmbH Z005 ProLine 5 KN, Ulm, Germany) in a conditioned atmosphere at a constant rate of 10 mm/min according to the EN-ISO 5079 standard [45]. Data were processed using TestXPer III software. At least three measurements were carried out for each sample and tensile strength and elongation at break were reported. The thickness of each film was measured using a digital comparator (Fowler).

2.4.6. Contact Angle

For the contact angle measurement, an optical goniometer EasyDrop model from Krüss Scientific GmbH (Hamburg, Germany) was used with the sessile drop method. A 10.5 µL milliQ water drop was deposited on the film surface with a syringe and the angle formed by each film surface and the drop profile was measured. A total of 8 measurements were performed on each film to obtain the mean and standard deviation.

2.5. Biodegradation Testing in Soil

PVA/hydrolyzed BSF protein films were dried at 50 °C, put in nylon mesh bags and buried under natural soil in a pot as reported by Bhavsar et al. [41]. The soil was kept moist by periodic irrigation, and samples were removed after 10/20/30/60/90 days and dried again at 50 °C.

The determination of biodegradability in soil was calculated using the following formula:

$$\text{Weight loss}[\% w/w] = \frac{W_i - W_f}{W_i} \times 100 \quad (5)$$

where:

W_i : initial dry weight

W_f : dry weight after *n dyes of burial in soil

*n: 10/20/30/60/90 days

FTIR spectra were acquired on each film after soil removal.

3. Results

3.1. Characterization of BSF Larvae and BSF Protein Extracts

The extraction hydrolysis yields referred to the dry weight of the defatted BSF larvae were 45.51% *w/w* for the trial carried out at 160 °C, 13.77% *w/w* for the trial at 160 °C after pretreatment with HCl, and 45.96% *w/w* for the trial at 180 °C. The time was always 1 h and the solvent was pressurized water, which offers the advantages of sterilizing the material and obtaining the extracts directly in water, avoiding costly and time-consuming purification processes.

The low yield of the process preceded by HCl pretreatment is presumably due to the loss of material during pretreatment, neutralization, and rinses, while the similar extraction yield of the 160 °C and 180 °C processes suggests that the temperature of 160 °C for 1 h is sufficient to extract the proteins and is not necessary to increase temperature and consume more energy.

The FT-IR spectra of the three extracts are shown in Figure 2. They have similar absorptions mainly attributable to the presence of proteins. In fact, the peaks of Amide I at about 1650 cm^{-1} (C=O stretching), Amide II at about 1550 cm^{-1} (C=N stretching and N-H bending) and Amide III at about 1230 cm^{-1} (C-N stretching and N-H bending) are present and the peaks of Amide A at 3270 cm^{-1} and Amide b at 2930 cm^{-1} representing N-H stretching and C-H stretching, respectively, are also visible [46].




Figure 2. FTIR spectra of dried protein extracted from defatted BSF larvae at 160 °C, 160 °C after HCl pretreatment and 180 °C.

As observed in Figure 3, in BSF larvae spectra, there are present peaks from lipids at 2954 cm^{-1} ($-\text{CH}_3$ asymmetrical stretch), at 2922 and 2853 cm^{-1} (symmetrical and asymmetrical stretching of $-\text{CH}_2$), at 1743 cm^{-1} ($-\text{C}=\text{O}$ stretch), and at 1713 cm^{-1} corresponding to carbonyl absorption [47]. All these absorptions are not present in the hydrolysate as grease was removed by extraction with hexane.




Figure 3. FTIR spectra of BSF larvae, BSF dried proteins extracted, BSF dried solid part after hydrolysis.

Moreover, in the solid part remaining as a deposit not extracted with the superheated water, there is a strong absorption mainly due to the mineral fraction with the characteristic peak of calcite (CaCO_3) at 1030 cm^{-1} imputable to symmetric CO_3 stretching [48] while the absorptions of the chitin present in the larvae overlap with non-solubilized protein and the inorganic parts absorptions [24]. Finally, as previously stated, protein peaks referable to amides are clearly visible in the dried extract.

3.2. Characterization of PVA/BSF Protein Blend Films

All PVA/BSF protein blends showed good film-forming ability except for the higher amount of protein blends (10/90 and 0/100% *w/w*), which produced brittle films hard to peel from the cast.

The films show visual properties influenced by their composition. They generally appear quite smooth with an even material distribution. However, in samples with a high concentration of protein, surface irregularities emerge. Regarding coloration, films with a higher percentage of PVA appear more transparent, while those with a high protein composition are more opaque and brownish in color (see Figure 4).



Figure 4. The visual appearance of PVA/BSF protein films in % *w/w* 100/0, 90/10, 70/30, 50/50, 30/70, 10/90 and 0/100 from left to right.

3.3. FT-IR Spectroscopy

The PVA/BSF protein films at different compositions were characterized via FT-IR spectroscopy, as shown in Figure 5.




Figure 5. FTIR spectra of PVA/BSF protein films in % *w/w* 100/0, 90/10, 70/30, 50/50, 30/70, 10/90 and 0/100.

In films composed exclusively of PVA, the band located at about 3300 cm^{-1} appears broad and intense, highlighting intra- and intermolecular hydrogen bonds between the O-H groups of PVA. By increasing the protein concentration, this band broadens and reduces its intensity. Finally, in samples with low PVA amounts, the band becomes less defined, indicating the predominance of N-H stretching from BSF proteins.

In contrast, the Amide I band at about 1650 cm^{-1} and Amide II bands at about 1550 cm^{-1} are characteristic signals of proteins and increase with increasing BSF protein fraction in films [49].

Moreover, an intense peak at about 1100 cm^{-1} can be seen in the films with higher amounts of PVA, representing a symmetric C-C stretching mode or some stretching of the C-O bonds. This absorption is strongly associated with PVA crystallinity as referred to by Mansur et al. [50]. In blend films, this absorption reduces intensity as the protein content increases, showing a partial decrease in PVA content and its crystallinity.

From the FT-IR analysis, it can be concluded that PVA and BSF protein in films are bound by non-covalent bonds, and in particular, hydrogen bonds.

3.4. Thermal Behaviour

The DSC curves of the films at different percentages of PVA/BSF protein (see Figure 6) show a first endothermic peak of around $80\text{ }^{\circ}\text{C}$ attributable to water evaporation and a second endothermic peak at around $212\text{ }^{\circ}\text{C}$ for pure PVA, representing the melting point of the crystalline regions of PVA [51,52].




Figure 6. DSC traces of PVA/BSF protein films at different concentrations.

As the protein concentration increases in different films, there is a progressive decrease in the intensity of this peak correlated with the decrease in the crystallinity of PVA, while its temperature undergoes a progressive reduction from 212 °C of the pure PVA film to 201 °C of the PVA/BSF protein 30/70% *w/w* film. The percentage of crystallinity relative to the pure PVA sample of the different samples (except the PVA/BSF protein 10/90% *w/w* sample due to the absence of a significant crystalline phase) was calculated using Formula 2, and the results are shown in Table 1.

Table 1. PVA relative crystallinity degree and melting enthalpy area for its calculation.

PVA/BSF Protein (% <i>w/w</i>)	ΔH_f [J/g]	X_c [%]
100/0	-52.73 ± 0.24	100
90/10	-43.385 ± 2.42	82.28 ± 6.48
70/30	-34.01 ± 1.46	64.50 ± 3.92
50/50	-22.25 ± 1.09	42.20 ± 2.92
30/70	-16.18 ± 0.83	30.68 ± 2.23

A progressive reduction in the relative crystallinity of PVA can be seen as the protein fraction increases, reaching the value of 30.68% in the 30% PVA sample. This trend can be attributed to interactions between PVA and BSF proteins, which insert between PVA polymer chains, limiting the PVA crystallization process, favoring a prevalence of amorphous regions within the films and affecting their physical and mechanical properties.

Finally, an additional endothermic event emerges in the DSC traces at higher temperatures that could be associated with protein degradation.

The results of thermogravimetric analysis of PVA/BSF protein films at different concentrations are shown in Figure 7 and summarized in Table 2.




Figure 7. TGA traces of PVA/BSF protein films at different concentrations (a) and their first derivatives (b).

Table 2. TGA parameters of PVA/BSF protein films at different concentrations.

PVA/BSF Protein [% w/w]	T_{onset} [°C]	T_{peak} [°C]	Residue [% w/w]
100/0	332.9 ± 0.8	360.4 ± 2.9	7.6 ± 0.3
90/10	274.6 ± 1.8	302.5 ± 10.7	7.7 ± 1.1
70/30	267.7 ± 0.6	294.7 ± 6.2	15.1 ± 0.5
50/50	259.3 ± 1.5	291.8 ± 10.7	24.2 ± 3.7
30/70	241.8 ± 1.2	284.6 ± 7.2	23.3 ± 0.8
10/90	235.7 ± 0.7	283.7 ± 3.5	29.4 ± 2.3
0/100	128.1 ± 1.5	280.8 ± 2.6	35.5 ± 1.6

TGA traces show an initial weight loss due to water evaporation at temperatures below 120 °C and degradation at a T_{onset} that increases with increasing PVA concentration. This behaviour indicates that PVA promotes a stabilizing effect on the polymer matrix, delaying the T_{onset} of thermal decomposition. In particular, the pure protein film exhibits the lowest temperature of 128.1 °C, consistent with the nature of proteins, which tend to degrade due to denaturation of their structures and disruption of intermolecular bonds. Minimal addition of PVA leads to a significant increase in T_{onset} , which reaches 235.7 °C, highlighting the strong stabilizing impact of PVA. With increasing PVA concentration, a gradual T_{onset} increase is observed until it reaches 332.9 °C in the case of pure PVA.

The final residue shown in Table 2 was calculated as a function of the dry weight of the films, excluding the part of the curve where the weight loss is due to water evaporation.

The final residue of 35.5% w/w in the pure protein sample indicates the BSF protein's tendency to leave a significant carbonaceous residue after thermal decomposition rather than decomposing completely into volatile compounds. The residue progressively decreases with the addition of PVA, showing that pyrolysis is increasingly complete due to the PVA contribution. A final residue of 7.6% w/w is achieved in pure PVA samples.

Finally, from the DTG (Derivative Thermogravimetry) curves, the peak temperature represents when the material decomposes at the maximum rate. In the pure protein sample, the DTG peak occurs at 280.8 °C, corresponding to the degradation of polypeptide chains [53]. As PVA increases in films, an increasingly pronounced shift of the peak toward

higher temperatures is observed until it reaches 360.4 °C with pure PVA, confirming the stabilizing PVA impact.

3.5. Solubility in Water

Experimental results (see Figure 8a) show different film solubilities in water depending on the concentration of PVA and protein. In general, as the concentration of PVA increases, a progressive decrease in film solubility is observed, and a decrease in the standard deviation related to inhomogeneity in film structure. This behaviour reflects both the higher solubility of BSF protein compared to PVA and a structural transition of the material from an amorphous to a more crystalline configuration that is less accessible to water [54]. The decrease in the PVA crystallinity correlated with the increase in protein concentration in films was demonstrated via previous DSC analysis.




Figure 8. Solubility in water (a) and water uptake (b) of PVA/BSF protein films at different concentrations.

3.6. Water Uptake

Analysis of water uptake curves (see Figure 8b) shows a significant increase in water uptake in the first eight hours for all the PVA/BSF protein films analyzed, followed by a gradual slowdown leading to a plateau within 24 h.

Films with a high concentration of PVA show consistently lower water uptake values at each time step. This behavior is attributable to the crystalline structure of PVA, which organizes its polymer chains into ordered and compact configurations, reducing the space available for water molecules and limiting the mobility of polymer chains, which further hinders water uptake. In addition, the low standard deviation observed in these samples suggests homogeneous and predictable behavior due to the uniform distribution of PVA within the material. In contrast, films with higher protein concentrations exhibit significantly higher water uptake. Proteins, predominantly amorphous, offer more hydrophilic sites, such as amine and carboxyl groups, which can form hydrogen bonds with water. This disordered structure promotes rapid absorption in the early stages and a greater ability to retain moisture. In addition, the data show greater variability in samples with high protein content, which can be attributed to local inhomogeneities in protein distribution.

3.7. Morphological Characterization

Figure 9 shows the surfaces of the PVA/BSF protein films at different concentrations at 100× magnification.




Figure 9. SEM pictures at 100 \times of PVA/BSF protein films at different concentration 100/0, 90/10, 70/30, 50/50, 30/70, 10/90 and 0/100 (% *w/w*).

For the pure PVA film, the surface appears smooth and homogeneous, confirming that the material forms an isotropic and stable matrix. At 10% protein addition, slight inhomogeneities emerge, but no porosity is detected and the polymer matrix retains its cohesion. Increasing the protein amount, small, randomly distributed cracks begin to appear, and some areas of the film appear darker, suggesting the presence of microvoids or areas of reduced density, given the onset of phase separation between PVA and BSF protein. In PVA/BSF 30/70% *w/w* protein films, the surface is characterized by a network of interconnected cracks, making the material less resistant to mechanical stress. In PVA/BSF 10/90% *w/w* protein films, proteins aggregate and don't integrate properly with the remaining PVA.

Moreover, film porosity is very pronounced, and the uneven distribution of proteins creates weak points that promote fracture formation. Finally, the neat protein film shows separate fragments. Analogous results were obtained by Rajabinejad et al. in similar materials [55].

3.8. Tensile Behaviour

The tensile mechanical properties of the films at different PVA/BSF protein concentrations are summarized in Table 3. For pure PVA films, the tensile strength of 8 MPa is attributable to the uniform and stable crystal structure of PVA, which ensures a homogeneous distribution of mechanical stress. By introducing protein, the tensile strength first slowly increases until 70/30% *w/w* PVA/BSF protein, suggesting that protein acts as a plasticizer, promoting a balanced stress distribution and stability of the crystalline network. When increasing the amount of protein until 70% *w/w*, however, the tensile strength decreases strongly as the crystalline network appears to be compromised by protein dominance. As the amount of protein increases, the elongation at break gradually increases until 30% *w/w* of protein. In particular, for the neat PVA film, the elongation at the break is 160.6%, which reflects a medium ductility of this polymer. Adding 10% and 30% protein, the film strain rises slightly, suggesting an increase in plasticization. As the protein content increases, the strain decreases and the material becomes brittle. At 50% and 30% protein content in the films, little necking has been observed.

Table 3. Tensile strength, elongation at break and modulus of PVA/BSF protein films at different concentration.

PVA/BSF Protein [% <i>w/w</i>]	Tensile Strength [MPa]	Elongation at Break [%]
100/0	8 ± 1.04	160.6 ± 14.0
90/10	11.3 ± 2.55	236.4 ± 38.7
70/30	11.35 ± 0.68	212.8 ± 40.4
50/50	6.85 ± 1.05	43.75 ± 4.45
30/70	3.21 ± 0.84	26.6 ± 16.8

3.9. Contact Angle


From Table 4, it can be seen that as the percentage of protein increases, the contact angle decreases from $67.6 \pm 0.41^\circ$ of pure PVA to $53.7 \pm 0.95^\circ$ of PVA/BSF protein 30/70% *w/w*, indicating greater film hydrophilicity. In addition, the standard deviation becomes more and more pronounced due to the increasingly irregular surface. Pure PVA film has hydrophilic functional groups; however, in the crystalline component, the denser packing of polymer chains limits exposure of hydrophilic groups, which has a direct impact on the wettability properties of the material. In films with 90% PVA, the proteins introduce polar groups that promote hydrogen bonds with water. Although PVA remains predominant, it maintains some resistance to liquid diffusion. As protein content increases, the contact angle decreases further due to protein functional groups facilitating interaction with water molecules. In addition, the increase in hydrophilicity as the protein amount increases could be related to the roughness of the films, as shown by SEM images [56].

Table 4. Contact angle values of PVA/BSF protein films at different concentrations.

PVA/BSF Protein [% w/w]	Contact Angle
100/0	$67.6 \pm 0.41^\circ$
90/10	$65.6 \pm 0.54^\circ$
70/30	$59.7 \pm 0.67^\circ$
50/50	$56.1 \pm 0.80^\circ$
30/70	$53.7 \pm 0.95^\circ$

3.10. Biodegradation Testing in Soil

Figure 10 summarizes the weight losses of PVA/BSF protein films at different concentrations after 10, 20, 30, 60 and 90 days of burial in soil.

**Figure 10.** Weight loss of PVA/BSF protein films with different compositions after 10, 20, 30, 60, and 90 days of burial in the soil.

The curves show that samples with a higher protein content degrade more rapidly, while films with a higher percentage of PVA are more resistant to soil degradation. The degradation is generally characterized by a rapid initial mass loss, followed by a gradual slowdown. The pure PVA film shows a weight loss of 12% w/w after 90 days, confirming poor biodegradability in the soil, as confirmed by other authors [57], because few microorganisms present in the soil can biodegrade PVA [58]. As the percentage of protein increases, the sample weight loss increases until 80% w/w after 90 days of soil burial for the 30/70% w/w PVA/BSF protein sample. Lowering and disappearance of the Amide I (1650 cm^{-1}) and Amide II (1550 cm^{-1}) absorption peaks in FTIR spectra of biodegraded films highlight

that the proteins are degraded in soil faster than PVA. This behaviour of rapid protein degradation in soil is confirmed by Dani et al. [59].

4. Conclusions

The present work focused on the production and characterization of bioplastics, combining PVA with proteins extracted from BSF larvae with superheated water without the use of harsh chemical reagents. The main objective was to develop a material which is adaptable to different applications, sustainable and biodegradable, and which can be a viable alternative to conventional plastics, which are not biodegradable and obtained from non-renewable sources. The experimental approach has started from the preparation of raw materials until the characterization of the properties of bioplastics obtained from PVA/BSF protein at different concentrations. FTIR analysis showed the formation of hydrogen bonds that ensure good cohesion of the polymer matrix. However, a nonuniform distribution of proteins within the polymer matrix is shown, with a tendency for aggregate formation affecting the material's mechanical properties, with decreased tensile properties in films with high protein content. In addition, films with higher protein content show higher water uptake, water solubility, hydrophilicity, and faster biodegradation in soil than films with higher PVA content. PVA/BSF protein bioplastics can be used as biodegradable packaging or as agricultural mulches, modulating the relative amount of PVA and BSF protein and taking advantage of the increased mechanical strength of films with higher concentrations of PVA and the increased biodegradability of films with a higher content of BSF protein. The optimization of these materials and their introduction into large-scale production processes could represent important progress for the sustainable materials industry, helping to reduce the environmental impact associated with the use of traditional plastics.

Author Contributions: Conceptualization, M.Z. and S.D.V.; Methodology, A.M. and G.D.F.; Investigation, A.D.P., G.D.F. and A.A.; Resources, M.Z.; Data Curation, G.D.F. and A.A.; Writing—Original Draft Preparation, M.Z. and A.D.P.; Writing—Review and Editing, A.M. and S.D.V.; Supervision, S.D.V.; Funding Acquisition, M.Z. All authors have read and agreed to the published version of the manuscript.

Funding: The research was funded by the research project HI-Tech “Hermetia illucens biofactory: from waste to high-value technological products”, PRIN 2022 (D.D. MUR n.104 del 2 February 2022).

Institutional Review Board Statement: Not applicable.

Data Availability Statement: All the data will be made available on specific request.

Conflicts of Interest: The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

References

1. Caligiani, A.; Marseglia, A.; Leni, G.; Baldassarre, S.; Maistrello, L.; Dossena, A.; Sforza, S. Composition of black soldier fly prepupae and systematic approaches for extraction and fractionation of proteins, lipids and chitin. *Food Res. Int.* **2018**, *105*, 812–820. [[CrossRef](#)]
2. Edea, C.; Tesfaye, E.; Yirgu, T.; Alewi, M. Black soldier fly (*Hermetia illucens*) larvae as a sustainable source of protein in poultry feeding: A review. *Ethiop. J. Agric. Sci.* **2022**, *32*, 89–104.
3. Nguyen, T.-X.; Tomberlin, J.; Vanlaerhoven, S. Ability of Black Soldier Fly (Diptera: Stratiomyidae) Larvae to Recycle Food Waste. *Environ. Entomol.* **2015**, *44*, 406–410. [[CrossRef](#)] [[PubMed](#)]
4. Van Huis, A.; Gasco, L. Insects as feed for livestock production. *Science* **2023**, *379*, 138–139. [[CrossRef](#)]
5. Odongo, E.E.; Bbosa, W.K.; Kahunde, P.K. Black Soldier Fly (BSF): A Sustainable Solution for Protein, Waste Management, and a Circular Bio-Economy. *Eur. J. Theor. Appl. Sci.* **2024**, *2*, 822–834. [[CrossRef](#)]

6. Regulation (EC) No. 1069/2009 of the European Parliament and of the Council of 21 October 2009 Laying Down Health Rules as Regards Animal by-Products and Derived Products Not Intended for Human Consumption and Repealing Regulation (EC) No. 1774/2002. Available online: <https://eur-lex.europa.eu/eli/reg/2009/1069/oj/eng> (accessed on 14 November 2009).
7. Commission Regulation (EU) 2017/1017 of 15 June 2017 Amending Regulation (EU) No. 68/2013 on the Catalogue of Feed Materials. Available online: <https://eur-lex.europa.eu/eli/reg/2017/1017/oj/eng> (accessed on 21 June 2017).
8. IPIFF Vision Paper on the Future of the Insect Sector Towards 2030. The European Insect Sector Today: Challenges, Opportunities and Regulatory Landscape. Available online: <https://ipiff.org/ipiff-vision-paper/> (accessed on 7 March 2022).
9. Fowles, T.M.; Nansen, C. *Insect-Based Bioconversion: Value from Food Waste BT—Food Waste Management: Solving the Wicked Problem*; Närvänen, E., Mesiranta, N., Mattila, M., Heikkinen, A., Eds.; Springer International Publishing: Cham, Switzerland, 2020; pp. 321–346, ISBN 978-3-030-20561-4.
10. Ravi, H.K.; Degrou, A.; Costil, J.; Trespeuch, C.; Chemat, F.; Vian, M.A. Larvae Mediated Valorization of Industrial, Agriculture and Food Wastes: Biorefinery Concept through Bioconversion, Processes, Procedures, and Products. *Processes* **2020**, *8*, 857. [CrossRef]
11. Shaboon, A.M.; Qi, X.; Omar, M.A.A. *Insect-Mediated Waste Conversion BT—Waste-to-Energy: Recent Developments and Future Perspectives Towards Circular Economy*; Abomohra, A.E.-F., Wang, Q., Huang, J., Eds.; Springer International Publishing: Cham, Switzerland, 2022; pp. 479–509, ISBN 978-3-030-91570-4.
12. Ragossnig, H.A.; Ragossnig, A.M. Biowaste treatment through industrial insect farms: One bioeconomy puzzle piece towards a sustainable net-zero carbon economy? *Waste Manag. Res. J. Sustain. Circ. Econ.* **2021**, *39*, 1005–1006. [CrossRef] [PubMed]
13. Siddiqui, S.A.; Ristow, B.; Rahayu, T.; Putra, N.S.; Widya Yuwono, N.; Nisa', K.; Mategeko, B.; Smetana, S.; Saki, M.; Nawaz, A.; et al. Black soldier fly larvae (BSFL) and their affinity for organic waste processing. *Waste Manag.* **2022**, *140*, 1–13. [CrossRef]
14. Eurostat 2024. Available online: <https://ec.europa.eu/eurostat/web/products-eurostat-news/w/ddn-20240927-2#:~:text=> (accessed on 27 September 2024).
15. Nayak, A.; Bhushan, B. An overview of the recent trends on the waste valorization techniques for food wastes. *J. Environ. Manag.* **2019**, *233*, 352–370. [CrossRef]
16. Smets, R.; Verbinnen, B.; Van De Voorde, I.; Aerts, G.; Claes, J.; Van Der Borgh, M. Sequential Extraction and Characterisation of Lipids, Proteins, and Chitin from Black Soldier Fly (*Hermetia illucens*) Larvae, Prepupae, and Pupae. *Waste Biomass Valorization* **2020**, *11*, 6455–6466. [CrossRef]
17. Martín-López, H.; Ayora-Talavera, T.; Liedo, P.; Ramos-Díaz, A.; Herrera-Rodríguez, S.; Cuevas-Bernardino, J.C.; Pacheco, N. The Mexican fruit fly puparia (*Anastrepha ludens*) and the black soldier fly imagoes (*Hermetia illucens*), promising alternative sources of chitin. *MRS Adv.* **2024**, *9*, 1747–1753. [CrossRef]
18. Ai, H.; Wang, F.; Yang, Q.; Zhu, F.; Lei, C. Preparation and biological activities of chitosan from the larvae of housefly, *Musca domestica*. *Carbohydr. Polym.* **2008**, *72*, 419–423. [CrossRef]
19. Batish, I.; Brits, D.; Valencia, P.; Miyai, C.; Rafeeq, S.; Xu, Y.; Galanopoulos, M.; Sismour, E.; Ovissipour, R. Effects of Enzymatic Hydrolysis on the Functional Properties, Antioxidant Activity and Protein Structure of Black Soldier Fly (*Hermetia illucens*) Protein. *Insects* **2020**, *11*, 876. [CrossRef] [PubMed]
20. McNeil, S.J.; Sunderland, M.R.; Zaitseva, L.I. Closed-loop wool carpet recycling. *Resour. Conserv. Recycl.* **2007**, *51*, 220–224. [CrossRef]
21. Bhavsar, P.; Patrucco, A.; Montarsolo, A.; Mossotti, R.; Rovero, G.; Giansetti, M.; Tonin, C. Superheated Water Hydrolysis of Waste Wool in a Semi-Industrial Reactor to Obtain Nitrogen Fertilizers. *ACS Sustain. Chem. Eng.* **2016**, *4*, 6722–6731. [CrossRef]
22. Yin, J.; Rastogi, S.; Terry, A.E.; Popescu, C. Self-organization of Oligopeptides Obtained on Dissolution of Feather Keratins in Superheated Water. *Biomacromolecules* **2007**, *8*, 800–806. [CrossRef]
23. Bhavsar, P.; Dalla Fontana, G.; Tonin, C.; Patrucco, A.; Zoccola, M. Superheated water hydrolyses of waste silkworm pupae protein hydrolysate: A novel application for natural dyeing of silk fabric. *Dye. Pigment.* **2020**, *183*, 108678. [CrossRef]
24. Bhavsar, P.S.; Dalla Fontana, G.; Zoccola, M. Sustainable Superheated Water Hydrolysis of Black Soldier Fly Exuviae for Chitin Extraction and Use of the Obtained Chitosan in the Textile Field. *ACS Omega* **2021**, *6*, 8884–8893. [CrossRef]
25. Caringella, R.; Bhavsar, P.; Dalla Fontana, G.; Patrucco, A.; Tonin, C.; Pozzo, P.D.; Zoccola, M. Fabrication and properties of keratose/sericin blend films. *Polym. Bull.* **2022**, *79*, 2189–2204. [CrossRef]
26. Barbi, S.; Spinelli, R.; Ferrari, A.M.; Montorsi, M. Design and environmental assessment of bioplastics from *Hermetia illucens* prepupae proteins. *Environ. Eng. Manag. J.* **2019**, *18*, 2123–2131.
27. Barbi, S.; Messori, M.; Manfredini, T.; Pini, M.; Montorsi, M. Rational design and characterization of bioplastics from *Hermetia illucens* prepupae proteins. *Biopolymers* **2019**, *110*, e23250. [CrossRef] [PubMed]
28. Bonilla, J.; Fortunati, E.; Atarés, L.; Chiralt, A.; Kenny, J.M. Physical, structural and antimicrobial properties of poly vinyl alcohol–chitosan biodegradable films. *Food Hydrocoll.* **2014**, *35*, 463–470. [CrossRef]
29. Dou, Y.; Zhang, B.; He, M.; Yin, G.; Cui, Y.; Savina, I.N. Keratin/Polyvinyl Alcohol Blend Films Cross-Linked by Dialdehyde Starch and Their Potential Application for Drug Release. *Polymers* **2015**, *7*, 580–591. [CrossRef]

30. Limpan, N.; Prodran, T.; Benjakul, S.; Prasarpran, S. Influences of degree of hydrolysis and molecular weight of poly(vinyl alcohol) (PVA) on properties of fish myofibrillar protein/PVA blend films. *Food Hydrocoll.* **2012**, *29*, 226–233. [[CrossRef](#)]
31. Abdullah, Z.W.; Dong, Y.; Davies, I.J.; Barbhuiya, S. PVA, PVA Blends, and Their Nanocomposites for Biodegradable Packaging Application. *Polym. Plast. Technol. Eng.* **2017**, *56*, 1307–1344. [[CrossRef](#)]
32. Pathak, V.M.; Navneet. Review on the current status of polymer degradation: A microbial approach. *Bioresour. Bioprocess.* **2017**, *4*, 15. [[CrossRef](#)]
33. Hong, M.; Chen, E.Y.-X. Chemically recyclable polymers: A circular economy approach to sustainability. *Green Chem.* **2017**, *19*, 3692–3706. [[CrossRef](#)]
34. Costa, A.; Encarnaç o, T.; Tavares, R.; Todo Bom, T.; Mateus, A. Bioplastics: Innovation for Green Transition. *Polymers* **2023**, *15*, 517. [[CrossRef](#)]
35. Asgher, M.; Qamar, S.A.; Bilal, M.; Iqbal, H.M.N. Bio-based active food packaging materials: Sustainable alternative to conventional petrochemical-based packaging materials. *Food Res. Int.* **2020**, *137*, 109625. [[CrossRef](#)]
36. Kuddus, M.; Roohi. *Bioplastics for Sustainable Development*; Springer: Singapore, 2021; ISBN 978-981-16-1822-2.
37. Reichert, C.L.; Bugnicourt, E.; Coltelli, M.-B.; Cinelli, P.; Lazzeri, A.; Canesi, I.; Braca, F.; Mart nez, B.M.; Alonso, R.; Agostinis, L.; et al. Bio-Based Packaging: Materials, Modifications, Industrial Applications and Sustainability. *Polymers* **2020**, *12*, 1558. [[CrossRef](#)]
38. Maraveas, C. Production of Sustainable and Biodegradable Polymers from Agricultural Waste. *Polymers* **2020**, *12*, 1127. [[CrossRef](#)] [[PubMed](#)]
39. Lambert, S.; Wagner, M. Environmental performance of bio-based and biodegradable plastics: The road ahead. *Chem. Soc. Rev.* **2017**, *46*, 6855–6871. [[CrossRef](#)] [[PubMed](#)]
40. Tian, L.; Jinjin, C.; Ji, R.; Ma, Y.; Yu, X. Microplastics in agricultural soils: Sources, effects, and their fate. *Curr. Opin. Environ. Sci. Health* **2022**, *25*, 100311. [[CrossRef](#)]
41. Bhavsar, P.; Balan, T.; Dalla Fontana, G.; Zoccola, M.; Patrucco, A.; Tonin, C. Sustainably Processed Waste Wool Fiber-Reinforced Biocomposites for Agriculture and Packaging Applications. *Fibers* **2021**, *9*, 55. [[CrossRef](#)]
42. Setti, L.; Francia, E.; Pulvirenti, A.; De Leo, R.; Martinelli, S.; Maistrello, L.; Macavei, L.I.; Montorsi, M.; Barbi, S.; Ronga, D. Bioplastic Film from Black Soldier Fly Prepupae Proteins Used as Mulch: Preliminary Results. *Agronomy* **2020**, *10*, 933. [[CrossRef](#)]
43. Gontard, N.; Guilbert, S.; Cuq, J.-L. Edible Wheat Gluten Films: Influence of the Main Process Variables on Film Properties using Response Surface Methodology. *J. Food Sci.* **1992**, *57*, 190–195. [[CrossRef](#)]
44. Patrucco, A.; Zoccola, M.; Consonni, R.; Tonin, C. Wool cortical cell-based porous films. *Text. Res. J.* **2013**, *83*, 1563–1573. [[CrossRef](#)]
45. *EN-ISO 5079 (1995)*; Determination of Breaking Force and Elongation at Break of Individual Fibers. International Organization for Standardization: Geneva, Switzerland, 1995.
46. Queiroz, L.S.; Regnard, M.; Jessen, F.; Mohammadifar, M.A.; Sloth, J.J.; Petersen, H.O.; Ajallouei, F.; Brouzes, C.M.C.; Fraihi, W.; Fallquist, H.; et al. Physico-chemical and colloidal properties of protein extracted from black soldier fly (*Hermetia illucens*) larvae. *Int. J. Biol. Macromol.* **2021**, *186*, 714–723. [[CrossRef](#)]
47. Mahmood, T.; Malik, M.; Bano, A.; Umer, J.; Shaheen, A. Nanocatalytic Conversion of Waste Palm Oil Grade III and Poplar Plant’s Wood Sawdust into Fuel. *Innov. Energy Res.* **2017**, *6*, 1000170. [[CrossRef](#)]
48. Tinti, A.; Tugnoli, V.; Bonora, S.; Francioso, O. Recent applications of vibrational mid-Infrared (IR) spectroscopy for studying soil components: A review. *J. Cent. Eur. Agric.* **2015**, *16*, 1–22. [[CrossRef](#)]
49. Gou, M.X.; Yang, X.H. Preparation and Characterization of Wool Keratin/PVA Blended Films. *Adv. Mater. Res.* **2011**, *175–176*, 132–136. [[CrossRef](#)]
50. Mansur, H.S.; Sadahira, C.M.; Souza, A.N.; Mansur, A.A.P. FTIR spectroscopy characterization of poly (vinyl alcohol) hydrogel with different hydrolysis degree and chemically crosslinked with glutaraldehyde. *Mater. Sci. Eng. C* **2008**, *28*, 539–548. [[CrossRef](#)]
51. Hyder, M.N.; Huang, R.Y.M.; Chen, P. Correlation of physicochemical characteristics with pervaporation performance of poly(vinyl alcohol) membranes. *J. Memb. Sci.* **2006**, *283*, 281–290. [[CrossRef](#)]
52. Nakano, Y.; Bin, Y.; Bando, M.; Nakashima, T.; Okuno, T.; Kurosu, H.; Matsuo, M. Structure and Mechanical Properties of Chitosan/Poly(Vinyl Alcohol) Blend Films. *Macromol. Symp.* **2007**, *258*, 63–81. [[CrossRef](#)]
53. Mshayisa, V.V.; Van Wyk, J.; Zozo, B.; Rodr guez, S.D. Structural properties of native and conjugated black soldier fly (*Hermetia illucens*) larvae protein via Maillard reaction and classification by SIMCA. *Heliyon* **2021**, *7*, e07242. [[CrossRef](#)]
54. Silva, G.G.D.; Sobral, P.J.A.; Carvalho, R.A.; Bergo, P.V.A.; Mendieta-Taboada, O.; Habitante, A.M.Q.B. Biodegradable Films Based on Blends of Gelatin and Poly (Vinyl Alcohol): Effect of PVA Type or Concentration on Some Physical Properties of Films. *J. Polym. Environ.* **2008**, *16*, 276–285. [[CrossRef](#)]
55. Rajabinejad, H.; Zoccola, M.; Patrucco, A.; Montarsolo, A.; Chen, Y.; Ferri, A.; Muresan, A.; Tonin, C. Fabrication and properties of keratases/polyvinyl alcohol blend films. *Polym. Bull.* **2020**, *77*, 3033–3046. [[CrossRef](#)]
56. Jayasekara, R.; Harding, I.; Bowater, I.; Christie, G.B.Y.; Lonergan, G.T. Preparation, surface modification and characterisation of solution cast starch PVA blended films. *Polym. Test.* **2004**, *23*, 17–27. [[CrossRef](#)]

57. Chiellini, E.; Corti, A.; D'Antone, S.; Solaro, R. Biodegradation of poly (vinyl alcohol) based materials. *Prog. Polym. Sci.* **2003**, *28*, 963–1014. [[CrossRef](#)]
58. Ishigaki, T.; Kawagoshi, Y.; Ike, M.; Fujita, M. Biodegradation of a polyvinyl alcohol-starch blend plastic film. *World J. Microbiol. Biotechnol.* **1999**, *15*, 321–327. [[CrossRef](#)]
59. Jagadeesh, D.; Jeevan Prasad Reddy, D.; Varada Rajulu, A.; Li, R. Green composites from wheat protein isolate and Hildegardia Populifolia natural fabric. *Polym. Compos.* **2011**, *32*, 398–406. [[CrossRef](#)]

Disclaimer/Publisher's Note: The statements, opinions and data contained in all publications are solely those of the individual author(s) and contributor(s) and not of MDPI and/or the editor(s). MDPI and/or the editor(s) disclaim responsibility for any injury to people or property resulting from any ideas, methods, instructions or products referred to in the content.